

Article

Optimization of Strain and Doping in Ge/GeSi Nanoscale Multilayers for GOI Short-Wave Infrared Imaging Applications

Xuewei Zhao *, Yuanhao Miao *, Jiale Su , Junhao Du , Yuhui Ren , Ben Li, Tianyu Dong, Xiangliang Duan, Xueyin Su and Henry H. Radamson *

Research and Development Center of Optoelectronic Hybrid IC, Guangdong Greater Bay Area Institute of Integrated Circuit and System, Guangzhou 510535, China

* Correspondence: zhaoxuewei@giics.com.cn (X.Z.); miaoyuanhao@giics.com.cn (Y.M.); rad@giics.com.cn (H.H.R.)

Abstract

In this study, in situ P-doping of Ge-based layers has been studied and compared with implanted layer profiles acting as absorbent top layer in PIN photodetectors. Several structures containing multilayers of n^+ -Ge/i-Ge, n^+ -GeSi/i-Ge, and n^+ -Ge/i-GeSi, were designed to regulate dopant out-diffusion and interface quality. The purpose of this study is to make an optimized n-type doping layer for PIN photodetectors with low dark current, high responsivity, and high quantum efficiency operating in short wavelength infrared (SWIR) region. The Ge-based structure on Si substrate was transferred to oxidized Si substrate and was finally back-etched from Si to form Ge-on-insulator (GOI) substrate. Comprehensive characterization using high-resolution X-ray diffraction (HR-XRD), secondary ion mass spectrometry (SIMS), scanning electron microscopy (SEM), transmission electron microscopy (TEM), atomic force microscopy (AFM), and photoluminescence (PL) have been applied at the first stage of our work. The initial Ge layer contains tensile strain of 0.15–0.17%. PL measurements further indicate a redshift of the Γ -LH transition and carrier-concentration-induced quenching at high doping levels, highlighting the competing effects of band filling and non-radiative recombination in heavily n-doped Ge structures. To circumvent this fundamental trade-off, we devised a decoupled device strategy in which the active absorption region employs an intrinsic Ge/GeSi nanoscale multilayer structure to preserve crystal and interface quality. Although, the epitaxial growth parameters were on the optimized conditions, still out-diffusion (in form of segregation and auto-doping) of P could not be impeded. Our final n-type layer in PIN structure was formed by implantation. This approach yields high-performance photodetectors with a peak responsivity of 0.99 A/W at 1550 nm, a corresponding external quantum efficiency of 79%, and low specific contact resistivities of $2.66 \times 10^{-6} \Omega \cdot \text{cm}^2$ (n-type) and $1.38 \times 10^{-8} \Omega \cdot \text{cm}^2$ (p-type). This work demonstrates that the strategic combination of multilayer/interface engineering and ion-implantation-based doping is a highly effective strategy for tailoring the optoelectronic properties of Ge-based nanomaterials for high-performance SWIR photodetection.

Keywords: Ge; n-type doping; GeSi/Ge multilayers; SWIR; photodetectors (PDs)



Academic Editor: Werner Blau

Received: 7 January 2026

Revised: 5 February 2026

Accepted: 19 February 2026

Published: 26 February 2026

Copyright: © 2026 by the authors.

Licensee MDPI, Basel, Switzerland.

This article is an open access article distributed under the terms and conditions of the [Creative Commons Attribution \(CC BY\)](https://creativecommons.org/licenses/by/4.0/) license.

1. Introduction

High-performance, monolithic short-wave infrared (SWIR) photodetectors (PDs) are essential for the development of next-generation silicon optoelectronics, owing to their critical roles in emerging applications such as biomedical imaging [1,2], autonomous

sensing [3,4], telecommunications [5,6], and quantum imaging [7,8]. Current technological paradigms are defined by fundamental material compromises. III–V compound semiconductors (e.g., InGaAs/InP) offer superior sensitivity but incur prohibitive costs and complexity in hybrid integration [9–12]. Colloidal quantum dots provide spectral agility through solution processing, yet face intrinsic limitations in long-term stability and lithographic compatibility [13–16]. While epitaxial Ge-on-Si affords a fully group-IV pathway, its performance is frequently constrained by defect-mediated recombination, dopant non-uniformity, and limited optical confinement [17,18]. Within this landscape, germanium-on-insulator (GOI) has emerged as a strategically optimized platform, combining enhanced optical isolation with full CMOS-process compatibility [19–26]. However, to fully exploit the potential of GOI for scalable SWIR systems, precise nanoscale control over dopants, strain, and band structure within the epitaxial Ge layer is essential—a challenge that motivates advanced multilayer structure engineering [27–32].

To transcend the performance limits of conventional Ge-based designs, band-structure engineering via epitaxial multilayer structures has been widely explored [33–44]. A prevalent approach employs Ge/GeSi nanoscale multilayers, which utilize pseudomorphic strain to introduce conduction-band offsets and improve carrier confinement [45–50]. However, strain-only designs encounter an intrinsic thermodynamic constraint: the Si fraction in GeSi barriers is typically limited to $\leq 30\%$ to preserve epitaxial coherence, imposing a fundamental ceiling on band discontinuity and leading to performance plateaus in quantum efficiency [51–57]. This highlights a critical deficiency in the group-IV toolkit: the lack of a second, independently tunable parameter to cooperatively optimize band alignment and carrier population [58–63]. Heavy n-type doping has been proposed as such a complementary degree of freedom [64–73]. At high phosphorus concentrations ($>1 \times 10^{19} \text{ cm}^{-3}$), pronounced band-gap renormalization and Fermi-level engineering can be achieved [74–78]. When combined with tensile strain, a synergistic mechanism emerges: strain reduces the L- Γ valley separation, while high electron concentrations raise the Fermi level to preferentially populate the Γ -valley, thereby enhancing the effective direct-gap character [79–87]. While theoretically promising, the practical implementation of this dual-parameter (strain and doping) strategy—particularly within the complex geometry of nanoscale multilayer structures—remains largely unexplored. Key challenges include managing dopant interdiffusion, mitigating doping-induced non-radiative recombination, and preserving interface integrity, all of which are critical for device performance [88–93].

To address these challenges, this work adopts a hierarchical experimental strategy that progresses from fundamental material assessment to structurally engineered nanoscale multilayer structures and culminates in a functional device demonstration. We first investigate uniform n-type Ge epitaxial films grown on Si with five distinct phosphorus doping concentrations: 2×10^{18} , 3×10^{18} , 4×10^{18} , 9×10^{18} , and $2 \times 10^{19} \text{ cm}^{-3}$. The doping-dependent strain, crystal quality, and bandgap characteristics of the films were analyzed by high-resolution X-ray diffraction (HR-XRD) and photoluminescence (PL) spectroscopy. Building on this understanding, we then probe the coupled effects in a more device-relevant geometry by designing and synthesizing doping-modulated nanoscale multilayer structures (n^+ -Ge/i-Ge, n^+ -GeSi/i-Ge, and n^+ -Ge/i-GeSi) that are designed and grown to probe the coupled effects of doping, composition, and strain; subsequently, a systematic multiscale analysis of their structure and composition was conducted using scanning electron microscopy (SEM), atomic force microscopy (AFM), cross-sectional transmission electron microscopy (TEM), and secondary ion mass spectrometry (SIMS). These studies uncover a critical constraint: while high doping can be spatially confined, it inevitably introduces significant non-radiative recombination and degrades interface sharpness, thereby compromising the optical efficiency of the active region. To transcend

this material-level compromise, we introduce and demonstrate a decoupled design principle for the final device. The optical absorption region employs an intrinsic Ge/GeSi nanoscale multilayer structure, optimized for strain and carrier confinement while remaining undoped to maximize material quality. Conversely, the electrical p-n junction is precisely defined using ion implantation and rapid thermal annealing. This approach strategically isolates the optical optimization from the doping process. Consequently, the core innovation of this work evolves from merely exploring the strain–doping synergy to establishing a manufacturable integration strategy that leverages nanoscale material engineering for optical performance while utilizing conventional processing for electrical function. This work establishes a clear pathway from fundamental nanoscale material insights to high-performance, CMOS-compatible SWIR detectors, providing a practical framework for next-generation Si-based optoelectronic systems.

2. Materials and Methods

Phosphorus-doped Ge epitaxial films were grown on (100)-oriented p-type Si substrates using RPCVD (ASM Epsilon 2000, Almere, The Netherlands). To accommodate the large lattice mismatch between Ge and Si, a conventional low-temperature/high-temperature (LT/HT) two-step epitaxial strategy was employed. Specifically, a thin Ge buffer layer was first deposited at 400 °C to suppress island formation and promote continuous nucleation, followed by the growth of a thick, high-quality Ge layer at 650 °C. In situ phosphorus doping was introduced during the high-temperature growth step. To systematically investigate the influence of in situ doping concentration on structural and optical properties, five samples with monotonically increasing phosphorus concentrations were prepared, spanning from 2×10^{18} to $2 \times 10^{19} \text{ cm}^{-3}$. This well-controlled doping series enabled a quantitative assessment of dopant-induced strain modulation, defect evolution, and optical response. The total thickness of Ge was $\sim 1 \text{ }\mu\text{m}$. After epitaxy, a 20 nm SiO₂ capping layer was deposited by plasma-enhanced chemical vapor deposition (PECVD) to suppress phosphorus out-diffusion during post-growth thermal treatment. Rapid thermal annealing (RTA) was subsequently performed at 550 °C for 60 s in a nitrogen ambient to activate dopant. While the strain and layer quality were preserved and no dopant out-diffusion was detectable in our structures after RTA treatment. Owing to the mismatch in thermal expansion coefficients between Ge and Si, a residual tensile strain was coherently introduced into the Ge epilayer during cool-down, providing an additional degree of nanoscale strain modulation.

To extend the investigation beyond uniformly doped Ge films and explore dopant behavior in more device-relevant architectures, three types of nanoscale multilayer structures—n⁺-Ge/i-Ge, n⁺-GeSi/i-Ge, and n⁺-Ge/i-GeSi—were fabricated on Si substrates. These structures were designed to emulate key building blocks of SWIR PDs. Sharp doping profiles and abrupt heterointerfaces are critical for device performance. To this end, each nanoscale multilayer featured a deliberately graded phosphorus profile, increasing from the interface toward the surface. This design allowed systematic evaluation of dopant diffusion kinetics, segregation tendencies, and interface abruptness under thermal processing. In particular, the comparison among Ge-only and GeSi-based structures allowed isolation of compositional effects on phosphorus redistribution and strain relaxation behavior. High-resolution X-ray diffraction (HR-XRD) ω -2 θ scans around the (004) reflection was performed to extract the out-of-plane lattice parameter and evaluate strain and crystalline quality (Section 3.1). Prior to the characterization, the SiO₂ capping layer was removed by wet etching in dilute hydrofluoric acid. Room-temperature photoluminescence (PL) spectra of the uniformly doped n-Ge films were acquired. Excitation was provided by a 785 nm diode laser with an incident power of 1 mW. Emission was collected in a back-scattering

configuration through a 50× objective and spectrally resolved using a liquid-nitrogen-cooled InGaAs detector over the wavelength range of 1200–2300 nm (Section 3.2). Surface and cross-sectional morphologies of the nanoscale multilayer structures were examined using field emission scanning electron microscopy (FE-SEM) and atomic force microscope (AFM) in tapping mode. For atomic-scale analysis, cross-sectional specimens were prepared by focused ion beam (FIB) milling and characterized using aberration-corrected transmission electron microscope (TEM) to assess interface sharpness, defect distribution, and strain contrast. Phosphorus concentration profiles and interlayer diffusion lengths were quantified via secondary ion mass spectroscopy (SIMS), providing insight into dopant segregation and redistribution across the nanoscale multilayer structures. The comprehensive characterization of multilayer structures established fundamental design rules governing dopant distribution, strain, and interface quality (Section 3.3). The insights gained—particularly the identified trade-off between high doping concentration and optical material quality—directly informed the subsequent device design strategy, which strategically employs an intrinsic absorption region and ion-implanted contacts to achieve high-performance PDs. Based on these material-level insights, Ge/GeSi nanoscale multilayer structure SWIR PDs were fabricated to validate the proposed decoupled design approach. The detailed fabrication process and characterization methods for these devices are described in Section 3.4.

3. Results and Discussions

3.1. X-Ray Characterization

As the crystal quality and strain state directly affect the electronic and optical performance of Ge epilayers, HR-XRD characterization was performed on n-Ge films with five different phosphorus doping concentrations to quantify the corresponding strain levels. The doping concentrations of these samples were independently measured using SIMS. The strain was calculated based on the lattice mismatch relative to unstrained bulk Ge. **Figure 1** presents the HR-XRD results. The Ge diffraction peaks of all samples are nearly symmetric, with no obvious shoulder on the high-angle side. This indicates that Ge/Si interdiffusion during thermal treatment is negligible, allowing the originally abrupt interface to be preserved without forming an intermediate $\text{Si}_{1-x}\text{Ge}_x$ transition layer. All Ge peaks exhibit a shift toward higher angles relative to bulk Ge, consistent with the presence of tensile strain. This tensile strain arises from the mismatch in thermal expansion coefficients between the Ge epilayer and the Si substrate. The perpendicular lattice constant ($\alpha^\perp$) of the epilayer can be extracted from the XRD diffraction peak position using Bragg's law [94].

$$\alpha^\perp = \frac{2\lambda}{\sin\left(\frac{\omega_{Ge}}{2}\right)} \quad (1)$$

where λ is the incident wavelength of the radiation (Cu $K_{\alpha 1}$ line, $\lambda = 1.5406 \text{ \AA}$) and ω_{Ge} is the angular position of the Ge (004) peak measured by HR-XRD on the Si (004) substrate. The in-plane lattice constant ($\alpha^\parallel$) can be defined as:

$$\alpha^\parallel = \frac{1+\nu}{2\nu} \left[\alpha_{Ge} - \alpha^\perp \left(\frac{1-\nu}{1+\nu} \right) \right] \quad (2)$$

where ν is the elastic modulus of Ge ($\nu = 0.271$) [57,73], and α_{Ge} is the unstrained Ge lattice constant ($\alpha_{Ge} = 5.6576 \text{ \AA}$). The residual strain of Ge epilayer can be calculated by the following equation:

$$\varepsilon = \frac{\alpha_{Ge}^\parallel - \alpha_{Ge}}{\alpha_{Ge}} \quad (3)$$




Figure 1. HR-XRD (004) curves of n-type Ge layers with different phosphorus doping concentrations grown on Si (100) substrates.

The sign of ε reflects the strain nature: $\varepsilon > 0$ indicates tensile strain, and $\varepsilon < 0$ indicates compressive strain in the Ge epilayer. For the five n-doped Ge samples, the extracted strain values range from 0.15% to 0.17%, confirming the presence of tensile strain. Although samples with higher phosphorus concentrations exhibit slightly larger strain values, the variation is minimal. This consistent tensile strain originates predominantly from the thermal expansion coefficient mismatch between the Ge epilayer and the Si substrate during final cool-down of the substrate. The minor variations observed in the measured strain values are within experimental uncertainty, confirming that phosphorus doping has negligible influence on the strain state for the doping concentrations investigated. Four-probe electrical measurements were subsequently performed to determine the active carrier concentrations of the samples. As shown in **Table 1**, the active carrier concentrations for some low-doped samples are lower than the nominal dopant concentrations, suggesting partial dopant activation. The other results indicate that the measured active concentrations closely match the phosphorus concentrations obtained from SIMS, confirming that the majority of incorporated dopants are electrically activated. Increasing the concentration of activated n-type doping in epitaxial Ge primarily reduces contact and series resistance, thereby improving the external quantum efficiencies (EQEs) and responsivity of PDs. Heavily activated n-type doping also enables effective band engineering by filling the L valleys, which is essential for quasi-direct bandgap operation. However, excessive n-type activation can lead to increased Auger recombination and free-carrier absorption, which can increase dark current and decrease optical efficiency.

Table 1. Four-probe electrical measurements and extracted active carrier concentrations for n-doped Ge samples with varying phosphorus concentrations.

Sample	Dopant Concentration (cm ⁻³)	Sheet Resistance (Ω)	ρ ($\Omega \cdot \text{cm}$)	Active Concentration (cm ⁻³)
A	2×10^{18}	165	0.006	1×10^{18}
B	3×10^{18}	61	0.0057	2×10^{18}
C	4×10^{18}	25	0.0025	4×10^{18}
D	9×10^{18}	17	0.0017	8×10^{18}
E	2×10^{19}	14	0.0014	1×10^{19}

3.2. Photoluminescence Measurements

The influence of n-type doping concentration on PL was investigated using five Ge-on-Si samples with phosphorus concentrations ranging from $2 \times 10^{18} \text{ cm}^{-3}$ to $2 \times 10^{19} \text{ cm}^{-3}$.

As shown in **Figure 2a**, the dominant emission peak observed between 1600 and 1800 nm corresponds to the direct optical transition at the Γ -valley of tensile-strained Ge. The shoulder feature at longer wavelengths (1800–2000 nm) can be attributed to indirect bandgap emission. For Sample A, the direct band-to-band transition occurs at 0.765 eV (1620 nm), which is 35 meV lower than the direct bandgap of bulk Ge (0.80 eV, 1550 nm). This redshift in the bandgap relative to bulk Ge arises from the combined effects of tensile strain and heavy n-type doping in the Ge epilayer. The light-hole (LH) and heavy-hole (HH) valence bands in Ge are split at the zone center of the Brillouin zone (BZ) due to epitaxial strain-induced tetragonal deformation. Theoretically, this splitting should give rise to separate PL peaks corresponding to the LH and HH transitions. In practice, these two transitions partially overlap, resulting in a broadening of the overall PL peak. For Samples A ($2 \times 10^{18} \text{ cm}^{-3}$) and B ($3 \times 10^{18} \text{ cm}^{-3}$), the PL intensity increases with higher n-type doping. However, when the carrier concentration exceeds $3 \times 10^{18} \text{ cm}^{-3}$, PL intensity begins to decrease due to carrier-concentration quenching, balancing the initial enhancement from band-filling effects. The strain-induced valence band splitting leads to two closely spaced optical transitions. **Figure 2b** shows the PL spectrum of Sample E, in which the peak splitting is clearly visible. The spectrum comprises transitions from the Γ -valley to both the HH and LH bands, as well as overlapping contributions from the L-valley to the HH and LH bands, which collectively broaden the high-wavelength side of the PL peak.




Figure 2. Room-temperature PL spectra of: (a) five n-type Ge films (Samples A–E); and (b) Sample E. Excitation was provided by a 785 nm diode laser with an incident power of 1 mW.

As noted by Sun et al. [79], the PL intensity of Ge layers generally increases with carrier density. In contrast, as illustrated in **Figure 2**, the PL signal corresponding to transitions from the Γ -valley to the valence band decreases when the carrier concentration exceeds $3 \times 10^{18} \text{ cm}^{-3}$. For compound semiconductors such as GaAs and GaP, the phenomenon where light emission intensity decreases is carrier concentration quenching. It is typically attributed to non-radiative recombination pathways, including vacancy-complex formation, precipitate generation, and band-to-band or impurity-assisted Auger recombination. For Ge layers grown on Si in this work, carrier-concentration quenching counteracts the anticipated benefits of heavy n-type doping, particularly in the context of Ge lasing. As the dopant concentration increases, the loss in emission intensity due to quenching can outweigh the gain from band-filling effects. This behavior may be attributed to degraded crystallinity caused by point defects, which is consistent with prior observations reported by Oehme [77] and Kasai et al. [81], revealed the similar trend. Furthermore, with increasing n-type doping, the Γ -HH peak position remains essentially unchanged, whereas the Γ -LH peak exhibits a pronounced redshift. This observation highlights that heavy-hole states are

less sensitive to doping-induced bandgap renormalization, whereas light-hole states shift more significantly, emphasizing the nuanced impact of heavy n-type doping on valence subbands. Due to its larger effective mass and higher density of states, the HH band is relatively insensitive to bandgap renormalization and local strain variations, resulting in an essentially fixed Γ -HH transition energy. In contrast, the LH band, with a smaller effective mass, is more susceptible to bandgap renormalization, enhanced valence band splitting, and doping-induced strain redistribution, leading to a reduction in the Γ -LH transition energy and a corresponding redshift of the PL component. These observations imply that, beyond a certain threshold, increasing n-type doping in the Ge active layer does not enhance, and may even reduce, the radiative efficiency of optoelectronic devices.

3.3. n^+ -Ge/i-Ge, n^+ -GeSi/i-Ge, and n^+ -Ge/i-GeSi Nanoscale Multilayer Structures

In most cases to form the n-type doped layer in a PIN detector structure is applying implantation followed by an RTA treatment for dopant activation. Therefore, our initial idea to form a PIN photodetector is the possibility to grow the whole structure since in such a case, the processing of detector could be shortened. Therefore, to explore the growth behavior of P-doped Ge/GeSi multilayers, we investigated three representative structures: n^+ -Ge/i-Ge, n^+ -GeSi/i-Ge, and n^+ -Ge/i-GeSi. A series of nanoscale multilayer films were fabricated with alternating n-type and intrinsic layers. For the n^+ -Ge/i-Ge multilayer, a 50 nm n^+ -Ge layer and a 100 nm intrinsic Ge layer were alternated four times, followed by a 400 nm intrinsic Ge capping layer. The n^+ -GeSi/i-Ge multilayer consisted of four repetitions of a 100 nm n^+ -GeSi/200 nm i-Ge bilayer. In the n^+ -Ge/i-GeSi multilayer, four periods of a 100 nm i-GeSi/200 nm n^+ -Ge bilayer were grown, capped with a 200 nm intrinsic Ge layer for surface protection. **Figure 3** illustrates the design schematics of these nanoscale multilayer structures. The phosphorus concentration in the n-type layers was deliberately graded, increasing from the bottom to the top n-type layer to investigate dopant diffusion and segregation effects. The GeSi layers in this study contain approximately 30% Si.




Figure 3. Schematic illustration of the (a) n^+ -Ge/i-Ge, (b) n^+ -GeSi/i-Ge, and (c) n^+ -Ge/i-GeSi nanoscale multilayer structures on Si.

The SEM result in **Figure 4a** shows that the surface of the n^+ -Ge/i-Ge multilayer was very rough and the AFM result in **Figure 4d** shows the roughness of the wafer surface is as high as 47.9 nm. The pronounced surface roughness (a transition from layer-by-layer of three-dimensional growth) and large-scale undulation observed in the n^+ -Ge/i-Ge nanoscale multilayer grown on Si indicate significant degradation of the epitaxial quality. Such morphology typically reflects substantial strain accumulation and partial relaxation within the Ge/Si structure, given the large lattice mismatch between Ge and Si. The relaxation process likely generates misfit and threading dislocations, whose propagation

toward the surface produces cross-hatch features and height modulations. In addition, the high n-type doping level in the Ge layers can suppress adatom mobility and promote three-dimensional island-like growth, further enhancing surface roughening and undulation. The repeated n/i multilayer also amplifies interface roughness through vertical propagation across the nanoscale multilayer periods. The observed severe surface corrugation reflects a combination of strain-induced relaxation, defect-mediated roughening, and dopant-modulated growth kinetics, resulting in a substantially nonideal epitaxial morphology on Si substrates.




Figure 4. SEM and AFM images of (a,d) n^+ -Ge/i-Ge, (b,e) n^+ -GeSi/i-Ge, and (c,f) n^+ -Ge/i-GeSi nanoscale multilayer structures.

As shown in **Figure 4b,c,e,f**, the n^+ -GeSi/i-Ge and n^+ -Ge/i-GeSi multilayers grown on Si, in contrast to the n^+ -Ge/i-Ge multilayer, exhibit considerably smoother surfaces with reduced roughness and more clearly defined layer interfaces. Compared with n^+ -Ge/i-Ge multilayer sample, the surface of n^+ -GeSi/i-Ge and n^+ -Ge/i-GeSi multilayer samples are remarkably better, with the roughness of 18.5 nm and 14.6 nm. This improvement suggests that the P incorporation in GeSi is higher than Ge. In general, the dopant incorporation in Ge (or Si) is ruled by thermodynamical theory which indicates the influence of strain effect and chemical effect. The latter effect is ruled by the tendency toward making Ge–Ge bond compared to P–P or P–Ge bond. This effect is expressed in heat sublimation energy and it is in favor of P–P bonding compared to P–Ge. Meanwhile, there is also strain effect which is directed by the difference in atomic radius between Ge and P. Both these effects are dominant for incorporation of P in Ge and it results in low P incorporation. Meanwhile the above two effects in GeSi are very different. The chemical effect is better in Si compared to Ge and the difference in atomic radius of Si and P is almost minor. Therefore, the P incorporation in GeSi is higher than Ge alone. In addition, GeSi layers generally provide higher adatom mobility and more favorable surface diffusion kinetics compared to highly doped Ge, which helps maintain two-dimensional layer-by-layer growth and reduces interface roughening during the repeated multilayer process. Consequently, the relatively smooth morphology and sharp interfaces indicate that partial Si alloying promotes more coherent epitaxy.

The details in the TEM images in **Figure 5** also show that the n^+ -Ge/i-GeSi nanoscale multilayer exhibits noticeably sharper interfaces, and its highly doped top n-Ge layer is able to maintain the intended thickness with minimal degradation. In contrast, the top n-GeSi layer in the n^+ -GeSi/i-Ge multilayer becomes thinner and increasingly interfacial roughness when the P concentration has increased to $2 \times 10^{19} \text{ cm}^{-3}$, deviating from the

designed thickness. This suggests that the presence of high P atoms during the growth may strongly affect the growth kinetics. These results indicate that n^+ -Ge/*i*-GeSi nanoscale multilayer provide a more compliant and kinetically favorable growth, whereas heavily doped GeSi in n^+ -GeSi/*i*-Ge is more susceptible to strain- and kinetics-driven degradation.




Figure 5. Cross-sectional TEM images of (a) n^+ -Ge/*i*-Ge, (b) n^+ -GeSi/*i*-Ge, and (c) n^+ -Ge/*i*-GeSi nanoscale multilayer structures.

To date, SIMS could probe dopant profile and obtain the depth resolution inside such nanoscale multilayer structure. **Figure 6a** shows the SIMS result and it is observed that it is difficult to form a clear interface between *n*-Ge and *i*-Ge, which is consistent with the TEM characterization surface results. Although cross-sectional TEM indicates that the n^+ -Ge/*i*-GeSi multilayer exhibits sharper morphological interfaces and that both the top heavily doped *n*-Ge and the intrinsic GeSi layers retain their designed thicknesses, SIMS depth profiles reveal the chemical picture regarding material doping concentration. The n^+ -GeSi/*i*-Ge multilayer in **Figure 6b** shows much steeper concentration gradients, preserves the intrinsic doping level of the *i*-Ge layer, and supports $>6 \times 10^{19} \text{ cm}^{-3}$ doping in the top *n*-GeSi, while in the n^+ -Ge/*i*-GeSi multilayer structure in **Figure 6c**, significant interdiffusion occurs in the nominal intrinsic GeSi layer, with the doping concentration of the top *n*-Ge layer reaching only about $5 \times 10^{18} \text{ cm}^{-3}$. The presence of Si in the doped GeSi layer alters the thermodynamics and kinetics of dopant solubility and migration which can suppress dopant out-diffusion and produce sharper SIMS profiles in the n^+ -GeSi/*i*-Ge case. High *n*-type doping in pure Ge may decrease surface adatom mobility and promote segregation or clustering during growth or subsequent thermal steps, resulting in net loss of dopants from the intended top layer, thereby lowering the measured peak concentration. The n^+ -GeSi/*i*-Ge multilayer appears to create a chemical and defect environment that is more retentive of dopants, whereas heavily doped Ge adjacent to GeSi is more susceptible to kinetically enhanced intermixing and dopant depletion, yielding broadened profiles and reduced top-layer peaks. The comprehensive characterization of the three in situ doped nanoscale multilayer structures (n^+ -Ge/*i*-Ge, n^+ -GeSi/*i*-Ge, and n^+ -Ge/*i*-GeSi) provides critical insights into the fundamental trade-offs between doping, strain, and interfacial integrity. A pivotal conclusion from this study is that despite enabling nanoscale dopant and strain engineering, in situ doped Ge/GeSi multilayers inherently suffer from significant dopant interdiffusion and interface degradation, as unequivocally revealed by SIMS and TEM. These material-level shortcomings would directly manifest as junction broadening and elevated leakage currents in photodetectors, fundamentally limiting device performance. These SIMS features, combined with interface roughening and dopant diffusion observed in in situ doped multilayers, indicate that devices based on these structures would be performance-limited. This motivates the use of ion-implanted multilayers, which decouple optical absorption and electrical conduction, preserving interface quality. Therefore, this study concludes that integrating such in situ doped multilayers directly as the

active region is impractical for high-performance detectors. This material-level understanding directly motivated the decoupled device strategy employed in this work: using an intrinsic Ge/GeSi multiple quantum well (MQW) for optimal optical absorption, while relegating the doping function to ion-implanted contacts, thereby circumventing the core limitations identified here. These growth-related effects, coupled with interface roughening in in situ doped structures, would inevitably limit device performance. Consequently, ion-implanted multilayers are used for device fabrication, ensuring high crystalline quality and well-confined doping.




Figure 6. SIMS depth profiles of (a) n^+ -Ge/i-Ge, (b) n^+ -GeSi/i-Ge, and (c) n^+ -Ge/i-GeSi nanoscale multilayer structures.

3.4. Design for SWIR Photodetectors with Intrinsic Ge Nanoscale Multilayer Heterostructures

Observations of interface roughening and dopant diffusion in in situ doped multilayers highlighted the limitations of such structures for device performance. Accordingly, the ion-implanted design was chosen to preserve optical quality while controlling electrical properties. Building upon the material insights from **Section 3.3**, we fabricated a GOI-based SWIR PD with a decoupled architecture: an intrinsic Ge/GeSi nanoscale multilayer structure as the optical absorption region and ion-implanted regions for electrical junction formation. This approach directly addresses the limitations of in situ doped structures by eliminating doping-induced defects from the active zone and utilizing a mature, high-resolution technique for contact doping. First, an intrinsic low temperature Ge buffer layer and a high temperature Ge layer were sequentially grown on a p-type Si (001) donor wafer using a LT/HT two-step epitaxy method in a RPCVD reactor. Subsequently, a four-period GeSi/Ge multilayer was directly grown, with each period consisting of a 20 nm thick GeSi layer and a 90 nm thick Ge layer. The nanoscale multilayer structure design—specifically the use of a GeSi barrier—was optimized to replicate the favorable strain accommodation and interfacial stability observed in the best-performing n^+ -Ge/i-GeSi model structure

from **Section 3.3**. It is important to note that the primary purpose of employing the Ge/GeSi nanoscale multilayer structure is to enhance the optical responsivity and quantum efficiency via strain engineering and carrier confinement. This design does not inherently improve, and may even influence, the dark current characteristics, which are predominantly governed by the material's defect density and the junction quality. Following the growth of the intrinsic epitaxial multilayer, a 300 nm PECVD SiO₂ layer was deposited as a bonding interface. A separate Si handling wafer with a 500 nm thermal oxide SiO₂ layer was prepared. The donor wafer and the handling wafer were then directly bonded. The donor substrate and the low-temperature Ge buffer layer were subsequently removed by grinding and wet etching, transferring the intrinsic nanoscale multilayer structure onto the insulating substrate to form the GOI platform. The electrical junctions were then formed exclusively by ion implantation, completely avoiding n-type in situ doping in the device integration flow. The fabrication of the top n-type contact layer was achieved through a two-stage ion implantation process, with each step employing a dose of $1 \times 10^{15} \text{ cm}^{-2}$ and an energy of 18 keV. A dedicated activation annealing cycle was performed immediately after each implantation step at 500 °C for 60 s in a hydrogen ambient. This process created a highly doped n⁺-Ge region with a concentration of approximately $2 \times 10^{20} \text{ cm}^{-3}$. The main process flow is illustrated in **Figure 7a**. The final n-type dopant distribution throughout the PIN structure was confirmed by SIMS, as shown in **Figure 7c**. Direct structural or optical comparison between in situ doped and ion-implanted multilayers is not performed, because material imperfections in the in situ doped structures would dominate device response. Instead, ion-implanted multilayers are used to decouple optical absorption and electrical conduction, ensuring meaningful device characterization and high-performance evaluation. The two approaches are conceptually linked: limitations observed in in situ doped multilayers directly informed the adoption of ion-implanted contacts. This clear linkage between material characterization and device design ensures continuity from in situ doped studies to the implementation of ion-implanted SWIR photodetectors, providing a coherent and traceable narrative for the reader.

A critical determinant of PD performance is the quality of the ohmic contact, specifically the associated contact resistance [95–98]. In this investigation, we sought to minimize this resistance by fabricating a NiGe layer directly onto the N-doped and P-doped Ge region within the p-i-n structure. To decouple the contact resistance from the intrinsic device resistance and quantify it independently, we employed the circular transmission line model (CTLM). Where L represents the inner circle radius, and d_i represents the difference between the outer circle radius and the inner circle radius. The mask design incorporated d_i values ranging from 5 to 30 μm in uniform increments of 5 μm . The derived metrics, specifically the total resistance (R_T) and the contact resistivity (ρ_c), are determined using the following established formulas [99]:

$$R_T = \frac{R_{sh}}{2\pi L} (d_i + 2L_T) \quad (4)$$

$$\rho_c = R_{sh} \cdot L_T^2 \quad (5)$$

Specifically, the relationship for R_T is defined as a function of the sheet resistance of the semiconductor (R_{sh}), the transfer length (L_T), and the inner circle radius (L). The CTLM analysis confirmed excellent ohmic contact performance for both doping types. Specifically, the data fitting, as detailed in **Figure 8**, yielded an n-type contact resistivity (ρ_c) of $2.66 \times 10^{-6} \Omega \text{ cm}^2$ and a p-type contact resistivity (ρ_c) of $1.38 \times 10^{-8} \Omega \text{ cm}^2$. These values demonstrate the highly efficient contact formation achieved on both doped Ge surfaces.




Figure 7. (a) Main process flow of the intrinsic Ge/GeSi nanoscale multilayer structure PDs. (b) The schematic of the Ge/GeSi p-i-n ssPD on the insulator. (c) Phosphorus SIMS data of intrinsic GeSi/Ge nanoscale multilayer p-i-n structure PDs on the insulator.




Figure 8. Circular transmission line model (CTLM) analysis demonstrating the relationship between the measured total resistance R_T and the contact circle radius spacing d_i for (a) n-type Ge and (b) p-type Ge ohmic contacts.

The photo currents of the fabricated PDs with undoped Ge/GeSi multilayer were measured at room temperature to confirm the optoelectronic performance. The device fabrication and photocurrent measurements were not performed on in situ doped multilayers because material characterization revealed interface roughening and dopant diffusion, which would inevitably degrade device performance. Instead, an ion-implanted doping strategy was adopted to decouple optical absorption and electrical conduction, ensuring

reliable device evaluation. Photocurrent measurements were conducted using an Agilent B1500A semiconductor parameter analyzer integrated with a manual probe station. To assess the spectral response, a fixed-wavelength laser (1310 nm) and a tunable laser source covering the 1500–1630 nm range were utilized. Optical excitation was achieved by coupling incident light through a single-mode fiber-oriented perpendicular to the device surface. The incident optical power was precisely regulated at 1 mW, with calibration verified via a high-precision commercial reference detector. The responsivity (R), a key figure of merit for detector efficiency, is defined by the following expression:

$$R = \frac{I_{ph}}{P_o} = \frac{\eta q \lambda}{hc} \quad (6)$$

where I_{ph} denotes the photocurrent, P_o represents the incident optical power, η is the external quantum efficiency (EQE), q is the elementary charge, λ is the incident wavelength, h is Planck's constant, and c is the speed of light in a vacuum.

The responsivity characteristics for the PD configurations at wavelengths of 1550 nm and 1310 nm are illustrated in **Figure 9a**. The optical responsivity of the Ge/GeSi nanoscale multilayer structure PD at 1550 and 1310 nm was 0.99 A/W and 0.83 A/W at -1 V, corresponding to EQEs of 79.2% and 78.6%, respectively. The responsivity remained nearly constant across the reverse bias range, indicating high carrier collection efficiency throughout operation. These results demonstrate that the fabricated PDs maintain efficient photogenerated carrier collection at the nanoscale, validating both the nanoscale multilayer structure design and the ion implantation doping strategy, which collectively ensure optimal junction formation. The spectral response of the PD was characterized at room temperature using a tunable laser source, as shown in **Figure 9b**. Due to the optical confinement provided by the QW nanoscale structure on insulator, a resonant response peak was clearly observed in the C-band, with the highest responsivity successfully obtained at 1550 nm. The maintenance of high-performance optoelectronic characteristics is primarily attributed to the synergistic effect of low contact resistivity and high crystalline quality in the nanoscale absorption multilayer, which minimizes carrier recombination and maximizes quantum efficiency. Furthermore, these results validate the effectiveness of ion implantation in forming well-controlled n-type layers in nanoscale SWIR detectors, ensuring that device performance is not significantly compromised during junction engineering. These findings highlight the critical role of nanoscale material design, interface engineering, and precise dopant placement in achieving high-performance, low-bias PDs suitable for low-power SWIR imaging applications.




Figure 9. (a) Responsivity versus reverse-bias voltage for 100-μm-diameter PDs at 1310 nm and 1550 nm. (b) Spectral response of the PD with undoped Ge/GeSi nanoscale multilayer structure measured between 1500 and 1630 nm.

4. Conclusions

We systematically investigated the effects of n-type in situ doping on Ge epitaxial films and Ge/GeSi nanoscale multilayer structures on Si. PL measurements showed initial enhancement of Γ -valley emission with increasing doping, but high concentrations ($>1 \times 10^{19} \text{ cm}^{-3}$) led to quenching, revealing the fundamental trade-off between doping and radiative efficiency. Among all the nanoscale multilayers, $\text{n}^+\text{-GeSi/i-Ge}$ exhibited the steepest dopant profile ($>6 \times 10^{19} \text{ cm}^{-3}$) and suppressed interdiffusion, whereas $\text{n}^+\text{-Ge/i-GeSi}$ maintained sharp nanoscale interfaces but lower peak doping ($\sim 5 \times 10^{18} \text{ cm}^{-3}$). These findings unequivocally demonstrated that while in situ doping enables band engineering, it inherently introduces defects that limit optical performance. Driven by the recognition that in situ doping inherently compromises optical material quality, we devised a decoupled device strategy: the active region adopted an intrinsic Ge/GeSi nanoscale multilayer structure to preserve interface quality and minimize non-radiative loss, while the electrical junctions were formed by ion implantation to ensure precise doping control. Consequently, optimized Ge/GeSi SWIR PDs achieved responsivity of 0.99 A/W at 1550 nm and 0.83 A/W at 1310 nm, EQE of 79.2% and 78.6%, and low contact resistivity ($2.66 \times 10^{-6} \Omega \cdot \text{cm}^2$ for n-type, $1.38 \times 10^{-8} \Omega \cdot \text{cm}^2$ for p-type). More broadly, the decoupled design strategy establishes a general paradigm for leveraging nanoscale heterostructures for optimal optical properties while employing conventional processing for electronic functions, which could be extended to other material systems for imaging applications.

Author Contributions: Conceptualization, X.Z., Y.M. and H.H.R.; methodology, X.Z., and H.H.R.; validation, X.Z., J.S., J.D., Y.R., B.L., T.D., X.D. and X.S.; formal analysis, X.Z., Y.M. and H.H.R.; investigation, X.Z. and Y.M.; data curation, X.Z.; writing—original draft preparation, X.Z. and Y.M.; writing—review and editing, X.Z., Y.M. and H.H.R.; visualization, X.Z., J.S. and J.D.; supervision, H.H.R.; funding acquisition, H.H.R. All authors have read and agreed to the published version of the manuscript.

Funding: This work was supported by the Guangdong S&T Programme (Grant No. 2024B0101130001), and in part by the “Pearl River Talent Plan” Innovation and Entrepreneurship Team Project of Guangdong Province (Grant No. 2021ZT09X479).

Data Availability Statement: The data presented in this study are available on request from the corresponding authors.

Conflicts of Interest: The authors declare no conflicts of interest.

References

1. Miao, Y.; Radamson, H.H. Functional Near-Infrared Imaging for Biomedical Applications. In *Recent Advances in Infrared Spectroscopy and Its Applications in Biotechnology*; Mazumder, N., Zhuo, G.-Y., Eds.; IntechOpen: London, UK, 2024. [CrossRef]
2. Mahadeva, M.M.S.; Yuta, M.; Kenji, M.; Setsuko, T.; Aravind, K.S.; Takashi, J. Biocompatible and Water-Soluble Shortwave-Infrared (SWIR)-Emitting Cyanine-Based Fluorescent Probes for In Vivo Multiplexed Molecular Imaging. *ACS Appl. Mater. Interfaces* **2024**, *16*, 17253–17266. [CrossRef]
3. Larique, E.; Chorier, P.; Aufranc, S.; Siam-Giao, D.; Gaucher, A.; Berthoz, J.; Chanel-Petitjean, E.; Bouchage, G. New SWIR staring arrays for Earth observation space applications at LYNRED. In *Proceedings of the International Conference on Space Optics—ICSO 2022, Dubrovnik, Croatia, 3–7 October 2022*; SPIE: Bellingham, WA, USA, 2023; pp. 998–1009.
4. Du, C.; Su, J.; Huang, Z.; Yang, Z.; Xu, T.; Zheng, Z.; Ma, C.; Chen, Y.; Yao, J.; Duan, X. Area-selective etching-free construction of arrayed high-performance WS_2 photodetectors. *J. Alloys Compd.* **2025**, *1032*, 181213. [CrossRef]
5. Liu, J.; Cannon, D.D.; Wada, K.; Ishikawa, Y.; Jongthammanurak, S.; Danielson, D.T.; Michel, J.; Kimerling, L.C. Tensile strained Ge p-i-n photodetectors on Si platform for C and L band telecommunications. *Appl. Phys. Lett.* **2005**, *87*, 011110. [CrossRef]
6. Jun, Z.; Xiangquan, L.; Jinlai, C.; Qinxin, H.; Zhi, L.; Yuhua, Z.; Buwen, C. Research Progress of GeSn Photodetectors for Infrared Application. *IEEE J. Select. Top. Quantum Electron.* **2025**, *31*, 3800609. [CrossRef]

7. Steckel, J.S.; Josse, E.; Pattantyus-Abraham, A.G.; Bidaud, M.; Mortini, B.; Bilgen, H.; Arnaud, O.; Allegret-Maret, S.; Saguin, F.; Mazet, L.; et al. 1.62 μ m Global Shutter Quantum Dot Image Sensor Optimized for Near and Shortwave Infrared. In *Proceedings of the 2021 IEEE International Electron Devices Meeting (IEDM), San Francisco, CA, USA, 11–16 December 2021*; IEEE: Piscataway, NJ, USA, 2021; pp. 23.4.1–23.4.4.
8. Khaled, O.; Yousuf, F.; Talal, B.; Mohammad, A.; Alobaid, A. The scientific footprint of SWIR detectors. In *Proceedings of the Advanced Optics for Imaging Applications: UV Through LWIR IX, National Harbor, MD, USA, 22–24 April 2024*; SPIE: Bellingham, WA, USA, 2024; pp. 102–111.
9. Mitsuru, T.; Younghyun, K.; Jaehoon, H.; Jian, K.; Yuki, I.; Yongpeng, C.; Jinkwon, P.; Misa, Y.; Seiya, T.; Shinich, T. Heterogeneous CMOS Photonics Based on SiGe/Ge and III–V Semiconductors Integrated on Si Platform. *IEEE J. Select. Top. Quantum Electron.* **2017**, *23*, 64–76. [\[CrossRef\]](#)
10. Dong, T.; Li, B.; Zhao, X.; Du, J.; Duan, X.; Su, J.; Zhang, F.; Lin, H.; Ren, Y.; Miao, Y.; et al. Boosting the performance of In_{0.53}Ga_{0.47}As/InP photodetectors with Al₂O₃/SiN_x bilayer passivation technology. *Mater. Sci. Semicond. Process.* **2026**, *202*, 110150. [\[CrossRef\]](#)
11. Andreu, G.; Enrico, B. Crosstalk mitigation and small-pitch consequences in SWIR InGaAs FPAs. *Opt. Express* **2022**, *30*, 12150–12162. [\[CrossRef\]](#)
12. Ying, X.; Yu, H.; Yi, W.; Jie, L.; Jingyi, W.; Zunyue, Z.; Xinlun, C.; Hon Ki, T.; Kei May, L. High-speed and low dark current silicon-waveguide-coupled III-V photodetectors selectively grown on SOI. *Optica* **2022**, *9*, 1219–1226. [\[CrossRef\]](#)
13. Cheng, Y.; Jiang, B.; Chaemchuen, S.; Verpoort, F.; Kou, Z. Advances and challenges in designing MXene quantum dots for sensors. *Carbon Neutralization* **2023**, *2*, 213–234. [\[CrossRef\]](#)
14. Deng, Y.; Pang, C.; Kheradmand, E.; Leemans, J.; Bai, J.; Minjauw, M.; Liu, J.; Molken, K.; Beeckman, J.; Detavernier, C.; et al. Short-wave infrared colloidal QD photodetector with nanosecond response times enabled by ultrathin absorber layers. *Adv. Mater.* **2024**, *36*, 2402002. [\[CrossRef\]](#)
15. Shuo, Z.; Yao, H.; Qun, H. Advances of Sensitive Infrared Detectors with HgTe Colloidal Quantum Dots. *Coatings* **2020**, *10*, 760. [\[CrossRef\]](#)
16. Kseniia, A.S.; Huichen, Z.; Arsenii, S.P.; Erwan, B.; Ge, M.; Stephen, V.K.; Sandrine, I.; Philippe, G.S.; Sean, K.; Christophe, D.; et al. The Rise of HgTe Colloidal Quantum Dots for Infrared Optoelectronics. *Adv. Funct. Mater.* **2024**, *34*, 2405307. [\[CrossRef\]](#)
17. Fischetti, M.V.; Laux, S.E. Band structure, deformation potentials, and carrier mobility in strained Si, Ge, and SiGe alloys. *J. Appl. Phys.* **1996**, *80*, 2234–2252. [\[CrossRef\]](#)
18. Radamson, H.H.; Noroozi, M.; Jamshidi, A.; Thompson, P.E.; Östling, M. Strain Engineering in GeSnSi Materials. *ECS Trans.* **2013**, *50*, 527. [\[CrossRef\]](#)
19. Lin, Y.; Ma, D.; Hong Lee, K.; Wen, R.-T.; Syaranamual, G.; Kimerling, L.C.; Seng Tan, C.; Michel, J. PIC-integrable, uniformly tensile-strained Ge-on-insulator photodiodes enabled by recessed SiN_x stressor. *Photon. Res.* **2021**, *9*, 1255. [\[CrossRef\]](#)
20. Soumava, G.; Kuan-Chih, L.; Cheng-Hsun, T.; Kwang Hong, L.; Qimiao, C.; Bongkwon, S.; Bratati, M.; Chuan Seng, T.; Guo-En, C. Resonant-cavity-enhanced responsivity in germanium-on-insulator photodetectors. *Opt. Express* **2020**, *28*, 23739–23747. [\[CrossRef\]](#)
21. Lin, Y.; Son, B.; Lee, K.H.; Michel, J.; Tan, C.S. Sub-mA/cm² dark current density, buffer-less germanium (Ge) photodiodes on a 200-mm Ge-on-insulator substrate. *IEEE Trans. Electron. Devices* **2021**, *68*, 1730–1737. [\[CrossRef\]](#)
22. Son, B.; Zhou, H.; Lin, Y.; Lee, K.H.; Tan, C.S. Gourd-shaped hole array germanium (Ge)-on-insulator photodiodes with improved responsivity and specific detectivity at 1,550 nm. *Opt. Express* **2021**, *29*, 16520–16533. [\[CrossRef\]](#)
23. Liu, Z.; Liu, J.; Cheng, B.; Zheng, J.; Li, C.; Xue, C.; Wang, Q. Enhanced light trapping in Ge-on-Si-on-insulator photodetector by guided mode resonance effect. *J. Appl. Phys.* **2018**, *124*, 053101. [\[CrossRef\]](#)
24. Yu, J.; Zhao, X.; Miao, Y.; Su, J.; Kong, Z.; Li, H.; Wu, Y.; Zhou, Z.; Wang, B.; Ye, T.; et al. High-performance Ge PIN photodiodes on a 200 mm insulator with a resonant cavity structure and monolayer graphene absorber for SWIR detection. *ACS Appl. Nano Mater.* **2024**, *7*, 5889–5898. [\[CrossRef\]](#)
25. Chin-Yuan, C.; Cheng-Hsun, T.; Po-Lun, Y.; Sheng-Feng, H.; Shuyu, B.; Kwang Hong, L.; Chuan Seng, T.; Guo-En, C. Ge-on-insulator lateral p-i-n waveguide photodetectors for optical communication. *Opt. Lett.* **2020**, *45*, 6683–6686. [\[CrossRef\]](#)
26. Xiong, W.; Wang, G.; Du, Y.; Lin, H.; Zhao, X.; Yu, J.; Kong, Z.; Dong, Y.; Jiang, H.; Tao, Y.; et al. Integration of silicon nitride waveguide in Ge-on-insulator substrates for monolithic solutions in optoelectronics. *J. Mater. Sci. Mater. Electron.* **2021**, *32*, 6133–6140. [\[CrossRef\]](#)
27. Lingyan, Y.; Shan, Z.; Guanglin, Z.; Zhengyi, H.; Xiaoqiang, F.; Zhiduo, L.; Gang, W.; Weidong, T.; Li, Z.; Siwei, Y.; et al. Dual-Enhanced Photodetectors Combining Graphene Plasmonic Nanoresonators with Germanium-on-Insulator Optical Cavities. *IEEE Trans. Electron. Devices* **2022**, *69*, 3246–3250. [\[CrossRef\]](#)
28. Kwang Hong, L.; Shuyu, B.; Gang Yih, C.; Yew Heng, T.; Eugene, A.F.; Chuan Seng, T. Defects reduction of Ge epitaxial film in a germanium-on-insulator wafer by annealing in oxygen ambient. *APL Mater.* **2015**, *3*, 016102. [\[CrossRef\]](#)

29. Ji, R.; Yao, L.; Jiao, J.; Xu, G.; Fu, F.; Lin, G.; Li, C.; Huang, W.; Xue, C.; Chen, S. Highly integrated ultra-low leakage current shortwave infrared photodetector based on Ge-Si heterogenous wafer bonding. *IEEE Electron. Device Lett.* **2024**, *45*, 948–951. [\[CrossRef\]](#)
30. Yamamoto, Y.; Corley, C.; Schubert, M.A.; Zoellner, M.; Tillack, B. Threading Dislocation Reduction of Ge by Introducing a SiGe/Ge Superlattice. *ECS J. Solid State Sci. Technol.* **2021**, *10*, 034005. [\[CrossRef\]](#)
31. Baile, C.; Yaojiang, C.; Zhuo, D. Recent Advances in High Speed Photodetectors for eSWIR/MWIR/LWIR Applications. *Photonics* **2021**, *8*, 14. [\[CrossRef\]](#)
32. Wang, B.; Zhao, X.; Dong, T.; Li, B.; Zhang, F.; Su, J.; Ren, Y.; Duan, X.; Lin, H.; Miao, Y.; et al. Convergence of Thermistor Materials and Focal Plane Arrays in Uncooled Microbolometers: Trends and Perspectives. *Nanomaterials* **2025**, *15*, 1316. [\[CrossRef\]](#)
33. Hyeon Deok, Y.; Yeon-Ho, K.; Jong-Han, Y.; Sukill, K.; Tae Soo, J.; Chel-Jong, C.; Taek Sung, K.; Kyu-Hwan, S. Fabrication of PIN photo-diode from p-Ge/i-Ge/n-Si hetero junction structure. *Mater. Sci. Semicond. Process.* **2014**, *17*, 74–80. [\[CrossRef\]](#)
34. Carroll, L.; Imbert, F.; Sigg, H.; Süess, M.; Müller, E.; Virgilio, M.; Pizzi, G.; Rossbach, P.; Chrastina, D.; Isella, G. Quantum-confined direct-gap transitions in tensile-strained Ge/SiGe multiple quantum wells. *Appl. Phys. Lett.* **2011**, *99*, 031907. [\[CrossRef\]](#)
35. Chang, G.-E.; Chen, S.-W.; Cheng, H.H. Tensile-strained Ge/SiGe quantum-well photodetectors on silicon substrates with extended infrared response. *Opt. Express* **2016**, *24*, 17562–17571. [\[CrossRef\]](#)
36. Zhao, Z.; Ruan, D.-B.; Yang, Q.C.; Sun, J.; Zhang, J.-Y.; Gan, K.-J.; Pan, S.; Jiang, X.; Chang-Liao, K.-S.; Wu, H.; et al. Investigation of atomically flat surface Ge_{0.8}Si_{0.2}/Ge superlattice epitaxial and high-selectivity stacked Ge_{0.8}Si_{0.2} nanosheet release. *Vacuum* **2025**, *242*, 114724. [\[CrossRef\]](#)
37. Zhang, Q.; Tu, H.; Gu, S.; Zhang, Z.; Wang, G.; Wei, F.; Ma, T.; Zhao, H.; Wei, Q.; Yin, H.; et al. Influence of Rapid Thermal Annealing on Ge-Si Interdiffusion in Epitaxial Multilayer Ge_{0.3}Si_{0.7}/Si Superlattices with Various GeSi Thicknesses. *ECS J. Solid State Sci. Technol.* **2018**, *7*, P671–P676. [\[CrossRef\]](#)
38. Kolahdouz, M.; Farniya, A.A.; Benedetto, L.D.; Radamson, H.H. Improvement of infrared detection using Ge quantum dots multilayer structure. *Appl. Phys. Lett.* **2010**, *96*, 213516. [\[CrossRef\]](#)
39. Botti, S.; Weissker, H.-C.; Marques, M.A.L. Alloying effects on the optical properties of Ge_{1-x}Si_x nanocrystals from time-dependent density functional theory and comparison with effective-medium theory. *Phys. Rev. B* **2009**, *79*, 155440. [\[CrossRef\]](#)
40. Prost, M.; El Kurdi, M.; Aniel, F.; Zerounian, N.; Sauvage, S.; Checoury, X.; Bœuf, F.; Boucaud, P. Analysis of optical gain threshold in n-doped and tensile-strained germanium heterostructure diodes. *J. Appl. Phys.* **2015**, *118*, 125704. [\[CrossRef\]](#)
41. Radamson, H.H.; Kolahdouz, M.; Shayestehaminzadeh, S.; Farniya, A.A.; Wissmar, S. Carbon-doped single-crystalline SiGe/Si thermistor with high temperature coefficient of resistance and low noise level. *Appl. Phys. Lett.* **2010**, *97*, 223507. [\[CrossRef\]](#)
42. Kanesawa, R.; Kikuoka, S.; Shibahara, Y.; Wagatsuma, Y.; Yamada, M.; Hamaya, K.; Sawano, K. Fabrication of crack-free strained SiGe/Ge multiple quantum wells on Ge-on-Si(111) by the patterning method. *Mater. Sci. Semicond. Process.* **2024**, *177*, 108300. [\[CrossRef\]](#)
43. Zhenzhen, K.; Guilei, W.; Renrong, L.; Jiale, S.; Meng, X.; Yuanhao, M.; Shihai, G.; Junjie, L.; Kaihua, C.; Hongxiao, L.; et al. Growth and Strain Modulation of GeSn Alloys for Photonic and Electronic Applications. *Nanomaterials* **2022**, *12*, 981. [\[CrossRef\]](#) [\[PubMed\]](#)
44. Kolahdouz, M.; Östling, M.; Radamson, H.H. High performance infra-red detectors based on Si/SiGe multilayers quantum structure. *Mater. Sci. Eng. B* **2012**, *177*, 1563–1566. [\[CrossRef\]](#)
45. Kuo, Y.-H.; Lee, Y.K.; Ge, Y.; Ren, S.; Roth, J.E.; Kamins, T.I.; Miller, D.A.B.; Harris, J.S. Strong quantum-confined Stark effect in germanium quantum-well structures on silicon. *Nature* **2005**, *437*, 1334–1336. [\[CrossRef\]](#)
46. Chang, G.-E.; Chang, S.-W.; Chuang, S.L. Theory for n-type doped, tensile-strained Ge-Si_x Ge_y Sn_{1-x-y} quantum-well lasers at telecom wavelength. *Opt. Express* **2009**, *17*, 11246. [\[CrossRef\]](#)
47. Süess, M.J.; Carroll, L.; Sigg, H.; Diaz, A.; Chrastina, D.; Isella, G.; Müller, E.; Spolenak, R. Tensile strained Ge quantum wells on Si substrate: Post-growth annealing versus low temperature re-growth. *Mater. Sci. Eng. B* **2012**, *177*, 696–699. [\[CrossRef\]](#)
48. Yugova, T.G.; Mil'vidskii, M.G.; Vdovin, V.I. Defect formation in Ge_{1-x}Si_x/Ge(111) epitaxial heterostructures. *Phys. Solid State* **2004**, *46*, 1520–1527. [\[CrossRef\]](#)
49. Chaisakul, P.; Vakarin, V.; Frigerio, J.; Isella, G.; Vivien, L.; Marris-Morini, D. Silicon nitride waveguide-integrated Ge/SiGe quantum wells optical modulator. *J. Phys. Conf. Ser.* **2017**, *901*, 012152. [\[CrossRef\]](#)
50. Chaisakul, P.; Marris-Morini, D.; Isella, G.; Chrastina, D.; Rouifed, M.-S.; Le Roux, X.; Edmond, S.; Cassan, E.; Coudeville, J.-R.; Vivien, L. 10-Gb/s Ge/SiGe Multiple Quantum-Well Waveguide Photodetector. *IEEE Photon. Technol. Lett.* **2011**, *23*, 1430–1432. [\[CrossRef\]](#)
51. Rong, Y.; Ge, Y.; Huo, Y.; Fiorentino, M.; Tan, M.R.T.; Kamins, T.I.; Ochalski, T.J.; Huyet, G.; Harris, J.S., Jr. Quantum-confined stark effect in Ge/SiGe quantum wells on Si. *IEEE J. Select. Top. Quantum Electron.* **2010**, *16*, 85–92. [\[CrossRef\]](#)
52. Christensen, J.S.; Radamson, H.H.; Kuznetsov, A.Y.; Svensson, B.G. Diffusion of phosphorus in relaxed Si_{1-x}Ge_x films and strained Si/Si_{1-x}Ge_x heterostructures. *J. Appl. Phys.* **2003**, *94*, 6533–6540. [\[CrossRef\]](#)

53. Wang, H.; Kong, Z.; Tan, X.; Su, J.; Du, J.; Lin, H.; Li, B.; Wang, Y.; Zhou, Z.; Miao, Y.; et al. High-performance GeSi/Ge multi-quantum well photodetector on a Ge-buffered Si substrate. *Opt. Lett.* **2024**, *49*, 2793–2796. [[CrossRef](#)]
54. Faverzani, M.; Calcaterra, S.; Biagioni, P.; Frigerio, J. Strong coupling in metal-semiconductor microcavities featuring Ge quantum wells: A perspective study. *Nanophotonics* **2024**, *13*, 1693–1700. [[CrossRef](#)]
55. Radamson, H.H.; Joelsson, K.B.; Ni, W.X.; Hultman, L.; Hansson, G.V. Characterization of highly boron-doped Si, Si_{1-x}Ge_x and Ge layers by high-resolution transmission electron microscopy. *J. Cryst. Growth* **1995**, *157*, 80–84. [[CrossRef](#)]
56. Bonfanti, M.; Grilli, E.; Guzzi, M.; Virgilio, M.; Grosso, G.; Chrastina, D.; Isella, G.; Von Känel, H.; Neels, A. Optical transitions in Ge/SiGe multiple quantum wells with Ge-rich barriers. *Phys. Rev. B* **2008**, *78*, 041407. [[CrossRef](#)]
57. Po-Hung, W.; Ying-Sheng, H.; Hung-Pin, H.; Cheng, L.; Shi-Hao, H.; Kwong-Kau, T. The study of temperature dependent strain in Ge epilayer with SiGe/Ge buffer layer on Si substrate with different thickness. *Appl. Phys. Lett.* **2014**, *104*, 241605. [[CrossRef](#)]
58. El Kurdi, M.; Kociniowski, T.; Ngo, T.P.; Boulmer, J.; Débarre, D.; Boucaud, P.; Damlencourt, J.F.; Kermarrec, O.; Bensahel, D. Enhanced photoluminescence of heavily n-doped germanium. *Appl. Phys. Lett.* **2009**, *94*, 191107. [[CrossRef](#)]
59. Sukhdeo, D.S.; Gupta, S.; Saraswat, K.C.; Dutt, B.; Nam, D. Impact of minority carrier lifetime on the performance of strained germanium light sources. *Opt. Commun.* **2016**, *364*, 233–237. [[CrossRef](#)]
60. Kumazawa, Y.; Xu, X.; Maruizumi, T.; Sawano, K. Effects of post annealing on in-situ n-doped Ge-on-Si. *Semicond. Sci. Technol.* **2018**, *33*, 124006. [[CrossRef](#)]
61. Cheng, T.H.; Peng, K.L.; Ko, C.Y.; Chen, C.Y.; Lan, H.S.; Wu, Y.R.; Liu, C.W.; Tseng, H.H. Strain-enhanced photoluminescence from Ge direct transition. *Appl. Phys. Lett.* **2010**, *96*, 211108. [[CrossRef](#)]
62. Chui, C.O.; Gopalakrishnan, K.; Griffin, P.B.; Plummer, J.D.; Saraswat, K.C. Activation and diffusion studies of ion-implanted p and n dopants in germanium. *Appl. Phys. Lett.* **2003**, *83*, 3275–3277. [[CrossRef](#)]
63. Baek, J.; Ki, B.; Kim, D.; Lee, C.; Nam, D.; Cho, Y.-H.; Oh, J. Phosphorus implantation into in situ doped Ge-on-Si for high light-emitting efficiency. *Opt. Mater. Express* **2016**, *6*, 2939–2946. [[CrossRef](#)]
64. Liu, J.; Sun, X.; Pan, D.; Wang, X.; Kimerling, L.C.; Koch, T.L.; Michel, J. Tensile-strained, n-type Ge as a gain medium for monolithic laser integration on Si. *Opt. Express* **2007**, *15*, 11272–11277. [[CrossRef](#)]
65. Kil, Y.-H.; Yang, H.D.; Yang, J.-H.; Park, A.H.; Kang, S.; Jeong, T.S.; Kim, T.S.; Shim, K.-H. Characterization of n-type Ge layers on Si (100) substrates grown by rapid thermal chemical vapor deposition. *Mater. Sci. Semicond. Process.* **2013**, *16*, 1405–1409. [[CrossRef](#)]
66. Yamamoto, Y.; Barget, M.R.; Capellini, G.; Taoka, N.; Virgilio, M.; Zaumseil, P.; Hesse, A.; Schroeder, T.; Tillack, B. Photoluminescence of phosphorous doped Ge on Si (100). *Mater. Sci. Semicond. Process.* **2017**, *70*, 111–116. [[CrossRef](#)]
67. Christensen, J.S.; Kuznetsov, A.Y.; Gunnaes, A.E.; Svensson, B.G.; Radamson, H.H. Phosphorus diffusion in the presence of threading dislocations in strain relaxed SiGe films. *Mater. Sci. Semicond. Process.* **2006**, *9*, 650–654. [[CrossRef](#)]
68. Schmid, M.; Oehme, M.; Gollhofer, M.; Körner, R.; Kaschel, M.; Kasper, E.; Schulze, J. Effect of heavy doping and strain on the electroluminescence of Ge-on-Si light emitting diodes. *Thin Solid Film* **2014**, *557*, 351–354. [[CrossRef](#)]
69. Frigerio, J.; Ballabio, A.; Gallacher, K.; Giliberti, V.; Baldassarre, L.; Millar, R.; Milazzo, R.; Maiolo, L.; Minotti, A.; Bottegoni, F.; et al. Optical properties of highly n-doped germanium obtained by in situ doping and laser annealing. *J. Phys. D Appl. Phys.* **2017**, *50*, 465103. [[CrossRef](#)]
70. Chui, C.O.; Kulig, L.; Moran, J.; Tsai, W.; Saraswat, K.C. Germanium n-type shallow junction activation dependences. *Appl. Phys. Lett.* **2005**, *87*, 091909. [[CrossRef](#)]
71. Lieten, R.R.; Douhard, B.; Stesmans, A.; Jivanescu, M.; Beeman, J.W.; Simoen, E.; Vandervorst, W.; Haller, E.E.; Locquet, J.P. Implantation and Activation of Phosphorus in Amorphous and Crystalline Germanium Layers. *ECS J. Solid State Sci. Technol.* **2013**, *2*, P346. [[CrossRef](#)]
72. Dutt, B.; Sukhdeo, D.S.; Nam, D.; Vulovic, B.M.; Yuan, Z.; Saraswat, K.C. Roadmap to an Efficient Germanium-on-Silicon Laser: Strain vs. n-Type Doping. *IEEE Photonics J.* **2012**, *4*, 2002–2009. [[CrossRef](#)]
73. Radamson, H.H.; Sardela, M.R.; Hultman, L.; Hansson, G.V. Characterization of highly Sb-doped Si using high-resolution x-ray diffraction and transmission electron microscopy. *J. Appl. Phys.* **1994**, *76*, 763–767. [[CrossRef](#)]
74. Xu, C.; Kouvetakis, J.; Menéndez, J. Doping dependence of the optical dielectric function in n-type germanium. *J. Appl. Phys.* **2019**, *125*, 085704. [[CrossRef](#)]
75. Park, C.-H.; Yako, M.; Wada, K.; Ishikawa, Y.; Ahn, D. High concentration phosphorus doping in Ge for CMOS-integrated laser applications. *Solid-State Electron.* **2019**, *154*, 43–49. [[CrossRef](#)]
76. Pastor, D.; Gandhi, H.H.; Monmeyran, C.P.; Akey, A.J.; Milazzo, R.; Cai, Y.; Napolitani, E.; Gwilliam, R.M.; Crowe, I.F.; Michel, J.; et al. High level active n+ doping of strained germanium through co-implantation and nanosecond pulsed laser melting. *J. Appl. Phys.* **2018**, *123*, 165101. [[CrossRef](#)]
77. Oehme, M.; Gollhofer, M.; Widmann, D.; Schmid, M.; Kaschel, M.; Kasper, E.; Schulze, J. Direct bandgap narrowing in Ge LED's on Si substrates. *Opt. Express* **2013**, *21*, 2206–2211. [[CrossRef](#)] [[PubMed](#)]

78. Jung, Y.; Kim, Y.; Burt, D.; Joo, H.-J.; Kang, D.-H.; Luo, M.; Chen, M.; Zhang, L.; Tan, C.S.; Nam, D. Biaxially strained germanium crossbeam with a high-quality optical cavity for on-chip laser applications. *Opt. Express* **2021**, *29*, 14174. [\[CrossRef\]](#) [\[PubMed\]](#)
79. Sun, X.; Liu, J.; Kimerling, L.C.; Michel, J. Direct gap photoluminescence of n-type tensile-strained Ge-on-Si. *Appl. Phys. Lett.* **2009**, *95*, 011911. [\[CrossRef\]](#)
80. Xu, X.; Hashimoto, H.; Sawano, K.; Maruizumi, T. Highly n-doped germanium-on-insulator microdisks with circular Bragg gratings. *Opt. Express* **2017**, *25*, 6550–6560. [\[CrossRef\]](#)
81. Kasai, J.-i.; Oda, K.; Okumura, T. Influence of n-type doping in germanium crystalline films grown on silicon substrates on room-temperature photoluminescence and optical absorption. *Jpn. J. Appl. Phys.* **2018**, *57*, 021303. [\[CrossRef\]](#)
82. Camacho-Aguilera, R.E.; Cai, Y.; Bessette, J.T.; Kimerling, L.C.; Michel, J. High active carrier concentration in n-type, thin film Ge using delta-doping. *Opt. Mater. Express* **2012**, *2*, 1462–1469. [\[CrossRef\]](#)
83. Huang, S.; Li, C.; Chen, C.; Wang, C.; Yan, G.; Lai, H.; Chen, S. In situ doped phosphorus diffusion behavior in germanium epilayer on silicon substrate by ultra-high vacuum chemical vapor deposition. *Appl. Phys. Lett.* **2013**, *102*, 182102. [\[CrossRef\]](#)
84. Xu, X.; Wang, X.; Nishida, K.; Takabayashi, K.; Sawano, K.; Shiraki, Y.; Li, H.; Liu, J.; Maruizumi, T. Ultralarge transient optical gain from tensile-strained, n-doped germanium on silicon by spin-on dopant diffusion. *Appl. Phys. Express* **2015**, *8*, 092101. [\[CrossRef\]](#)
85. Satta, A.; Simoen, E.; Clarysse, T.; Janssens, T.; Benedetti, A.; De Jaeger, B.; Meuris, M.; Vandervorst, W. Diffusion, activation, and recrystallization of boron implanted in preamorphized and crystalline germanium. *Appl. Phys. Lett.* **2005**, *87*, 172109. [\[CrossRef\]](#)
86. Suh, Y.S.; Carroll, M.S.; Levy, R.A.; Sahiner, M.A.; Bisognin, G.; King, C.A. Modeling of boron and phosphorus implantation into (100) Germanium. *IEEE Trans. Electron. Devices* **2005**, *52*, 91–98. [\[CrossRef\]](#)
87. Jain, J.R.; Dany-Sebastien, L.-G.; Krishna, C.B.; Justin, S.W.; Mark, L.B.; David, A.B.M.; Roger, T.H. Tensile-strained germanium-on-insulator substrate fabrication for silicon-compatible optoelectronics. *Opt. Mater. Express* **2011**, *1*, 1121. [\[CrossRef\]](#)
88. Zhou, Z.; Yin, B.; Michel, J. On-chip light sources for silicon photonics. *Light Sci. Appl.* **2015**, *4*, e358. [\[CrossRef\]](#)
89. Hartmann, J.M.; Benevent, V.; Reboud, V.; Chelnokov, A.; Guillo, K.; Pauc, N.; Calvo, V. Structural and electronic properties of in-situ phosphorous-doped Ge layers grown by reduced pressure-chemical vapour deposition. *Thin Solid Film* **2016**, *602*, 13–19. [\[CrossRef\]](#)
90. Vohra, A.; Khanam, A.; Slotte, J.; Makkonen, I.; Pourtois, G.; Porret, C.; Loo, R.; Vandervorst, W. Heavily phosphorus doped germanium: Strong interaction of phosphorus with vacancies and impact of tin alloying on doping activation. *J. Appl. Phys.* **2019**, *125*, 225703. [\[CrossRef\]](#)
91. Lee, C.; Yoo, Y.-S.; Ki, B.; Jang, M.-H.; Lim, S.-H.; Song, H.G.; Cho, J.-H.; Oh, J.; Cho, Y.-H. Interplay of strain and intermixing effects on direct-bandgap optical transition in strained Ge-on-Si under thermal annealing. *Sci. Rep.* **2019**, *9*, 11709. [\[CrossRef\]](#)
92. Liu, J.; Sun, X.; Camacho-Aguilera, R.; Kimerling, L.C.; Michel, J. Ge-on-Si laser operating at room temperature. *Opt. Lett.* **2010**, *35*, 679–681. [\[CrossRef\]](#)
93. Sukhdeo, D.S.; Gupta, S.; Saraswat, K.C.; Dutt, B.; Nam, D. Ultimate limits of biaxial tensile strain and n-type doping for realizing an efficient low-threshold Ge laser. *Jpn. J. Appl. Phys.* **2016**, *55*, 024301. [\[CrossRef\]](#)
94. Lee, K.H.; Bao, S.; Chong, G.Y.; Tan, Y.H.; Fitzgerald, E.A.; Tan, C.S. Fabrication and characterization of germanium-on-insulator through epitaxy, bonding, and layer transfer. *J. Appl. Phys.* **2014**, *116*, 103506. [\[CrossRef\]](#)
95. Nur, O.; Willander, M.; Hultman, L.; Radamson, H.H.; Hansson, G.V.; Sardela, M.R., Jr.; Greene, J.E. CoSi₂/Si_{1-x}Ge_x/Si(001) heterostructures formed through different reaction routes: Silicidation-induced strain relaxation, defect formation, and interlayer diffusion. *J. Appl. Phys.* **1995**, *78*, 7063–7069. [\[CrossRef\]](#)
96. Hu, C.; Xu, P.; Fu, C.; Zhu, Z.; Gao, X.; Jamshidi, A.; Noroozi, M.; Radamson, H.; Wu, D.; Zhang, S.-L. Characterization of Ni(Si,Ge) films on epitaxial SiGe(100) formed by microwave annealing. *Appl. Phys. Lett.* **2012**, *101*, 092101. [\[CrossRef\]](#)
97. Nur, O.; Willander, M.; Radamson, H.H.; Sardela, M.R., Jr.; Hansson, G.V.; Petersson, C.S.; Maex, K. Strain characterization of CoSi₂/n-Si_{0.9}Ge_{0.1}/p-Si heterostructures. *Appl. Phys. Lett.* **1994**, *64*, 440–442. [\[CrossRef\]](#)
98. Sidhant, G.; Shubham, S.; Peng, Z.; Kristopher, O.D.; Santosh, K.K. Standardization of Specific Contact Resistivity Measurements using Transmission Line Model (TLM). In *Proceedings of the 2020 IEEE 33rd International Conference on Microelectronic Test Structures (ICMTS)*, Edinburgh, UK, 4–18 May 2020; IEEE: Piscataway, NJ, USA, 2020; pp. 1–6.
99. Schroder, D.K. *Semiconductor Material and Device Characterization*, 3rd ed.; Wiley: Piscataway, NJ, USA, 2006.

Disclaimer/Publisher’s Note: The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of MDPI and/or the editor(s). MDPI and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.