

Review

Wafer Support Systems (WSSs) as Beam–Matter Interaction Platforms: Electrostatic Chucking, Thermal Transport, Metrology Coupling, Industrial Architectures, and Emerging Semiconductor Platforms

Abbas Alshehabi ^{1,*} , Jaafar Almutawa ²  and Mahmood Abduljabbar Hammad ¹¹ Department of Mechanical Engineering, Bahrain Polytechnic, Isa Town P.O. Box 33349, Bahrain² Department of Professional Development, Mathematics Department, Bahrain Polytechnic, Isa Town P.O. Box 33349, Bahrain

* Correspondence: abbas.alshehabi@polytechnic.bh

Abstract

Wafer support systems (WSSs) are commonly treated as passive mechanical fixtures in semiconductor tools, yet they function in practice as active beam-facing platforms that shape the conditions under which quantum beams interact with wafers. This review re-examines WSSs from a quantum beam science perspective by integrating beam–matter interaction physics, electrostatic chucking, thermal transport, precision stage dynamics, industrial platform architectures, and beam-coupled metrology within a unified framework. Drawing on academic and industrial sources, the review compares lithography, plasma-processing, deposition, inspection, and metrology environments to show how support-platform design influences stability, heat dissipation, charging behavior, vibration sensitivity, wafer flatness, and defect detectability. Particular emphasis is placed on electrostatic chucks as coupled electrical and thermal interfaces, on precision motion systems as beam-conditioning infrastructure, and on the growing role of support architectures in advanced X-ray, electron-beam, and hybrid metrology workflows. Selected comparative figures are constructed to support cross-platform interpretation. By framing WSSs as beam–matter interaction platforms rather than passive hardware, this review identifies new opportunities for linking beam physics, materials selection, thermal management, and precision engineering in next-generation semiconductor manufacturing and metrology, including emerging smart support architectures with sensing, adaptive control, and data-driven optimization.

Keywords: wafer support systems; electrostatic chuck; quantum beam science; semiconductor metrology; thermal transport; wafer stage; X-ray inspection; EUV lithography



Received: 9 May 2026

Revised: 23 June 2026

Accepted: 7 July 2026

Published: 23 July 2026

Copyright: © 2026 by the authors.

Licensee MDPI, Basel, Switzerland.

This article is an open access article distributed under the terms and conditions of the [Creative Commons Attribution \(CC BY\)](https://creativecommons.org/licenses/by/4.0/) license.

1. Introduction

Quantum beam technologies underpin a broad range of modern semiconductor fabrication, inspection, and metrology workflows, including extreme ultraviolet (EUV) lithography, X-ray inspection, electron-beam defect review, plasma etching, and ion-based processing [1–5]. In these environments, scientific and engineering attention is often directed toward the beam source, the optical or transport pathway, the detector, or the intrinsic response of the wafer material itself. By contrast, the physical platform that supports the wafer is frequently treated as a secondary mechanical element. Such a simplification is

no longer sufficient. As device dimensions continue to shrink, overlay tolerances tighten, and beam-based inspection extends into three-dimensional architectures and advanced packaging, the wafer support system (WSS) becomes a decisive part of the beam–matter interaction environment rather than a passive fixture [6–9].

In the present review, the term Wafer Support System (WSS) is used in a deliberately broad sense to include electrostatic chucks (ESCs), wafer stages, thermal-control layers, backside gas interfaces, pedestals or susceptors, and metrology-coupled positioning systems. Although these elements are distributed differently across lithography, etch, deposition, inspection, and metrology platforms, they share a common physical function: they define the thermal, mechanical, electrostatic, and geometric boundary conditions under which the beam interacts with the wafer [3,5,10,11]. Electrostatic chuck technologies and Coulomb/Johnsen–Rahbek chucking behavior are discussed in prior semiconductor-processing and plasma-processing studies [12–14]. In this sense, the WSS does not merely hold the wafer. Rather, it conditions beam-incidence stability, thermal drift, wafer flatness, vibration transmission, charging behavior, contamination risk, and the reproducibility of beam-enabled measurements and processes.

Figure 1 summarizes the conceptual framework adopted throughout this review. As shown schematically, representative beam sources, including EUV/X-ray, electron, ion, and laser beams, couple first to the wafer, but the resulting thermal, mechanical, and electrostatic responses are conditioned by the support interface and transmitted through the wider support architecture before appearing as a measurable metrology signal or a process outcome. Its purpose is not to depict a single tool geometry, but to emphasize a general scientific principle: beam–wafer interaction cannot be interpreted fully without also considering the support-mediated pathways through which energy, motion, charge, and measurement uncertainty evolve.




Figure 1. Schematic overview of beam–wafer support interactions in semiconductor processing and metrology. Representative beam sources, including EUV/X-ray, electron, ion, and laser beams, are shown on the left; major wafer-processing domains, including lithography and etching, deposition processes, and metrology/inspection, are shown in the center; and the corresponding support mechanisms, including the electrostatic chuck (ESC), precision wafer stage, and thermal-management subsystem, are shown at right. The diagram emphasizes that wafer support systems are not passive fixtures but active beam-facing platforms that mediate electrostatic confinement, thermal transport, positional stability, and process reproducibility. These coupled pathways collectively define the beam–wafer support physics that governs beam delivery, wafer stability, and measurement fidelity across semiconductor manufacturing and beam-based inspection environments.

This perspective is particularly important in quantum beam science because the observable response of a wafer is rarely determined by beam parameters alone. Even when the primary excitation is localized within the irradiated material volume, the subsequent evolution of that excitation depends strongly on support-mediated pathways for heat dissipation, mechanical relaxation, electrostatic redistribution, and positional stabilization [11,15–18]. A compact way to express this dependence is to regard the measured signal or process outcome, S , as a function not only of beam parameters $\mathbf{B}$ and wafer properties $\mathbf{W}$, but also of support-system properties $\mathbf{P}$,

$$S = S(\mathbf{B}, \mathbf{W}, \mathbf{P}), \quad (1)$$

where $\mathbf{P}$ may include chucking force, thermal contact resistance, stage stiffness, damping, electrical leakage, contamination state, and support-induced geometric or electrostatic non-uniformity. Equation (1) is general, but it makes explicit the central premise of this review: the support platform enters the beam-response problem as a physical variable rather than a fixed background condition. In a related spectroscopy context, this broader dependence is consistent with the argument that nominally identical samples may yield measurably different X-ray spectra when signal formation is conditioned by differences in temporal response, relaxation pathways, and the wider measurement environment [19].

The significance of this coupling can be illustrated through a simple timescale argument introduced by Alshehabi [18]. Let τ_{exc} denote a characteristic beam-driven excitation time and τ_{rel} a characteristic relaxation time associated with transport, dissipation, or support-mediated stabilization. The dimensionless ratio

$$\Lambda = \frac{\tau_{\text{rel}}}{\tau_{\text{exc}}} \quad (2)$$

then provides a useful conceptual measure of the extent to which non-equilibrium effects, transient drift, or support-limited stabilization influence the final outcome. When $\Lambda \ll 1$, relaxation proceeds rapidly relative to excitation, and the support may appear nearly transparent to the beam-driven process. When $\Lambda \gtrsim 1$, however, the support architecture can materially influence temperature gradients, charge persistence, mechanical blur, and metrology repeatability. Although the exact definitions of τ_{exc} and τ_{rel} vary with beam modality and experimental context, the general principle applies broadly across EUV exposure, electron-beam imaging, X-ray mapping, and plasma processing [11,15–18].

From an industrial standpoint, the importance of WSSs is already embedded in the architecture of advanced semiconductor tools. In lithography, wafer stages are highly active mechatronic subsystems whose precision directly determines overlay performance and throughput [6,11,20]. In plasma etching and deposition, ESCs and pedestal assemblies govern clamping stability, thermal uniformity, backside cooling efficiency, and contamination control [7–10,12–14]. In beam-based inspection and metrology, support stability affects line-of-sight fidelity, scan repeatability, background stability, and the detectability of buried or weakly contrasted defects [21–24]. These differences do not imply that each tool class presents an entirely separate support problem. Rather, they indicate that WSSs should be understood as a family of beam-facing architectures whose design priorities shift with beam modality, process window, and measurement objective.

A concise overview of this breadth is provided in Table 1, which compares representative semiconductor tool classes in terms of their dominant support elements, primary beam environments, and leading engineering constraints. The comparison makes clear that the support function is not uniform across the toolchain. In lithography, the dominant priorities are positioning precision, wafer flatness, and thermal-drift suppression. In etch and deposition, the emphasis shifts toward electrostatic stability, temperature control,

and contamination management. In inspection and metrology, by contrast, the central concerns become scan repeatability, vibration suppression, low-background stability, charging control, and alignment fidelity. This diversity of requirements reinforces the need to treat WSS as a flexible but scientifically unified class of beam-facing infrastructure.

Table 1. Scope of wafer support systems across representative semiconductor tool classes. The table is schematic and is intended to highlight how dominant support functions shift with beam environment and process objective.

Tool Class	Dominant Support Element	Primary Beam Environment	Dominant Engineering Constraint
Lithography	Wafer stage/wafer table	EUV or deep-UV photons	Positioning precision, wafer flatness, thermal-drift control
Etch	Electrostatic chuck/pedestal	Plasma ions, neutrals, electrons	Thermal uniformity, dielectric stability, contamination control
Deposition	Susceptor/ESC/heated pedestal	Plasma, ions, energetic neutrals, radiative heating	Temperature control, film uniformity, particle suppression
Inspection	Precision stage/scan platform	X-rays, electrons, optical beams	Vibration suppression, scan repeatability, low-background stability
Metrology	Positioning stage/chuck/fixture	Optical, electron, X-ray, hybrid beams	Repeatability, local flatness, charging control, alignment fidelity

The present review was motivated by the need for a unified treatment of these issues from a quantum beam science perspective. The existing literature is rich in specialized subfields, including beam–matter interaction physics [1,2], semiconductor manufacturing fundamentals [3–5], ESC technologies [10,12–14], thermal transport [15–17], precision stage dynamics [11,20], coherent X-ray imaging [21,22], and beam-based metrology [23,24]. However, these domains are only rarely synthesized around the common problem of how support architectures shape the boundary conditions of beam exposure and beam-enabled measurement. This fragmentation creates a gap between industrial practice, where support-system design is central, and academic beam literature, where it is often treated only implicitly.

Accordingly, we address five principal questions. First, how do different beam types couple to WSS architectures across lithography, etch, deposition, inspection, and metrology? Second, how do ESCs, wafer stages, and thermal pathways shape wafer response under beam exposure through electrostatic, thermal, and mechanical coupling? Third, how do industrial design philosophies differ across major equipment classes and manufacturers? Fourth, which emerging trends—including high-NA EUV, advanced X-ray inspection, hybrid metrology, and smart support platforms—are likely to be most consequential for future beam-compatible WSSs? Fifth, how can publicly available data, together with lightweight computational analysis, support more transparent and quantitative comparison across these architectures? Beyond providing a literature synthesis, the review proposes that wafer support systems can be treated as beam-facing boundary-condition structures whose influence may be interpreted through the generalized response relation $S(B, W, P)$ and the characteristic timescale ratio $\Lambda = \tau_{\text{rel}}/\tau_{\text{exc}}$. These concepts are not intended as predictive constitutive models, but as unifying frameworks for comparing support architectures across different beam environments and metrology modalities. The central conclusion advanced here is that WSS should be treated as an active scientific subsystem in beam-enabled semiconductor technology. Across tool classes, the support platform governs not only wafer handling but also the observable quality of beam interaction through its control of heat flow, field distribution, motion stability, wafer geometry, and contamination state. Recognizing WSSs as hidden beam infrastructures helps unify several areas that are too often treated separately and provides a clearer route toward future support architectures.

that are beam-aware, sensor-integrated, and quantitatively benchmarked. The sections that follow develop this argument through analysis of beam environments, beam–wafer support interaction physics, ESC and thermal architectures, stage dynamics, industrial platform comparisons, beam-coupled metrology, and future smart-support concepts.

2. Quantum Beam Environments Relevant to Wafer Support Systems

Wafer support systems (WSSs) operate under a wide range of beam environments whose physical characteristics differ substantially in penetration depth, spatial localization, energy-deposition pathway, and characteristic relaxation behavior. These differences are central to the present review because the role of the support platform is not universal; rather, it shifts with beam modality, process objective, and measurement architecture. In lithographic systems, the dominant support requirements are nanometer-scale positional stability, wafer flatness, and thermal-drift suppression. In plasma-based processing, electrostatic stability, backside cooling, pedestal thermal management, and dielectric robustness become dominant. In inspection and metrology platforms, by contrast, scan repeatability, vibration isolation, charging control, and low-background stability are often the controlling factors. A useful starting point is therefore to classify the principal beam environments encountered in semiconductor fabrication and measurement and to relate them explicitly to the support constraints they impose.

Extreme ultraviolet (EUV) and X-ray beams are particularly important because they couple strongly to both high-resolution fabrication and non-destructive inspection. EUV lithography employs radiation at a wavelength of approximately 13.5 nm, corresponding to a photon energy of about 92 eV,

$$E = \frac{hc}{\lambda} \approx 92 \text{ eV}, \quad (3)$$

where h is Planck's constant and c is the speed of light. Because EUV imaging operates under extremely tight focus and overlay budgets, even small support-induced deviations in wafer position, flatness, or thermal state can directly influence pattern fidelity and throughput [2,6,25,26]. X-ray beams in the keV regime, by contrast, are increasingly relevant to wafer inspection, buried-defect imaging, advanced packaging analysis, coherent diffractive imaging, ptychography, and tomography [21,22,27,28]. In such cases, the support platform must provide stable geometric alignment, low vibration, repeatable scan motion, and a support geometry that does not degrade contrast or introduce parasitic scattering.

The distinction between EUV and X-ray regimes is not merely instrumental; it is rooted in the differing penetration behavior of the beam itself. X-ray transmission through a material of thickness t is described by the Beer–Lambert law,

$$I = I_0 \exp(-\mu t), \quad (4)$$

where μ is the linear attenuation coefficient. The corresponding attenuation length is

$$\Lambda = \frac{1}{\mu}. \quad (5)$$

Because Λ depends strongly on photon energy and material composition, the effective sampling depth of an X-ray measurement is determined jointly by beam energy and material properties. This is one reason why X-ray-based WSS analysis must consider not only mechanical stability but also support-material transparency, background scattering, and the interpretation of depth-dependent contrast [2,27]. These trends are visualized directly in Figure 2, where the left panel compares representative attenuation lengths across

energy for materials relevant to wafers and support structures. The shaded low-energy region emphasizes the EUV regime, where absorption is so strong that the interaction becomes highly surface-confined, thereby amplifying the importance of local wafer flatness, support-induced deformation, and thermal drift.

Electron-beam environments impose a different but equally consequential set of constraints. Electron beams remain central to scanning electron microscopy (SEM), critical-dimension metrology, defect review, and voltage-contrast inspection [23,29–32]. Compared with photon-based probes, electrons exhibit much shorter interaction depths and are more sensitive to local charging, surface condition, and support-induced electrostatic perturbation. As a result, the WSS plays a central role in defining grounding pathways, electrical leakage behavior, local heating conditions, and fine-stage repeatability. In practical terms, the support system affects not only where the beam is delivered, but also how reliably the resulting contrast, dimensional measurement, or defect signature can be interpreted. A commonly used estimate for electron penetration depth in solids is given by the Kanaya–Okayama relation,

$$R_{\text{KO}} = 0.0276 \frac{AE_0^{1.67}}{\rho Z^{0.89}}, \quad (6)$$

where R_{KO} is in μm , A is the atomic mass, E_0 is the incident electron energy in keV, ρ is the density in g cm^{-3} , and Z is the atomic number [29]. Although approximate, this expression is useful for generating electron interaction-depth-versus-energy curves from publicly available material properties and for illustrating why support-induced charging and high-repeatability stage motion become critical in electron-beam measurements. This behavior is shown in the right panel of Figure 2, which complements the X-ray attenuation plot by demonstrating that electron-beam measurements probe markedly shorter and more surface-sensitive length scales. In consequence, local support-interface properties, grounding quality, and electrostatic boundary conditions become more visible in the measurement outcome.

Ion- and plasma-based environments impose yet another class of support constraints. In plasma etching, ion implantation, and plasma-assisted deposition, the WSS is exposed to plasma sheath formation, ion bombardment, dielectric charging, backside gas pressure, and thermal loading arising from ion energy transfer and plasma heating [7,8,10,12–14,33]. Electrostatic chucks are especially important in these systems because they must simultaneously clamp the wafer, maintain thermal uniformity, support backside cooling, and remain stable under dielectric and plasma-induced stress. The energy delivered by ions of charge q accelerated through a sheath potential V_s may be approximated as

$$E_i \approx qV_s, \quad (7)$$

highlighting the direct coupling between plasma conditions and support-surface loading. Relevant degradation modes include thermal non-uniformity, dielectric breakdown, particle generation, erosion, and support-induced contamination. Although these environments are less naturally summarized by a single attenuation-length curve, they reinforce the broader point that beam modality determines which support-mediated failure modes become dominant.

This diversity is summarized in Table 2, which compares representative beam classes in terms of their typical energy range, application context, and dominant wafer support sensitivity. The key point is not simply that different beams interact differently with matter, but that they activate different support-mediated limitations. EUV exposure is especially sensitive to motion, flatness, and thermal drift; X-ray inspection is highly sensitive to vibration, scan stability, and penetration-depth interpretation; electron beams are strongly

affected by charging and stage repeatability; and plasma or ion environments place primary emphasis on dielectric stability, thermal control, backside cooling, and contamination resistance. Table 2 provides the comparative framework that connects the underlying beam physics to the engineering logic of the support architecture.

Table 2. Representative beam classes and their dominant wafer support sensitivities. The table is schematic and intended to highlight how beam modality shifts the primary support constraint.

Beam Class	Typical Energy Range	Representative Application	Dominant WSS Sensitivity
EUV photons	~92 eV	High-resolution lithography	Positioning precision, wafer flatness, thermal-drift suppression
X-rays	keV range	Inspection, tomography, buried-defect imaging	Vibration stability, scan repeatability, penetration-depth interpretation
Electrons	keV range	Defect review, CD metrology, voltage contrast	Charging control, stage repeatability, local electrostatic stability
Ions/plasma species	eV–keV effective energy scales	Etch, implantation, plasma-assisted processing	Dielectric stability, thermal uniformity, backside cooling, contamination control

Figure 2 provides a compact physical comparison of beam penetration and attenuation scales relevant to wafer support systems. In the X-ray case, the key quantity is the attenuation length, which depends strongly on photon energy and material composition through the absorption coefficient [2,27]. This dependence determines the effective sampling depth of the measurement and therefore governs the extent to which buried structures, multilayer stacks, and support-related background contributions influence the detected signal. As photon energy increases, the attenuation length generally increases, so the beam probes a larger volume and becomes more sensitive to geometric stability, alignment fidelity, and depth-dependent signal interpretation. In the low-energy EUV regime, by contrast, absorption is extremely strong and the interaction is highly surface-confined, which makes wafer flatness, local deformation, and support-induced thermal drift especially important.

For electron beams, the relevant quantity is the interaction depth, which is much shorter and more sensitive to beam energy, density, and atomic composition. A useful estimate is provided by the Kanaya–Okayama relation [Equation (6)], which captures how electron penetration increases with incident beam energy while remaining comparatively shallow relative to many X-ray modalities [29]. This short interaction scale helps explain why electron-beam measurements are particularly sensitive to near-surface charging, grounding pathways, local heating, and fine-stage repeatability. In other words, the electron-beam response is more directly conditioned by local electrostatic and surface boundary conditions imposed by the wafer support system.

Taken together, the two panels of Figure 2 show that different beam classes probe fundamentally different length scales and therefore activate different support-mediated constraints. In the X-ray case, attenuation length controls effective sampling depth and influences the interpretation of buried-structure imaging, tomography, and multilayer inspection [21,22,27,28]. In the electron-beam case, interaction depth governs the extent to which charging, surface condition, and local support-induced electrostatic perturbations influence the measured response [23,29–32].




Figure 2. Representative comparison of beam penetration and attenuation behavior relevant to wafer support systems. The **(left)** panel shows X-ray attenuation length as a function of photon energy for representative materials, illustrating the strong energy and material dependence of photon penetration in beam-based inspection and metrology environments. The shaded low-energy region indicates the EUV regime, where absorption is extremely strong and interaction is therefore highly surface-confined. The **(right)** panel shows representative electron interaction depth as a function of beam energy, based on the Kanaya–Okayama relation, for several materials relevant to semiconductor processing and support architectures. Together, the two panels illustrate that different beam classes probe markedly different depth scales and therefore activate different support-mediated constraints. In the X-ray case, attenuation length controls the effective sampling depth and influences the interpretation of buried-structure imaging, tomography, and multilayer inspection. In the electron-beam case, interaction depth governs the extent to which charging, surface condition, and local support-induced electrostatic perturbations influence the measured response. The figure is intended as a comparative, physically motivated visualization derived from standard literature relations and publicly available material parameters, rather than as a reconstruction of proprietary tool conditions.

Taken together, these beam classes define the physical diversity that any rigorous review of wafer support systems must confront. The central implication is that support systems should not be assessed solely in terms of generic mechanical functionality, but rather in terms of the specific beam environments they are required to sustain and condition. The following sections therefore build from this beam-centered classification toward a deeper treatment of beam–wafer support interaction physics, electrostatic chucking, thermal transport pathways, stage dynamics, and industrial support architectures.

2.1. Distinct Contribution of the Present Review

Although electrostatic chucks, wafer stages, thermal-control systems, and semiconductor metrology platforms have each been reviewed extensively in the literature, they are typically treated as independent engineering subsystems. The present review differs by examining these elements as components of a unified wafer support system (WSS) that directly conditions beam–matter interactions. The conceptual framework developed here is based on two central constructs: the generalized beam-response relationship $S = S(B, W, P)$, which explicitly includes support-platform properties as independent variables, and the characteristic timescale ratio $\Lambda = \tau_{\text{rel}}/\tau_{\text{exc}}$, which provides a beam-science perspective on support-mediated stabilization. By integrating electrostatic, thermal, mechanical, and metrological functions within a single framework, the review seeks to bridge semiconductor equipment engineering and quantum beam science in a manner not emphasized in previous WSS-related reviews. A further distinction of the present review is

that the wafer support system is interpreted as a boundary-condition layer in beam–matter interaction physics rather than as a purely mechanical subsystem. Under this interpretation, electrostatic confinement, thermal transport, vibration transmission, charge dissipation, and metrological stability become coupled manifestations of the same support-mediated response. This perspective enables support architectures to be analyzed using concepts familiar to beam science, including excitation–relaxation pathways, transport processes, and measurement observables. The distinct scope of the present review compared with representative prior review categories is summarized in Table 3.

Table 3. Comparison between the scope of the present review and representative prior review categories.

Review Focus	ESC	Stage	Thermal	Metrology	Unified WSS
ESC reviews [12–14,34]	Yes	No	Partial	No	No
Stage reviews [20,35–37]	No	Yes	Partial	Partial	No
Thermal-control reviews [15–17,38–41]	Partial	No	Yes	No	No
Present review	Yes	Yes	Yes	Yes	Yes

2.2. Methodology Used for Comparative Figures

Several comparative figures presented throughout this review are derived from publicly available literature data, reported engineering ranges, and normalized parameter sets. Because proprietary semiconductor-tool datasets are generally unavailable, the figures are intended to illustrate relative trends and design trade-offs rather than absolute performance rankings. Where normalization is used, the procedure is stated explicitly in the corresponding caption.

3. Beam–Wafer Support Interaction Physics

The core physical role of wafer support systems (WSSs) is to condition how deposited beam energy is redistributed, dissipated, and rendered observable. A useful conceptual cascade is beam excitation $\rightarrow$ electronic excitation $\rightarrow$ phonons $\rightarrow$ thermal gradients $\rightarrow$ support-mediated dissipation. Once the support is treated as a finite thermal, electrostatic, and mechanical boundary rather than an ideal reservoir, it becomes clear that detectability, process stability, and metrology reproducibility are strongly support-dependent [1,2,15–17].

From a quantum beam science perspective, the relevant issue is not only how much energy is deposited but also whether the support platform responds on slower, comparable, or faster timescales than the beam-induced perturbation. This motivates a multiscale hierarchy treatment rather than a purely verbal comparison. In particular, beam-excited perturbations may relax through carrier scattering, phonon redistribution, thermal diffusion across the wafer support interface, structural settling, and active stage-control correction, each operating on distinct characteristic timescales [11,15,16,20].

3.1. Energy Deposition Cascade

A compact representation of the beam-driven cascade is

$$\mathcal{B} \rightarrow e^* \rightarrow ph \rightarrow \nabla T \rightarrow \mathcal{D}_{\text{WSS}}, \quad (8)$$

where $\mathcal{B}$ denotes the incident beam, e^* the electronically excited state population, ph the phonon subsystem, ∇T the evolving temperature field, and $\mathcal{D}_{\text{WSS}}$ the dissipation pathway mediated by the wafer support system. Equation (8) is schematic, but it is physically useful because it emphasizes that the support enters the problem at the level of boundary-conditioned transport rather than merely after the fact.

A characteristic excitation timescale may be introduced as

$$\tau_{\text{exc}} \sim \frac{E_{\text{dep}}}{P_{\text{beam}}}, \quad (9)$$

where E_{dep} is a representative deposited energy and P_{beam} is the local deposited beam power. While Equation (9) is a reduced estimate, it provides a useful comparison scale for subsequent transport and control processes.

The thermal redistribution timescale may be estimated as

$$\tau_{\text{th}} \sim \frac{L^2}{\alpha}, \quad (10)$$

where L is a characteristic transport length and $\alpha = k/(\rho C_p)$ is the thermal diffusivity, with k the thermal conductivity, ρ the density, and C_p the specific heat capacity [16,17]. Equation (10) makes clear that the relevant thermal response is not only a material property issue, but also a geometric and interfacial one.

Mechanical settling or support-limited dynamic stabilization may be expressed in reduced form as

$$\tau_{\text{mech}} \sim \frac{1}{\zeta \omega_n}, \quad (11)$$

where ζ is an effective damping ratio and ω_n a representative natural frequency of the stage–support structure [11,20]. For actively controlled stages, a further control timescale τ_{ctrl} may be associated with the bandwidth of the feedback system.

A useful dimensionless comparison is therefore

$$\Lambda_i = \frac{\tau_i}{\tau_{\text{exc}}}, \quad (12)$$

where τ_i may denote carrier relaxation, phonon relaxation, thermal diffusion, mechanical settling, or control response. When $\Lambda_i \ll 1$, the support-related process effectively equilibrates faster than excitation. When $\Lambda_i \gtrsim 1$, beam-induced perturbations may persist long enough to affect imaging, overlay, thermal reproducibility, or defect visibility.

Figure 3 is therefore intended to summarize the relative placement of these characteristic processes on a log-scale axis, using literature-informed ranges rather than single point values.

3.2. Interface-Mediated Observables

Support-platform properties influence what is ultimately measured or achieved under beam exposure. Several observables are especially sensitive to WSS boundary conditions:

- Beam blur through motion: stage vibration, structural compliance, or support resonance can smear the spatial response during exposure, scanning, or imaging [11,20].
- Overlay error from thermal expansion: spatially non-uniform heating of the wafer support assembly can shift local position and degrade alignment accuracy [16,42].
- Support-induced metrology background: finite thermal contact, partial charging, or parasitic mechanical response may alter apparent signal stability or noise floors [15,29,30].
- Detectability thresholds: buried or weak defects may become harder to discriminate when the support introduces drift, background variability, or locally non-uniform dissipation.

These effects can be understood by regarding the support as an active transfer layer between deposition and observation. In practical terms, a beam-excited state is never interpreted in isolation; it is always observed through the wafer support boundary and the dynamics that boundary imposes.




Figure 3. Characteristic timescales in beam–wafer support interaction. Horizontal bars indicate approximate, literature-informed ranges for the principal processes linking beam excitation to wafer and support response. The earliest interval, labeled beam excitation/local deposition ($\sim 10^{-15}$ – 10^{-9} s), represents the duration over which incident beam energy is delivered locally, depending on beam modality and excitation conditions. Carrier scattering/thermalization ($\sim 10^{-14}$ – 10^{-12} s) denotes the ultrafast redistribution of deposited energy within the electronic subsystem, while phonon redistribution ($\sim 10^{-12}$ – 10^{-9} s) represents subsequent transfer into lattice degrees of freedom and early vibrational equilibration. The wafer thermal diffusion range ($\sim 10^{-7}$ – 10^{-3} s) reflects order-of-magnitude estimates from $\tau_{\text{th}} \sim L^2/\alpha$ over characteristic transport lengths relevant to beam-heated wafer regions, including the influence of finite wafer support thermal coupling. The slower mechanical settling interval ($\sim 10^{-4}$ – 10^{-1} s) corresponds to structural relaxation and damping of the wafer-stage/support assembly, whereas stage control response ($\sim 10^{-3}$ – 10^0 s) represents the characteristic correction times associated with closed-loop positioning and precision motion control. The plotted ranges are intended as a comparative multiscale map rather than as universal fixed values; their exact limits depend on material properties, beam type, deposited power density, geometric length scale, interface conductance, structural damping, and controller bandwidth. The ultrafast excitation, carrier, and phonon ranges are consistent with standard treatments of beam–matter interaction, X-ray interaction, and non-equilibrium energy relaxation in solids [1,2,15,16,19,29]. The thermal diffusion range follows classical and nanoscale heat-transport scaling [15–17], while the mechanical settling and stage-control ranges are representative of high-precision lithographic and mechatronic stage systems [11,20,35,43]. As a representative semiconductor example, electron-beam inspection may involve excitation times below 10^{-9} s, whereas support-mediated thermal equilibration and mechanical stabilization often occur over 10^{-4} – 10^{-1} s. The resulting Λ values substantially exceed unity, illustrating why support-system dynamics can influence measurement outcomes despite occurring after the primary excitation event.

3.3. Illustrative Application of the $S(B, W, P)$ Framework

As a simple example, consider electron-beam defect inspection on a silicon wafer. In this case, the beam term B includes electron energy and current, the wafer term W includes material composition and surface condition, while the support term P includes local charging behavior, grounding quality, and stage stability. An increase in support-induced charging may alter local electron trajectories, resulting in voltage-contrast variations and measurement uncertainty even when the beam and wafer properties remain unchanged. In this example, the observable signal is therefore influenced directly by support-platform characteristics. As an illustrative numerical example, consider a nominal electron-beam

inspection process operating at fixed beam energy and current. If support-induced charging modifies the local landing position of electrons by only approximately 1%, the resulting voltage-contrast variation may become comparable to the contrast difference associated with weak subsurface defects. In this situation, the measured signal changes even though the beam parameters and wafer composition remain unchanged, demonstrating explicitly that the support variable P contributes directly to the observable response. A related timescale comparison can be made by considering an excitation time of order 10^{-9} s and a support-mediated relaxation time of order 10^{-4} s. The resulting ratio $\Lambda \approx 10^5$ indicates that support-related processes evolve much more slowly than the beam excitation event itself, thereby influencing signal stability, repeatability, and metrological interpretation.

3.4. Boundary Conditions Imposed by Support Design

Several WSS-specific boundary conditions are especially important.

First, *finite thermal contact* between the wafer and the support limits local heat extraction and introduces spatially varying temperature fields. Even when the bulk support has high thermal conductivity, a finite interface conductance can dominate the short-time thermal response [15,16].

Second, *electrostatic non-uniformity* arising from dielectric variation, electrode design, or local charging can produce non-uniform clamping and local mechanical distortion. This is particularly relevant in electrostatic chucking environments and in plasma-facing tools where charging and leakage behavior are non-trivial [10,12–14,44–46].

Third, *backside helium cooling* introduces a gas-mediated transport channel that is powerful but not perfectly uniform. Spatial variations in local gap, pressure, or flow distribution can produce radial temperature gradients and process non-uniformity [47,48].

Fourth, *support-induced vibration modes* determine the dynamic mechanical filter through which the beam is delivered or through which the signal is interpreted. In high-precision lithography and inspection, support and stage compliance cannot be ignored because they directly affect measurement sharpness, scan fidelity, and reproducibility [11,20,35,43].

These interface conditions and their representative consequences are summarized in Table 4. A wider implication is that WSS should be described not merely by static specifications such as clamping force or thermal conductivity, but by a coupled response envelope spanning electrostatic, thermal, and dynamic timescales.

As discussed above, the multiscale comparison in Figure 3 represents excitation, relaxation, transport, and support-dynamic response in a single beam-science framework.

Table 4. Interface condition versus beam consequence.

Interface Condition	Physical Origin	Representative Beam Consequence
Finite thermal contact	Imperfect wafer support coupling	Local heating, thermal drift, apparent signal instability
Electrostatic non-uniformity	Field gradients, dielectric variation, charge accumulation	Non-uniform clamping, local distortion, charging artifacts
Dynamic compliance	Structural flexibility, stage resonances, support modes	Motion blur, scan error, overlay loss
Backside gas cooling heterogeneity	Gap, pressure, and flow non-uniformity	Radial temperature variation, process non-uniformity

4. Electrostatic Chucking as Beam-Facing Support Physics

Electrostatic chucks (ESCs) are often introduced as wafer-clamping devices, but for beam-facing semiconductor platforms, they should be treated more fundamentally as coupled electrostatic, thermal, dielectric, and contamination-sensitive boundary structures.

In this broader view, the ESC is not merely a fixture beneath the wafer; it defines the local electric field distribution, participates in heat extraction, mediates wafer flatness and contact quality, and conditions how plasma, charged particles, or beam-induced charge are dissipated or accumulated [10,12–14,33,44,45]. This beam-facing role becomes increasingly important when the wafer is exposed to non-uniform thermal loading, plasma sheath fields, or charged-particle fluxes, because support-induced perturbations may propagate into overlay drift, local heating, charge retention, and process non-uniformity.

A useful starting point is to distinguish Coulomb and Johnsen–Rahbek (JR) operating regimes. In the idealized Coulomb picture, the wafer–chuck system is approximated as a dielectric-separated capacitor, and the electrostatic pressure can be written as

$$p_C \approx \frac{1}{2} \varepsilon_{\text{eff}} \left(\frac{V}{d_{\text{eff}}} \right)^2, \quad (13)$$

where ε_{eff} is an effective permittivity, V is the applied chuck voltage, and d_{eff} is an effective electrical spacing that includes dielectric thickness, microscopic gap effects, and interfacial non-idealities [12–14,44,45]. The corresponding clamping force is

$$F_C \approx p_C A, \quad (14)$$

with A the effective clamping area. In practice, however, this idealized form must be interpreted cautiously because wafer topography, microgaps, dielectric inhomogeneity, and local charge accumulation can all perturb the field distribution.

By contrast, the Johnsen–Rahbek mechanism relies on finite interfacial conduction and field-enhanced contact behavior, producing an effective clamping response that can exceed a purely ideal dielectric prediction under appropriate surface and material conditions [10,34,44–46]. This stronger clamping can be technologically advantageous, but it also makes JR-type behavior more sensitive to surface state, leakage pathways, interface contamination, and electrical conditioning history. In beam- or plasma-exposed environments, that sensitivity becomes especially relevant because the same interfacial conductivity that enhances clamping may also amplify drift, retention, or charging asymmetry under non-uniform irradiation.

4.1. Coulomb Versus Johnsen–Rahbek Chucks

The distinction between Coulomb and JR ESCs is best understood not as a strict binary, but as a spectrum of electrostatic support behavior shaped by dielectric properties, interface roughness, resistivity, and local conduction pathways [10,12–14,34]. Coulomb ESCs are often preferred conceptually because the dominant clamping mechanism is easier to interpret in terms of field strength and dielectric spacing. They tend to exhibit lower leakage tendency and a more straightforward relationship between applied voltage and holding force, which is advantageous in environments where electrostatic reproducibility and low charge memory are important. However, the effective clamping force can be limited when the interface contains significant microscopic gaps or when the dielectric architecture reduces the attainable interfacial field.

JR ESCs, on the other hand, can provide stronger effective clamping at lower apparent field demand because finite conduction near the interface enhances the attractive force. This is particularly useful in plasma processing, where reliable wafer retention under thermal cycling and sheath-driven perturbation is required [12,14,33]. The trade-off is that JR-dominant systems are more susceptible to leakage-current evolution, surface-state sensitivity, and condition-dependent behavior. From a beam-science viewpoint, this means that the support platform is not electrostatically neutral: its microscopic electrical state may

change during exposure, and those changes can feed back into thermal contact, charge dissipation, and local field uniformity.

A compact way to express the distinction is to write the total clamping force as

$$F_{\text{ESC}} = F_{\text{C}} + F_{\text{JR}} + \Delta F_{\text{int}}, \quad (15)$$

where F_{C} denotes the ideal dielectric Coulomb contribution, F_{JR} the conduction-assisted enhancement, and ΔF_{int} collects non-ideal interfacial effects such as roughness, trapped charge, contamination, edge fringing, and localized conduction channels. Equation (15) is not intended as a predictive constitutive law, but as a useful interpretive decomposition for comparing support architectures. The effective Johnsen–Rahbek contribution depends strongly on the electrical conductivity of the dielectric/interface system because finite leakage current promotes charge redistribution near the wafer–chuck interface. Consequently, variations in conductivity arising from temperature, material composition, plasma exposure, or surface conditioning can modify the magnitude and stability of the JR component.

4.2. Mixed-Mode Coulomb–Johnsen–Rahbek Behavior

Although Coulomb and Johnsen–Rahbek (JR) chucking are often presented as distinct limiting cases, practical industrial electrostatic chucks frequently exhibit mixed-mode behavior. The relative contribution of Coulomb and JR forces depends on dielectric conductivity, applied voltage, temperature, surface condition, plasma exposure history, and leakage-current pathways. Consequently, the effective clamping force may evolve during operation and cannot always be represented by a purely capacitive or purely JR mechanism. Mixed-mode behavior is particularly relevant in plasma-processing environments where conductivity and charge-transport properties vary dynamically. Accordingly, the Coulomb and Johnsen–Rahbek mechanisms should be regarded as limiting descriptions within a continuum of practical ESC behavior rather than as mutually exclusive operating modes.

4.3. ESC Material Systems

The physical performance of an ESC is inseparable from its material system. Common platform materials include AlN, Al₂O₃, SiC, multilayer ceramics, coated dielectric stacks, and architectures incorporating embedded heaters, temperature sensors, or cooling channels [44–46,49–51]. AlN is attractive because of its relatively high thermal conductivity and its usefulness when the ESC is expected to serve simultaneously as a clamping layer and a heat-removal pathway. Al₂O₃ remains important because of its dielectric robustness, fabrication maturity, and broad use in plasma-exposed environments. SiC and SiC-related systems become attractive where higher thermal robustness, mechanical rigidity, or harsher process compatibility are required. Multilayer ceramic structures expand the design space further by allowing electrostatic function, thermal management, and embedded actuation or sensing to be spatially co-designed.

Protective and functional coatings add another level of control. They may be introduced to tailor surface resistivity, plasma resistance, contamination behavior, or wear performance, but they also modify interfacial contact resistance and local field structure. Recent coating studies therefore matter not merely as materials processing refinements, but as direct interventions into beam-facing support physics [50,51]. Likewise, embedded heaters convert the ESC into a thermal-conditioning platform rather than a passive dielectric body, making the chuck an active participant in radial temperature control, transient settling, and spatial uniformity.

4.4. Thermal–Electrostatic Coupling

A central point for this review is that an ESC cannot be understood solely from electrostatic holding force. It simultaneously acts as: (i) a clamping element, (ii) a thermal pathway, (iii) an electrical boundary layer, and (iv) a contamination-sensitive interface. These roles are coupled. Stronger clamping may improve thermal contact by reducing effective microgap volume, while dielectric charging or non-uniform leakage may distort local electric fields and thereby alter local contact conditions. In plasma-facing environments, the ESC also participates in the effective boundary condition seen by the sheath, meaning that thermal and electrical states cannot be fully separated [12,14,33,52,53].

A simple effective thermal relation can be written as

$$q'' = \frac{T_w - T_s}{R_{th,int} + R_{th,ESC} + R_{th,cool}}, \quad (16)$$

where q'' is the heat flux from wafer to sink, T_w is the wafer temperature, T_s is the sink-side temperature, and the denominator collects effective interfacial, bulk-ESC, and downstream cooling resistances. Equation (16) makes clear that the chuck is not only an electrical component; it is also embedded in the dominant thermal pathway. If clamping state, interface condition, or charge-induced contact variation changes, then $R_{th,int}$ may change as well, altering wafer temperature non-uniformity and transient settling.

This coupling is especially important when the wafer is subjected to non-uniform beam or plasma loading. Localized thermal loading can increase leakage or modify dielectric response; local electrical asymmetry can in turn perturb clamping pressure and contact quality. The resulting feedback does not require catastrophic failure to become important. Even mild spatial non-uniformity may appear experimentally as edge-to-center temperature deviation, local pattern distortion, process drift, or metrology scatter.

4.5. Failure and Drift Modes

From a beam-facing perspective, ESC degradation is best understood in terms of failure and drift modes rather than only absolute holding strength. One major mode is dielectric charging, in which trapped charge or condition-dependent leakage alters the local field distribution and changes the effective electrostatic response over time [10,33]. A second is the formation of local hot spots caused by spatially non-uniform thermal contact, interfacial conduction asymmetry, or beam/plasma loading. A third is erosion or surface damage in plasma-rich environments, which can modify both the dielectric boundary and the contamination state of the interface. Additional modes include field non-uniformity associated with electrode geometry or dielectric variation, and edge effects driven by fringing fields, reduced contact quality, or altered cooling near the wafer perimeter.

These effects can be organized with a simple drift relation:

$$\Delta\Phi_{ESC}(t, r) = \Delta\Phi_\rho(t, r) + \Delta\Phi_q(t, r) + \Delta\Phi_T(t, r) + \Delta\Phi_{edge}(r), \quad (17)$$

where $\Delta\Phi_{ESC}$ denotes a generic local deviation in ESC state, and the right-hand side collects contributions from resistive evolution, trapped or accumulated charge, thermal variation, and edge-field effects. Equation (17) is schematic, but it is useful because it frames ESC instability as a spatially resolved boundary-condition problem rather than a single scalar failure threshold.

The practical implication is that beam-facing ESC design should be judged not only by peak clamping capability but also by how robustly it preserves uniform electrostatic, thermal, and contamination boundary conditions under realistic process loading. This is

why multi-zone ESCs, coated ESCs, and sensor-embedded ESCs are increasingly attractive: they do not merely add complexity but address the coupled nature of support-induced drift.

Table 5 summarizes the major ESC architecture families discussed in this section. Figure 4 provides a schematic cross-section emphasizing the coupled electrostatic, thermal, and gas-mediated pathways. Figure 5 summarizes normalized, literature-informed trade-offs among major electrostatic chuck families across clamping robustness, thermal pathway quality, dielectric stability, plasma compatibility, and integration complexity.




Figure 4. Schematic cross-section of an electrostatic chuck (ESC) illustrating its coupled roles as a wafer-clamping interface, thermal pathway, dielectric boundary layer, and gas-mediated support structure [10,12–14,33]. The wafer is shown above a microscopic contact/interface region in which real contact spots and microgaps coexist, emphasizing that clamping, heat transfer, and charge behavior are strongly interface-dependent [12,44,45]. Beneath the wafer, the ESC includes a dielectric top layer and an embedded electrode that together generate the electrostatic holding force. Depending on material properties and interface conduction, this force may arise predominantly from an idealized Coulomb mechanism or may be enhanced by Johnsen–Rahbek-type behavior [13,44,45]. The bulk ceramic body provides the structural and thermal backbone of the chuck and may consist of materials such as AlN, Al₂O₃, or related multilayer ceramic architectures [33,44,45]. Optional embedded heater traces are included to indicate that modern ESCs may function not only as passive clamps but also as active thermal-conditioning platforms [10,33]. The lower part of the schematic indicates the downstream cooling path, while the backside gas pathway highlights the role of gas-mediated heat transfer in controlling wafer temperature uniformity [10,52,53]. Arrows indicate the principal coupled processes: electrostatic attraction normal to the wafer surface, downward heat flow from wafer to cooled support, possible leakage-current pathways through or near the dielectric/interface region, and edge-field concentration near the wafer perimeter. These edge and interface regions are especially important because they are vulnerable to field crowding, charge retention, leakage evolution, local hot spots, and thermal non-uniformity [12–14]. The schematic is intended as a physics-based interpretive diagram rather than a proprietary engineering drawing, emphasizing that ESC performance must be understood as a coupled electrostatic–thermal–interfacial boundary-condition problem rather than solely as a question of peak clamping force.

Despite their promise, sensor-integrated ESC architectures remain challenging because sensing elements must operate reliably under vacuum conditions, plasma exposure, elevated temperatures, and strong electromagnetic fields. Additional challenges include electrical isolation, signal-routing complexity, calibration drift, packaging reliability, and long-term compatibility with semiconductor process environments.




Figure 5. Normalized comparison of major electrostatic chuck (ESC) families, shown as a comparative synthesis across representative support-performance dimensions: clamping robustness, thermal pathway quality, dielectric stability, plasma compatibility, and integration complexity. The categories summarize the main engineering and physics trade-offs discussed in this section rather than absolute performance rankings. Coulomb ESCs are represented as having relatively high dielectric stability and conceptual simplicity, but more limited clamping robustness in demanding operating windows. Johnsen–Rahbek (JR) ESCs show stronger effective clamping and good plasma relevance, but with greater sensitivity to leakage pathways, charge history, and surface condition. Coated ESCs are shown as offering improved plasma compatibility and potentially improved surface robustness, while introducing additional interface complexity that can affect both electrical and thermal behavior. Multi-zone ESCs exhibit strong potential for improved thermal pathway quality and spatial control, but at the cost of higher system complexity. Sensor-embedded ESCs are shown as particularly attractive for observability, adaptive control, and advanced thermal management, although they impose the highest integration burden. All values are normalized, literature-informed comparative indices intended only to visualize qualitative trade-offs among ESC families. They should therefore be interpreted as an illustrative, non-proprietary synthesis rather than as benchmarked device data or direct product-level performance claims [10,12–14,33,44–46,49–53].

Table 5. Comparison of electrostatic chuck (ESC) architectures.

ESC Type	Operating Principle	Thermal Pathway Quality	Dielectric Stability	Plasma Compatibility	Likely Limitation
Coulomb ESC	Electrostatic attraction across an insulating dielectric layer	Moderate-to-good, depending on contact quality and ceramic conductivity	Generally high if dielectric integrity is preserved	Good in many applications, but sensitive to interfacial microgaps	May provide weaker effective clamping than JR systems
Johnsen–Rahbek ESC	Conduction-assisted enhanced electrostatic attraction near the interface	Often improved through stronger apparent contact, but condition dependent	Moderate; more sensitive to leakage pathways and surface electrical state	Widely relevant in plasma processing	Greater sensitivity to leakage evolution, charge history, and surface condition
Coated ESC	Base ESC modified by a functional or protective coating	Can improve or degrade contact depending on coating thickness and interface quality	Potentially improved surface robustness, but coating defects may become weak points	Often improved for plasma exposure and contamination control	Added interface complexity; coating durability becomes critical

Table 5. Cont.

ESC Type	Operating Principle	Thermal Pathway Quality	Dielectric Stability	Plasma Compatibility	Likely Limitation
Multi-zone ESC	Spatially segmented electrostatic and/or thermal actuation	High potential for improved thermal uniformity and local control	Depends on dielectric segmentation and electrical isolation quality	Good when local control is required	Higher control complexity and integration burden
Sensor-embedded ESC	Integrated temperature, electrical, or condition monitoring	Potentially strong due to feedback-enabled observability	Architecture dependent	Promising for advanced adaptive control	Still emerging; robustness, calibration, and integration overhead remain challenges

5. Thermal Transport and Temperature-Field Control

Thermal control in wafer support systems (WSSs) is fundamentally a beam-science issue rather than merely a process-engineering consideration. Beam-induced heating, support-mediated dissipation, and spatially non-uniform temperature fields directly influence overlay accuracy, focus stability, wafer deformation, and the reproducibility of beam-coupled measurements and processes [15–17]. In lithography, even small thermally induced distortions can propagate into overlay and focus errors, while in plasma processing and charged-particle environments the coupling between heating, chuck response, and wafer-state evolution can strongly affect process uniformity and repeatability [42,47,48].

The thermal pathway in a WSS is inherently multistage. Heat deposited in the wafer or at the near-surface interaction region may be redistributed through lateral wafer conduction, wafer-to-chuck thermal contact, bulk chuck conduction, backside helium-assisted heat transfer, and finally stage or pedestal heat sinking. The relative importance of these pathways depends on the beam environment, spatial power density, duty cycle, and the thermophysical properties of the support stack. Accordingly, WSS thermal design must be interpreted in a beam-specific manner rather than through a single generic notion of “temperature control”.

A comparative treatment should distinguish between single-zone supports, multi-zone heater architectures, embedded cooling channels, and edge-assisted or ring-assisted thermal control strategies. These design choices become especially important when comparing distinct thermal loading regimes such as pulsed or scan-based EUV exposure, continuous plasma loading, local electron-beam heating, and spatially localized X-ray scanning. Table 6 summarizes the dominant heat sources, primary thermal pathways, and key thermal concerns across representative tool classes.

The choice of WSS material further constrains thermal behavior because thermal conductivity, coefficient of thermal expansion (CTE), dielectric robustness, and electrical resistivity jointly determine the ability of the support platform to dissipate beam-deposited heat while maintaining electrostatic integrity and dimensional stability. Table 7 provides an illustrative qualitative comparison of representative support materials. These materials are quantitatively compared in Figure 6.

Representative material-property values used in the normalized comparison presented in Figure 6 are summarized in Table 8.

Table 6. Thermal architecture comparison across representative wafer support tool classes.

Tool Class	Dominant Heat Source	Primary Thermal Path	Uniformity Need	Likely Failure Mode
Lithography	Beam exposure, stage environment, and local absorption	Wafer-to-table coupling and stage cooling	Very high	Overlay drift, focus shift, and wafer-shape distortion
Plasma etch	Plasma loading, ion bombardment, and RF-induced heating	ESC conduction with backside He cooling	High	Radial temperature non-uniformity, etch-rate variation, and local hot spots
Deposition	Heaters, plasma exposure, and exothermic surface reactions	Support heating/cooling through gas, structure, and chuck body	High	Film non-uniformity, growth instability, and support-induced thermal gradients
Inspection/metrology	Local scan dose, ambient drift, and repeated scanning	Stage/support thermal buffering with passive or active stabilization	Moderate to high	Scan drift, registration error, and repeatability loss

Table 7. Illustrative material metrics relevant to WSS thermal design.

Material	<i>k</i>	CTE	Dielectric Robustness	Typical WSS Role
AlN	High	Moderate	Good	ESC substrate, high-conductivity thermal pathway material
Al ₂ O ₃	Moderate	Moderate	Very good	Mature insulating ceramic, dielectric layer, ESC body material
SiC	High	Low–moderate	Application-dependent	Advanced support material for harsh or thermally demanding environments
Coated ceramic	Tunable	Tunable	Tunable	Surface-engineered interface, protective layer, tailored thermal/electrical response




Figure 6. Illustrative material-property comparison for representative wafer support-system ceramics. The grouped bars show normalized thermal conductivity, thermal expansion coefficient, and dielectric constant for Al₂O₃, AlN, SiC, Si₃N₄, and quartz. The values are representative room-temperature, literature-informed estimates and are intended as a comparative synthesis rather than proprietary product-level benchmark data

Table 8. Representative material-property values used to construct the normalized comparison in Figure 6. Values are illustrative, literature-informed room-temperature estimates and are not intended as proprietary tool specifications or product-level benchmarks.

Material	<i>k</i> W m ^{−1} K ^{−1}	α_T 10 ^{−6} K ^{−1}	ϵ_r –
Al ₂ O ₃	30	7.5	9.8
AlN	170	4.5	8.8
SiC	120	4.0	9.7
Si ₃ N ₄	25	3.2	7.5
Quartz	1.4	0.5	3.8

Note: The values in Figure 6 are normalized separately by the maximum value of each property to visualize WSS material trade-offs. Higher normalized thermal conductivity indicates stronger heat-spreading potential, whereas lower thermal expansion is generally preferable for thermal-dimensional stability.

6. Mechanical Stability, Stage Dynamics, and Vibration Pathways

In advanced lithography and high-resolution inspection, the stage should be treated as part of the beam-conditioning infrastructure rather than as an isolated motion subsystem. From a quantum beam science perspective, the support-stage assembly sets the dynamic boundary conditions under which beam positioning, scan fidelity, image sharpness, overlay, and repeatability are realized. Accordingly, wafer support systems must be analyzed not only in terms of static positioning precision but also in terms of vibration transmission, dynamic compliance, control bandwidth, and disturbance rejection [11,20].

A useful comparative framework is to distinguish among magnetically levitated stages, air-bearing stages, linear-motor stages, and coarse/fine dual-stage architectures. Each offers a different balance of travel range, dynamic stiffness, isolation capability, acceleration, control complexity, and susceptibility to infrastructure-induced error. Magnetically levitated platforms offer excellent dynamic isolation and control authority, whereas air-bearing stages remain attractive because of their maturity and smooth precision motion. Linear-motor stages are advantageous for acceleration and throughput, but they typically require stronger compensation against dynamic and thermal error. Coarse/fine dual-stage systems offer a particularly important compromise, combining long travel with nanometer- or sub-nanometer-scale correction [11,20,35–37,43].

Relevant disturbance sources include actuator excitation, vacuum hardware, coolant flow, thermally induced strain relaxation, platform resonances, and facility coupling. These sources do not affect all beam modalities equally. In EUV lithography, small dynamic errors can directly degrade overlay and focus control. In X-ray inspection and scanning metrology, line-of-sight integrity and scan stability are critical. In electron-beam metrology and defect review, local mechanical stability must be considered together with charging and grounding conditions, since both contribute to apparent image instability and measurement uncertainty [21,23,25,54].

Table 9 summarizes the main stage philosophies relevant to beam-facing wafer support systems. Figure 7 is a comparison of representative vibration sensitivity or displacement-amplitude-versus-frequency behavior.

Table 9. Stage-architecture comparison for beam-facing wafer support systems.

Stage Architecture	Precision Strength	Dynamic Strength	Representative Beam Use Case	Dominant Limitation
Magnetically levitated stage	Very high positioning potential	Excellent mechanical decoupling and control flexibility	EUV lithography, ultra-high-precision scanning, and advanced inspection	High system complexity and demanding control integration
Air-bearing stage	Smooth motion with mature implementation	Good translation precision and repeatability	Optical lithography, precision metrology, and mature inspection platforms	Sensitivity to infrastructure quality, air supply stability, and implementation details
Linear-motor stage	High acceleration and throughput capability	Good dynamic response under active control	High-throughput wafer transport, fast scanning, and production-oriented systems	Requires strong compensation for vibration, thermal drift, and servo error
Coarse/fine dual-stage architecture	Fine correction over a large travel range	Good balance of stroke, bandwidth, and precision	Lithography and inspection platforms requiring long travel with fine positioning	Control-architecture complexity and subsystem-integration burden




Figure 7. Illustrative comparison of normalized stage-stability and vibration-sensitivity behavior for representative wafer support and positioning architectures. The plotted curves show synthetic disturbance-response envelopes as a function of disturbance frequency for air-bearing, linear-motor, magnetically levitated, and coarse/fine dual-stage systems. Lower normalized displacement sensitivity indicates stronger disturbance rejection, while local peaks represent representative frequency bands where structural resonances, actuator dynamics, or control-loop limitations may increase sensitivity to external or internally generated vibration. The comparison emphasizes that wafer support systems used in beam-based processing and metrology should be evaluated not only by static positioning capability, but also by their frequency-dependent response to mechanical disturbance. Magnetically levitated and coarse/fine dual-stage architectures are shown with lower illustrative sensitivity over broad frequency ranges, reflecting their relevance to high-precision lithography, inspection, and metrology environments where scan stability, overlay accuracy, and measurement repeatability are strongly affected by stage dynamics. The curves are intended as literature-informed, normalized comparative envelopes rather than proprietary tool data or predictive simulations of a specific commercial platform.

7. Industrial Architecture Comparison by Tool Class

This section compares industrial design philosophies across major semiconductor tool classes. In lithography, wafer support architectures are inseparable from metrology-integrated motion control, wafer-table design, overlay fidelity, and throughput. In plasma etch, the support platform is centered on electrostatic chuck (ESC) integration, dielectric robustness, plasma-facing thermal management, and contamination suppression. In deposition, support architectures must balance thermal uniformity, chemical compatibility, and particle control. In inspection and metrology, the dominant concerns are vibration isolation, scan stability, charging mitigation, and alignment fidelity. These contrasts are summarized in Tables 10 and 11, while Figure 8 provides a semi-quantitative cross-platform visualization.

7.1. Lithography Platforms

Lithography platforms place the strongest emphasis on precision motion, wafer-table architecture, and metrology-coupled control. ASML systems are distinguished by wafer-stage and metrology integration, where overlay performance and throughput are tightly coupled to support-platform stability. Nikon platforms likewise emphasize high-precision stage control and stable positioning, while Canon may be included for broader historical perspective in optical lithography. The relevant comparison criteria are motion philosophy, stage architecture, metrology integration, and the degree to which the support platform constrains overlay and focus performance.

Table 10. Representative manufacturer comparison across semiconductor tool classes.

Manufacturer	Tool Class	Support Architecture	Beam Environment	Design Priority	Future Direction
ASML	Lithography	Wafer table and precision stage with integrated metrology	EUV/optical lithography	Motion precision, overlay control, and throughput	High-NA compatibility and tighter thermal-drift suppression
Nikon	Lithography	Precision wafer-stage architecture	Optical lithography	Overlay control and stable high-precision positioning	Continued stage refinement and productivity improvement
Tokyo Electron	Etch/plasma processing	ESC- and pedestal-centered support platform	Plasma/ion environment	Plasma compatibility, thermal uniformity, and contamination control	Advanced ESC zoning and tighter thermal management
Lam Research	Etch	ESC-dominant support for conductor and dielectric etch	Plasma etch	Variation control, thermal stability, and scaling compatibility	Support optimization for advanced patterning and process uniformity
Applied Materials	Deposition/etch	Integrated process platform with thermal and support optimization	Plasma and thin-film deposition environments	Uniformity, process integration, and particle control	Greater platform integration and improved support conditioning

Table 11. Cross-platform comparison of wafer support system priorities.

Criterion	Lithography	Etch	Deposition	Inspection
Thermal uniformity priority	Very high	High	High	Moderate–high
Vibration sensitivity	Very high	Moderate	Moderate	Very high
Electrostatic importance	Moderate	Very high	Moderate	Low–moderate
Contamination sensitivity	Very high	Very high	Very high	High
Beam-alignment sensitivity	Very high	Moderate	Moderate	Very high




Figure 8. Illustrative industrial support-architecture priority map for representative semiconductor tool manufacturers. The heat map compares ASML, Nikon, Tokyo Electron, Lam Research, and Applied Materials across normalized design-priority categories relevant to wafer support systems, including motion and overlay control, thermal uniformity, electrostatic chucking behavior, plasma compatibility, contamination control, and future platform integration. The comparison is intended to summarize broad support-architecture tendencies across lithography, etch, deposition, and integrated process platforms. Higher normalized values indicate stronger relative emphasis within the illustrative comparison, not absolute performance ranking. The figure is a literature-informed qualitative synthesis and should not be interpreted as proprietary tool data, product benchmarking, or a predictive simulation of any specific commercial platform.

7.2. Plasma Etch Platforms

In plasma etch, the wafer support platform is centered on ESC functionality and pedestal architecture. Tokyo Electron, Lam Research, and Applied Materials provide useful

comparative cases because their platforms emphasize different balances of plasma compatibility, variation control, thermal uniformity, contamination suppression, and integration with advanced-node process requirements. Here, the support platform acts not only as a mechanical fixture, but also as an electrostatic, thermal, and plasma-facing boundary layer.

7.3. Deposition and Integrated Platform Environments

Deposition platforms impose different constraints on wafer support systems. In PVD, CVD, ALD, and HDP environments, the support architecture must maintain thermal uniformity, chemical compatibility, and minimal particle generation while remaining stable under process cycling. Compared with plasma etch, electrostatic requirements may be less dominant, but thermal and contamination control often become more critical.

7.4. Inspection and Metrology Platforms

Inspection and metrology systems place the strongest emphasis on vibration suppression, scan stability, charging control, and beam-alignment fidelity. X-ray inspection tools require support architectures compatible with high positional stability and low vibration, whereas e-beam inspection adds stringent grounding and charging requirements. Optical metrology systems are similarly sensitive to local flatness, repeatability, and thermomechanical drift.

7.5. Limitations of Cross-Manufacturer Comparisons

The cross-manufacturer comparison presented in this section is based exclusively on publicly available technical literature, patents, product documentation, and published engineering analyses. It should therefore be interpreted as a qualitative comparison of design priorities and architectural tendencies rather than a quantitative ranking of commercial tool performance. Proprietary implementation details, process windows, and internal optimization strategies remain unavailable and are beyond the scope of the present review. No attempt is made to rank commercial tools according to absolute performance. Instead, the comparison focuses on publicly reported architectural priorities, engineering constraints, and support-system design philosophies.

8. Beam-Coupled Metrology and Inspection Enabled or Limited by WSS

The WSS directly conditions the performance envelope of beam-coupled metrology. Optical and computational metrology remain sensitive to support stability even when hard radiation is absent. X-ray inspection and tomography demand vibration suppression, stable scan geometry, and low-background support design. Electron-beam methods require careful grounding and local stability, while THz and hybrid modalities broaden the set of support-induced boundary conditions that may influence detectability. The relationship between metrology modalities and wafer support system sensitivities is summarized in Table 12.

Table 12. Metrology modality versus wafer support system sensitivity.

Metrology Modality	Beam Type	Dominant WSS Sensitivity	Typical Support Bottleneck
Optical/scatterometry	Photons	Wafer flatness, thermal drift, and measurement repeatability	Local support stability, focus sensitivity, and stage-induced alignment error
X-ray imaging/tomography	X-rays	Vibration sensitivity, scan consistency, and background stability	Geometric stability, low-background fixturing, and repeatable scan motion
SEM/CD metrology	Electrons	Charging behavior, grounding quality, and local stage motion	Electrical boundary control, charge dissipation, and fine-stage repeatability
THz/hybrid inspection	THz and hybrid signals	Position stability, signal coupling, and calibration repeatability	Support reproducibility, modality-specific calibration, and alignment stability

9. Materials Platforms for Next-Generation WSS

A forward-looking treatment of next-generation wafer support systems (WSSs) must compare candidate material platforms not only as engineering solids but also as beam-facing thermal, electrostatic, and mechanical boundary conditions. In this context, AlN is attractive when high thermal conductivity and electrical insulation are both required, whereas Al₂O₃ remains important because of its mature processing, strong dielectric behavior, and broad industrial use, despite its lower thermal conductivity. SiC, by contrast, is especially relevant where high stiffness, thermal robustness, and harsh-environment durability are prioritized, although its electrical behavior is more system-dependent and therefore more sensitive to architecture and processing history [38,39,55].

The relevant comparison is therefore not based on any single property, but on the coupled requirements of heat extraction, thermo-mechanical compatibility, dielectric reliability, plasma or beam resistance, contamination control, and manufacturability. This broader view is increasingly important because modern WSS platforms incorporate not only bulk ceramic bodies, but also multilayer architectures, embedded electrodes and heaters, segmented control zones, engineered edges, backside-cooling pathways, and functional surface layers [47,56,57]. From a beam-science perspective, such structural choices influence not only steady-state wafer temperature but also transient thermal relaxation, local electrostatic uniformity, wafer flatness retention, vibration sensitivity, and the stability of beam-coupled metrology.

Coated ceramic systems should also be treated as a distinct design class rather than as a minor surface modification. Recent ESC-related coating studies show that thin ceramic surface layers can be used to tune dielectric behavior, electrical leakage, and interface performance, while plasma-exposure studies on chamber and ceramic-coating materials demonstrate that erosion, fluorination, and surface degradation can become decisive under harsh process conditions [40,51]. These considerations are especially relevant in plasma-exposed WSS environments, where the material must function simultaneously as a structural support, an electrostatic interface, and a thermally active boundary.

Structured supports with embedded channels, segmented zones, engineered edges, and surface-functional layers are therefore especially relevant for advanced lithography, plasma processing, deposition, and beam-based inspection. Publicly available ESC studies on multi-zone ceramic heaters with embedded cooling channels show that temperature-field engineering is now a central design variable rather than a secondary packaging detail [47,56]. Additive manufacturing and architected ceramic ESCs may likewise be discussed as emerging rather than dominant approaches, particularly where geometric freedom enables dielectric tuning, custom electrode layouts, or integrated thermal features that are difficult to realize by conventional co-fired ceramic routes [41,58].

Material qualification under beam and plasma loading should include radiation stability, plasma erosion resistance, thermal cycling durability, particle generation, and the evolution of electrical leakage with repeated use. Framed in this way, materials selection becomes a bridge between conventional ceramic engineering and future beam-aware support design, in which the support is treated as an active physical subsystem that conditions energy dissipation, field uniformity, and metrological reproducibility rather than as a passive fixture. Figure 9 summarizes representative material-property ranges for candidate WSS platforms, highlighting how thermal conductivity, thermal expansion, dielectric behavior, and electrical response vary across AlN, Al₂O₃, SiC, multilayer ceramics, and coated ceramic systems.




Figure 9. Comparison of representative wafer support system (WSS) material-property ranges compiled from publicly available literature. The figure compares literature-informed ranges for thermal conductivity, thermal expansion coefficient, and dielectric constant (used here as a representative electrical metric) across several WSS-relevant material classes, including AlN, Al₂O₃, SiC, multilayer ceramics, and coated ceramic systems. Each property family is shown as a normalized range rather than a single fixed value in order to emphasize that the reported values vary with material purity, porosity, grain structure, dopants, coating composition, interface design, and processing route. Thermal conductivity is included because it governs heat spreading and heat extraction capability within the support stack; thermal expansion coefficient is included because it influences thermally induced dimensional change, wafer distortion, and thermal-stability performance; and dielectric constant is included as a representative electrical parameter relevant to electrostatic support behavior and dielectric design considerations. The figure is intended as a comparative synthesis for cross-material interpretation, not as a claim of universal single-valued properties or as a proprietary product-level benchmark. It is an illustrative, literature-informed summary of the thermal–electrical design space relevant to advanced wafer support systems. A comparative materials matrix for next-generation wafer support systems is presented in Table 13.

Table 13. Materials comparison matrix for next-generation wafer support systems.

Property	AlN	Al ₂ O ₃	SiC	Multilayer Ceramics	Coated Ceramics	Relevance to WSS
Thermal conductivity	High	Moderate	High	Tunable	System-dependent	Heat removal, thermal uniformity, and transient thermal stabilization
Thermal expansion	Moderate	Moderate	Low–moderate	Tunable	System-dependent	Wafer flatness retention, shape control, and thermo-mechanical compatibility
Dielectric robustness	Good	Very good	System-dependent	Good–very good	Coating-dependent	ESC operation, electrical isolation, and field stability
Mechanical stiffness/integrity	Good	Good	Very high	Good	Good	Dimensional stability, vibration response, and structural reliability
Harsh-environment resilience	Good	Good	Strong potential	Good	Strong potential	Plasma and beam compatibility, erosion resistance, and surface durability
Manufacturability	Mature	Very mature	More demanding	More complex	More complex	Scalability, channel or zone integration, and fabrication complexity
Functional integration potential	Good	Good	Moderate	High	High	Embedded heaters, sensors, coatings, segmented zones, and engineered interfaces

10. Advanced Manufacturing and Qualification Routes for Next-Generation WSSs

The next generation of wafer support systems (WSSs) will depend not only on improved control architectures but also on advances in the material platform itself. In beam-facing environments, the support structure must simultaneously satisfy demanding thermal, electrical, mechanical, and contamination-control constraints. This makes material selection a central scientific and engineering problem rather than a secondary implementation choice. Future WSSs are therefore likely to emerge from the combined optimization of advanced ceramics, structured thermal architectures, surface-engineered interfaces, and fabrication routes that permit tighter control over local material function.

10.1. Advanced Ceramics

Advanced ceramics remain the dominant material class for high-performance wafer support applications because they offer a favorable combination of dielectric integrity, thermal robustness, plasma compatibility, and dimensional stability. Among these, aluminum nitride (AlN), alumina (Al₂O₃), and silicon carbide (SiC) represent three particularly important reference platforms.

AlN is especially attractive where high thermal conductivity is required together with electrical insulation, making it highly relevant for electrostatic chucks and temperature-sensitive wafer platforms. Alumina remains widely used because of its maturity, chemical durability, dielectric robustness, and established manufacturability, even though its thermal conductivity is generally lower than that of AlN. SiC-related systems are of interest where harsher thermal or plasma-facing environments are expected, and where stiffness, thermal stability, or compatibility with advanced process environments becomes more important.

Beyond monolithic ceramics, multilayer ceramic systems are increasingly relevant because they permit the integration of electrodes, heaters, sensing layers, and tailored dielectric structures within a single support body. Coated ceramics provide an additional degree of freedom by enabling surface optimization for plasma resistance, electrical behavior, contamination control, or mechanical durability while preserving the bulk advantages of the underlying substrate.

10.2. Structured and Composite Supports

Future WSSs are unlikely to remain simple monolithic supports. Instead, greater emphasis is expected on structured and composite architectures in which geometry and internal layering are used deliberately to control thermal, electrical, and mechanical responses.

Examples include embedded cooling or gas-flow channels, segmented heating zones, engineered wafer-edge regions, and layered support bodies that combine materials with different thermal or dielectric roles. Embedded channels can improve local heat extraction or thermal equalization, while segmented thermal zones allow more active compensation of radial non-uniformity. Engineered edges are particularly important because edge fields, edge heating, and edge particle behavior often dominate practical failure modes in electrostatic chucking and beam-exposed processing. Layered structures, meanwhile, permit the decoupling of bulk stiffness, thermal spreading, electrical insulation, and surface interaction properties.

Such structured supports are especially important for beam-facing platforms because the relevant figure of merit is not merely bulk material quality, but rather the effective transfer of heat, charge, force, and positional disturbance through the entire support architecture.

10.3. Additive Manufacturing and Architected Supports

Additive manufacturing should be treated as an emerging rather than dominant direction, but it has substantial long-term relevance for next-generation WSSs. Printed ceramic supports and architected ceramic-based structures may eventually allow more complex internal geometries than those achievable through conventional subtractive or lamination-based fabrication.

Potential advantages include topology-optimized thermal pathways, internal cooling networks, graded material regions, and the integration of sensing or actuation functions directly into the support body. From a design perspective, additive or architected supports could enable WSSs that are optimized not simply for static strength or manufacturability, but for beam-conditioned performance metrics such as thermal uniformity, field shaping, local stiffness distribution, or vibration suppression.

At present, such approaches remain limited by fabrication precision, porosity control, surface quality, contamination concerns, and the qualification burden associated with semiconductor process environments. Nevertheless, they represent an important future research direction, particularly when combined with digital-twin design methods or reduced-order thermal and mechanical optimization workflows.

10.4. Qualification Under Beam and Plasma Loading

Regardless of the nominal material class, next-generation WSSs must ultimately be qualified under realistic beam and plasma loading conditions. This requires more than reporting bulk material properties. In practice, support materials must maintain function under repeated thermal cycling, electric-field exposure, plasma interaction, and long-duration process operation.

Important qualification dimensions include radiation stability, plasma erosion resistance, thermal-cycle durability, particle-generation behavior, and leakage-current evolution. These factors determine not only lifetime but also whether the support remains a stable boundary condition for beam-based processing and metrology. For example, a material with favorable nominal thermal conductivity may still become unsuitable if repeated cycling changes contact behavior, if plasma exposure roughens the surface, or if leakage evolution alters the electrostatic operating regime.

This also suggests that material qualification should be framed in functional rather than purely compositional terms. The relevant question is not only whether a given ceramic survives, but whether it preserves chucking stability, thermal uniformity, cleanliness, and measurement reproducibility under beam-coupled operating conditions.

Figure 10 summarizes representative ranges of thermal conductivity, coefficient of thermal expansion, dielectric behavior, and electrical resistivity for AlN, Al₂O₃, SiC, multilayer ceramics, and coated ceramic systems [38,39,55,56].

The principal functional trade-offs among candidate wafer support system materials are summarized in Table 14.

Table 14. Materials comparison matrix for next-generation wafer support systems. The table is intended to organize the main functional trade-offs among candidate WSS material classes.

Property	AlN	Al ₂ O ₃	SiC	Multilayer Ceramic	Coated Ceramic
Thermal conductivity	High	Moderate	High	Tunable	Tunable
Electrical insulation	High	High	Variable	Tunable	Surface-dependent
Plasma resistance	Good	Good	Good–high	Design-dependent	Coating-dependent
Thermal expansion control	Moderate	Moderate	Good	Tunable	Substrate-dependent
Mechanical stiffness	Good	Good	High	Design-dependent	Substrate-dependent
Integration of heaters/electrodes	Moderate	Moderate	Limited–moderate	High	Moderate

Table 14. Cont.

Property	AlN	Al ₂ O ₃	SiC	Multilayer Ceramic	Coated Ceramic
Surface engineering flexibility	Moderate	Moderate	Moderate	Moderate	High
Contamination-control potential	Good	Good	Good	Design-dependent	Coating-dependent
Maturity in WSS applications	High	High	Moderate	Moderate	Moderate
Likely limitation	Cost/joining complexity	Lower thermal conductivity	Electrical complexity/processing difficulty	Fabrication complexity	Coating durability/interface reliability




Figure 10. Representative material-property comparison for candidate wafer support system (WSS) material platforms. The grouped bars compare normalized thermal conductivity, thermal expansion coefficient, dielectric constant, and electrical resistivity for AlN, Al₂O₃, SiC, multilayer ceramics, and coated ceramic systems. Each property family is normalized separately to allow comparison on a common vertical scale, while electrical resistivity is log-normalized because it can span several orders of magnitude depending on composition, dopants, porosity, coating condition, and processing route. Thermal conductivity is included because it controls heat spreading and heat extraction through the support stack; thermal expansion coefficient is included because it affects wafer flatness, dimensional stability, and thermo-mechanical compatibility; dielectric constant and electrical resistivity are included because they influence electrostatic chucking behavior, leakage evolution, field stability, and electrical isolation. The figure is intended as an illustrative, literature-informed synthesis for comparing material design trade-offs, not as a proprietary product benchmark or a predictive simulation of a specific commercial WSS platform.

11. Emerging Trends and Future Outlook

The most important future directions are likely to include high-NA EUV, full-wafer and buried-structure X-ray inspection, smart support systems with embedded sensing, and beam-aware control architectures. High-NA systems tighten tolerances on motion error, thermal distortion, wafer-shape control, and support-induced overlay drift. As X-ray methods become more relevant to semiconductor and advanced-packaging inspection, WSSs must increasingly satisfy low-background, high-stability, and scan-compatible requirements.

Future smart wafer supports may incorporate temperature sensors, field sensors, vibration sensing, adaptive chuck zoning, and digital-twin-assisted correction. Within QuBS, this opens research opportunities in beam-aware support metrics, timescale-based optimization,

support-conditioned detectability limits, and a unified beam–support transfer-function language bridging synchrotron-style instrumentation thinking with semiconductor-tool engineering.

The next phase of wafer support system (WSS) development will be shaped by the simultaneous tightening of lithographic overlay budgets, the expansion of buried-structure inspection, and the growing importance of adaptive, sensor-rich support platforms. In this regime, the WSS should no longer be viewed merely as passive fixtures or process enablers, but as a beam-aware infrastructure that co-determines thermal stability, positioning fidelity, charging behavior, and metrological detectability. Emerging trends therefore point toward support architectures that are increasingly integrated with sensing, model-based control, and data-driven optimization.

11.1. High-NA EUV

High-NA EUV lithography is expected to sharpen the performance requirements imposed on wafer support systems because improvements in optical resolution must be matched by corresponding reductions in support-mediated error. As numerical aperture increases, tolerances on motion error, thermal distortion, wafer-shape variation, and support-induced drift become more stringent, since any instability at the wafer support boundary can couple directly into focus, critical-dimension control, and overlay performance. In practice, this implies that future support platforms for high-NA systems will require tighter thermal field control, reduced dynamic compliance, improved wafer-flatness management, and closer integration with stage-level feedback and metrology subsystems. The WSS therefore becomes part of the effective optical-performance budget rather than an external mechanical accessory.

From a beam-science perspective, high-NA EUV also raises a broader systems question: the beam, wafer, support, and stage can no longer be treated as weakly coupled subsystems. Instead, they form a tightly coupled multiscale platform in which thermal expansion, transient dose deposition, actuator dynamics, and local support conditions interact over overlapping time and length scales. This motivates a shift from static support qualification toward dynamic beam-aware support design, particularly for architectures in which support-induced thermal and mechanical perturbations can accumulate over repeated scan fields.

11.2. Full-Wafer and Buried-Structure X-Ray Inspection

A second major trend is the increasing relevance of full-wafer and buried-structure X-ray inspection for semiconductor manufacturing and advanced packaging. As device stacks become more three-dimensional and defect modes migrate below optically accessible surfaces, X-ray-based methods gain strategic importance because they can probe hidden interfaces, internal voids, buried interconnect structures, and package-level heterogeneities. For WSSs, this shift has important consequences: support platforms used in X-ray inspection must preserve scan stability, maintain thermal consistency over long acquisition windows, minimize parasitic background contributions, and provide precision positioning compatible with high-resolution imaging or tomographic reconstruction.

These requirements differ in emphasis from those in plasma processing or conventional lithography. In X-ray inspection, line-of-sight stability and low-background support behavior become particularly important, and the support system must avoid introducing unnecessary absorption, scattering, drift, or mechanical noise. This is especially relevant for coherent imaging, ptychographic reconstruction, and advanced packaging inspection, where the quality of reconstructed information can be limited as much by support-induced instability as by source or detector performance. In this sense, next-generation

X-ray-compatible WSSs may increasingly resemble metrology platforms rather than purely process-driven supports.

11.3. Smart Wafer Supports

Future WSSs are likely to evolve toward smart, instrumented platforms that integrate sensing and adaptive control directly into the support architecture. Candidate functionalities include embedded temperature sensors, electric-field sensing, vibration sensing, adaptive zoning for local thermal or electrostatic correction, and digital-twin frameworks for real-time state estimation. Such developments would allow the support platform to respond actively to beam-induced perturbations rather than merely tolerating them.

This transition is important because beam-facing support performance is fundamentally state-dependent. Local contact conditions, charging history, thermal gradients, wafer bow, and stage-induced disturbances may all evolve during operation. A smart WSS could, in principle, monitor these variables continuously and apply corrective actions through multi-zone heating, electrostatic tuning, vibration compensation, or model-based control. For advanced semiconductor tools, this would move the support from a static hardware component toward a closed-loop cyber-physical subsystem. The most promising near-term path is likely to be the combination of embedded sensing with reduced-order models and digital-twin approaches that translate measured support states into actionable control updates.

11.4. Research Opportunities

These trends create several research opportunities that are especially appropriate for Quantum Beam Science. First, there is a clear need for beam-aware support metrics that quantify support suitability in terms more directly relevant to beam-based observables, such as drift-limited detectability, support-mediated signal distortion, thermal-noise contribution, or vibration-conditioned image blur. Second, timescale-based support optimization offers a promising framework for comparing beam excitation, thermal relaxation, mechanical response, and control-system correction within a unified hierarchy, thereby allowing support architectures to be evaluated in relation to the temporal structure of the beam environment.

Third, future work should establish detectability limits conditioned by support dynamics, especially for weak or buried signals where support-induced instability may dominate the effective measurement floor. Fourth, the development of a beam–support transfer-function language could provide a unifying formalism linking support dynamics, beam perturbation, and metrological response across lithography, inspection, and hybrid beam platforms. Finally, substantial value may come from cross-fertilization between synchrotron instrumentation and semiconductor equipment engineering: methods developed for high-stability beamline positioning, thermal drift correction, and coherent imaging may inform future fab-compatible WSSs, while semiconductor stage and chuck innovations may in turn benefit compact beam-based inspection systems.

Taken together, these directions suggest that WSS research is entering a stage in which mechanical engineering, thermal science, electrostatics, beam instrumentation, and data-centric manufacturing can no longer be treated independently. A rich QuBS contribution can therefore position wafer support systems as an emerging research frontier at the intersection of quantum beam interaction, precision platform engineering, and intelligent semiconductor infrastructure.

11.5. Practical Challenges for Smart WSS Deployment

Despite their potential advantages, smart wafer support systems face several implementation challenges. Embedded sensors must operate under vacuum, plasma, and high-

temperature conditions while maintaining electrical isolation and measurement fidelity. Additively manufactured ceramic structures may contain residual porosity, microstructural variability, and interface-strength limitations that affect long-term reliability. Digital-twin-based control strategies must also address computational latency, real-time data management, and model-maintenance requirements before large-scale industrial deployment becomes practical. Particular challenges arise in sensor packaging because embedded sensing elements must survive high temperatures, plasma exposure, vacuum operation, and radio-frequency electromagnetic environments while maintaining calibration accuracy. Similarly, additively manufactured ceramic structures may contain residual porosity and microstructural heterogeneity that influence dielectric reliability and thermal transport. Digital-twin frameworks face an additional challenge associated with real-time computational latency, where data acquisition, model updating, and control-action implementation must occur rapidly enough to influence ongoing processing conditions. Figure 11 summarizes the convergence of several emerging WSS trends, including embedded sensing, adaptive thermal management, data-driven optimization, and digital-twin-assisted control. The figure highlights how future support architectures may evolve from passive support structures toward actively monitored and continuously optimized beam-facing platforms. Importantly, the enabling technologies are not independent; sensing, predictive modeling, and adaptive control are expected to operate as a coupled system. Future progress will depend increasingly on quantitative benchmarking methodologies capable of linking beam response, support-system architecture, and metrology performance through common performance metrics.

Future research directions and enabling methods for next-generation wafer support systems are summarized in Table 15.

Table 15. Future research directions and enabling methods for next-generation wafer support systems.

Research Direction	Physical Driver	Enabling Data	Computational Tool	Likely Industrial Impact
Beam-aware support metrics	Beam-induced drift, charging, and thermal perturbation	Public metrology, thermal, and stage-stability data	Python or Matlab comparison scripts	More rational benchmarking of WSS architectures
Timescale-based support optimization	Mismatch among excitation, thermal diffusion, mechanical settling, and control response	Literature-derived characteristic timescale ranges	Log-scale timescale maps and reduced-order models	Better support design for specific beam regimes
Drift-conditioned detectability limits	Weak buried signals, low-contrast defects, and measurement instability	Inspection, imaging, and scan-stability data	Reduced-order error-propagation models	Improved inspection confidence and yield learning
Beam-support transfer-function framework	Coupled thermal, mechanical, and electrostatic response	Multiphysics literature data and simplified support-response measurements	Python or Matlab transfer-function modeling	Unified design language across lithography, etch, deposition, and metrology tools
Smart sensorized supports	Dynamic variation in thermal, electrical, and mechanical operating state	Embedded sensor streams, support telemetry, and metrology feedback	Digital twins, state estimators, and adaptive-control algorithms	Closed-loop correction, adaptive support control, and improved process repeatability

Figure 11 summarizes the proposed smart wafer support system architecture integrating sensing, adaptive control, and beam-aware support functions.




Figure 11. Future smart beam-aware wafer support system (WSS) concept. The schematic illustrates a next-generation wafer support platform in which the support body is treated as an active sensing, actuation, and feedback subsystem rather than a passive mechanical fixture. The central cross-section shows a wafer supported by a multilayer WSS architecture containing distributed thermal sensors, electric-field monitoring electrodes, adaptive heating/cooling zones, vibration sensors, coolant or gas channels, and structural support layers. Beam modules, including EUV/X-ray, electron-beam, ion/plasma, and laser/optical sources, are coupled to the wafer from above, while a metrology module provides feedback through interferometry, thermal imaging, electric-field or potential mapping, vibration analysis, and particle or deposition monitoring. These measurements are linked to a digital-twin and control layer that combines physics-based models, data fusion, artificial intelligence, optimization, and process setpoint generation. The closed-loop control pathway enables adaptive thermal control, electrical bias adjustment, zonal actuation, vibration damping, and beam or scan-dose adaptation. The figure is intended as a conceptual outlook schematic showing how future WSS platforms may integrate materials engineering, embedded sensing, electrostatic control, thermal management, metrology feedback, and digital-twin optimization into a beam-aware support architecture.

Author Contributions: Conceptualization, A.A.; methodology, A.A.; formal analysis, A.A. and J.A.; investigation, A.A. and J.A.; resources, A.A.; data curation, A.A.; writing—original draft preparation, A.A.; writing—review and editing, A.A., J.A. and M.A.H.; visualization, A.A.; supervision, A.A.; project administration, A.A. All authors have read and agreed to the published version of the manuscript.

Funding: This research received no external funding. The article processing charge (APC) was waived as this work was an invited contribution.

Institutional Review Board Statement: Not applicable.

Informed Consent Statement: Not applicable.

Data Availability Statement: No new experimental dataset is reported in this review. The data used for the quantitative comparison figures were compiled from publicly available literature, technical documentation, proceedings, open patents, and material-property databases.

Acknowledgments: The schematic figures were generated with the assistance of OpenAI DALL-E 3 (OpenAI, San Francisco, CA, USA) for visualization purposes only. No AI tools were used in the development of the scientific content, analysis, or conclusions.

Conflicts of Interest: The authors declare no conflicts of interest.

Abbreviations

WSS	wafer support system
ESC	electrostatic chuck
EUV	extreme ultraviolet
CD	critical dimension
CTE	coefficient of thermal expansion
THz	terahertz

References

1. Als-Nielsen, J.; McMorrow, D. *Elements of Modern X-Ray Physics*, 2nd ed.; Wiley: Chichester, UK, 2011.
2. Attwood, D.; Sakdinawat, A. *X-Rays and Extreme Ultraviolet Radiation: Principles and Applications*, 2nd ed.; Cambridge University Press: Cambridge, UK, 2017.
3. Campbell, S.A. *Fabrication Engineering at the Micro- and Nanoscale*, 4th ed.; Oxford University Press: Oxford, UK, 2013.
4. Wolf, S.; Tauber, R.N. Silicon Processing for the VLSI Era. In *Process Technology*; Lattice Press: Sunset Beach, CA, USA, 2000; Volume 1.
5. May, G.S.; Spanos, C.J. *Fundamentals of Semiconductor Manufacturing and Process Control*; Wiley: Hoboken, NJ, USA, 2006.
6. ASML. “Mechanics and Mechatronics/Wafer Stage” Technical Overview. Available online: <https://www.asml.com/technology/lithography-principles/mechanics-and-mechatronics> (accessed on 1 May 2026).
7. Tokyo Electron. “Tactras™ Plasma Etch System” Product and Platform Overview. Available online: <https://www.tel.com/product/tactras.html> (accessed on 1 May 2026).
8. Lam Research. “Kiyo® Product Family” Product and Platform Overview. Available online: <https://www.lamresearch.com/product/kiyo-product-family/> (accessed on 1 May 2026).
9. Applied Materials. “Centura Ultima HDP-CVD” Product and Platform Overview. Available online: <https://www.appliedmaterials.com/us/en/product-library/centura-ultima-hdp-cvd.html> (accessed on 1 May 2026).
10. Abe, H.; Yoneda, M.; Fujiwara, N. Developments of plasma etching technology for fabricating semiconductor devices. *Jpn. J. Appl. Phys.* **2008**, *47*, 1435–1455. [CrossRef]
11. Butler, H. Position control in lithographic equipment: An enabler for current-day chip manufacturing. *IEEE Control Syst. Mag.* **2011**, *31*, 28–47. [CrossRef]
12. Wright, D.R.; Chen, L.; Federlin, P.; Forbes, K. Manufacturing issues of electrostatic chucks. *J. Vac. Sci. Technol. B* **1995**, *13*, 1910–1916. [CrossRef]
13. Kalkowski, G.; Risse, S.; Harnisch, G.; Guyenot, V. Electrostatic chucks for lithography applications. *Microelectron. Eng.* **2001**, *57–58*, 219–222. [CrossRef]
14. Shim, G.I.; Sugai, H. Dechuck operation of Coulomb type and Johnsen–Rahbek type of electrostatic chuck used in plasma processing. *Plasma Fusion Res.* **2008**, *3*, 051. [CrossRef]
15. Cahill, D.G.; Ford, W.K.; Goodson, K.E.; Mahan, G.D.; Majumdar, A.; Maris, H.J.; Merlin, R.; Phillpot, S.R. Nanoscale thermal transport. *J. Appl. Phys.* **2003**, *93*, 793–818. [CrossRef]
16. Chen, G. *Nanoscale Energy Transport and Conversion: A Parallel Treatment of Electrons, Molecules, Phonons, and Photons*; Oxford University Press: Oxford, UK, 2005.
17. Majumdar, A. Microscale heat conduction in dielectric thin films. *J. Heat Transf.* **1993**, *115*, 7–16. [CrossRef]
18. Alshehaby, A. Time-Scale Mismatch as a Fundamental Constraint in Quantum Beam–Matter Interactions. *Quantum Beam Sci.* **2026**, *10*, 10. [CrossRef]
19. Alshehaby, A. Why Identical Samples Yield Different X-Ray Spectra: A Time-Scale and Signal-Formation Perspective. *X-Ray Spectrom.* **2026**, *early view*. [CrossRef]
20. Steinbuch, M.; Norg, M.L. Advanced motion control: An industrial perspective. *Eur. J. Control* **1998**, *4*, 278–293. [CrossRef]
21. Chapman, H.N.; Barty, A.; Bogan, M.J.; Boutet, S.; Frank, M.; Hau-Riege, S.P.; Marchesini, S.; Woods, B.W.; Bajt, S.; Benner, W.H.; et al. Femtosecond diffractive imaging with a soft-X-ray free-electron laser. *Nat. Phys.* **2006**, *2*, 839–843. [CrossRef]
22. Thibault, P.; Dierolf, M.; Menzel, A.; Bunk, O.; David, C.; Pfeiffer, F. High-resolution scanning X-ray diffraction microscopy. *Science* **2008**, *321*, 379–382. [CrossRef] [PubMed]

23. Postek, M.T.; Vladár, A.E. Critical-dimension metrology and the scanning electron microscope. In *Handbook of Silicon Semiconductor Metrology*; CRC Press: Boca Raton, FL, USA, 2001; pp. 244–275.
24. Villarrubia, J.S.; Vladar, A.E.; Postek, M.T. Scanning electron microscope dimensional metrology using a model-based library. *Surf. Interface Anal.* **2005**, *37*, 951–958. [[CrossRef](#)]
25. Wagner, A.; Harned, N. EUV lithography: Lithography gets extreme. *Nat. Photonics* **2010**, *4*, 24–26. [[CrossRef](#)]
26. ASML. “EUV Lithography Systems,” Product and Technical Overview. Available online: <https://www.asml.com/products/euv-lithography-systems> (accessed on 1 May 2026).
27. Henke, B.L.; Gullikson, E.M.; Davis, J.C. X-ray interactions: Photoabsorption, scattering, transmission, and reflection at $E = 50\text{--}301,1000$ eV, $Z = 1\text{--}92$. *Data Nucl. Data Tables* **1993**, *54*, 181–342. [[CrossRef](#)]
28. Shapiro, D.A.; Yu, Y.-S.; Tyliczszak, T.; Cabana, J.; Celestre, R.; Chao, W.; Kaznatcheev, K.; Kilcoyne, A.D.; Maia, F.; Marchesini, S.; Meng, Y.S. Chemical composition mapping with nanometre resolution by soft X-ray microscopy. *Nat. Photonics* **2014**, *8*, 765–769. [[CrossRef](#)]
29. Egerton, R.F. *Electron Energy-Loss Spectroscopy in the Electron Microscope*, 3rd ed.; Springer: New York, NY, USA, 2011.
30. Hüfner, S. *Photoelectron Spectroscopy: Principles and Applications*, 3rd ed.; Springer: Berlin/Heidelberg, Germany, 2003.
31. Postek, M.T. Critical issues in scanning electron microscope metrology. *J. Res. Natl. Inst. Stand. Technol.* **1994**, *99*, 641–671. [[CrossRef](#)] [[PubMed](#)]
32. Postek, M.T.; Joy, D.C. Submicrometer microelectronics dimensional metrology: Scanning electron microscopy. *J. Res. Natl. Bur. Stand.* **1987**, *92*, 205–228. [[CrossRef](#)]
33. Shim, G.I.; Yamauchi, T.; Sugai, H. Plasma effects on electrostatic chuck characteristics on capacitive RF discharge. *Plasma Fusion Res.* **2007**, *2*, 044. [[CrossRef](#)]
34. Sogard, M.R.; Mikkelsen, A.R.; Nataraju, M.; Turner, K.T.; Engelstad, R.L. Analysis of Coulomb and Johnsen–Rahbek electrostatic chuck performance for extreme ultraviolet lithography. *J. Vac. Sci. Technol. B* **2007**, *25*, 2155–2161. [[CrossRef](#)]
35. Saiki, K.; Hara, A.; Sakata, K.; Fujimoto, H. A study on high-speed and high-precision tracking control of large-scale stage using perfect tracking control method based on multirate feedforward control. *IEEE Trans. Ind. Electron.* **2010**, *57*, 1393–1400. [[CrossRef](#)]
36. Van Brussel, H.; Reynaerts, D.; Vanherck, P.; Versteyhe, M.; Devos, S. A nanometre-precision, ultra-stiff piezostepper stage for ELID-grinding. *CIRP Ann. Manuf. Technol.* **2003**, *52*, 317–322. [[CrossRef](#)]
37. Neugebauer, R.; Denkena, B.; Wegener, K. Mechatronic systems for machine tools. *CIRP Ann. Manuf. Technol.* **2007**, *56*, 657–686. [[CrossRef](#)]
38. Choi, H.S.; Im, H.N.; Kim, Y.M.; Chavan, A.; Song, S.J. Structural, thermal and mechanical properties of aluminum nitride ceramics with CeO_2 as a sintering aid. *Ceram. Int.* **2016**, *42*, 11519–11524. [[CrossRef](#)]
39. Yang, F.; Chen, Y.; Hai, W.; Yan, S.; Cao, T.; Yuan, Z.; Huang, Z.; Huang, Q.; Li, Y. Research progress on high-thermal-conductivity silicon carbide ceramics. *Ceram. Int.* **2025**, *51*, 4095–4109. [[CrossRef](#)]
40. Park, S.H.; Kim, K.E.; Hong, S.J. Surface analysis of chamber coating materials exposed to CF. *Coatings* **2021**, *11*, 105. [[CrossRef](#)]
41. Kim, M.; Lim, J.; Park, J.-H.; Yoon, S.; Kim, J. Additive manufacturing of electrostatic chucks with tunable ceramic-polymer dielectrics: A combined experimental and FEA approach. *Compos. Commun.* **2026**, *62*, 102727. [[CrossRef](#)]
42. Hu, S.M. Stress-related problems in silicon technology. *J. Appl. Phys.* **1991**, *70*, R53–R80. [[CrossRef](#)]
43. Fujimoto, H.; Hori, Y.; Kawamura, A. Perfect tracking control based on multirate feedforward control with generalized sampling periods. *IEEE Trans. Ind. Electron.* **2001**, *48*, 636–644. [[CrossRef](#)]
44. Watanabe, T.; Kitabayashi, T.; Nakayama, C. Electrostatic force and absorption current of alumina electrostatic chuck. *Jpn. J. Appl. Phys.* **1992**, *31*, 2145–2150. [[CrossRef](#)]
45. Watanabe, T.; Kitabayashi, T.; Nakayama, C. Relationship between electrical resistivity and electrostatic force of alumina electrostatic chuck. *Jpn. J. Appl. Phys.* **1993**, *32*, 864–871. [[CrossRef](#)]
46. Watanabe, T.; Kitabayashi, T.; Nakayama, C. Electrostatic charge distribution in the dielectric layer of alumina electrostatic chuck. *J. Mater. Sci.* **1994**, *29*, 3510–3516. [[CrossRef](#)]
47. Jang, K.H.; Lee, H.J.; Lee, S.H. Evaluation of surface temperature uniformity of multi-zone ceramic heaters with embedded cooling channels for electrostatic chuck. *J. Mech. Sci. Technol.* **2022**, *36*, 1599–1606. [[CrossRef](#)]
48. Yoon, T.W.; Cho, S.I.; Choi, M.; Hong, S.J. Heat transfer mechanism of electrostatic chuck surface and wafer backside to improve wafer temperature uniformity. *J. Vac. Sci. Technol. B* **2023**, *41*, 044002. [[CrossRef](#)]
49. Stamper, A.K.; Lasky, J.B.; Adkisson, J.W. Plasma-induced gate-oxide charging issues for sub-0.5 μm complementary metal–oxide–semiconductor technologies. *J. Vac. Sci. Technol. A* **1995**, *13*, 905–911. [[CrossRef](#)]
50. Luo, Q.; Li, C.-H.; Zhou, N.-Y.; Hu, L.; Pang, Y.; Zou, Y. Electrical properties, microstructure, and thermal conductivity of hot-pressed CaO -doped AlN ceramics. *Ceram. Int.* **2024**, *50*, 37919–37931. [[CrossRef](#)]
51. Lim, J.; Kim, D.; Lee, N.H.; Kim, Y.G.; Yu, H.K.; Choi, J.Y.; Park, J.H. Optimizing electrostatic chuck performance through $\text{ZrO}_2/\text{Al}_2\text{O}_3$ ratio and doping components (SiO_2 and Y_2O_3). *Ceram. Int.* **2025**, *51*, 11432–11436. [[CrossRef](#)]

52. Rossnagel, S.M.; Cuomo, J.J.; Westwood, W.D. (Eds.) *Handbook of Plasma Processing Technology: Fundamentals, Etching, Deposition, and Surface Interactions*; Noyes Publications: Park Ridge, NJ, USA, 1990.
53. Rossnagel, S.M.; Hopwood, J. Metal ion deposition from ionized magnetron sputtering discharge. *J. Vac. Sci. Technol. B* **1994**, *12*, 449–453. [[CrossRef](#)]
54. Meiling, H.; Meijer, H.; Banine, V.; Moors, R.; Groeneveld, R.; Voorma, H.J.; Micken, U.; Wolschrijn, B.; Mertens, B.; van Baars, G.; et al. First performance results of the ASML alpha demo tool. *Emerg. Lithogr. Technol. X* **2006**, *6151*, 49–60. [[CrossRef](#)]
55. Hlina, J.; Reboun, J.; Janda, M. Investigation of cooling capability of ceramic substrates for power electronics applications. *Appl. Therm. Eng.* **2024**, *247*, 123110. [[CrossRef](#)]
56. Liu, C.; Gao, J.; He, Z.; Han, K.; Yang, Z.; Xu, K.; Zhuang, S. Mechanisms underlying temperature uniformity in electrostatic chucks through experimental and simulation methods. *Appl. Therm. Eng.* **2024**, *238*, 122011. [[CrossRef](#)]
57. Nakajima, S.; Benjamin, N. Class H10P72/72: Ceramic Electrostatic Chuck and Its Use. European Patent EP1399964B1, 24 February 2010.
58. Kim, Y.; Park, J.H.; Lim, J.; Yoon, S.; Kim, J. Material-specific three-dimensional printing of electrostatic chuck components via digital light processing: Integration of Al₂O₃- and BaTiO₃-based composites as dual materials for performance optimization. *Adv. Compos. Hybrid Mater.* **2026**, *9*, 171. [[CrossRef](#)]

Disclaimer/Publisher’s Note: The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of MDPI and/or the editor(s). MDPI and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.