

Article



Comparative Cradle-to-Grave Life Cycle Assessment of Low and Mid-Rise Mass Timber Buildings with Equivalent Structural Steel Alternatives

Kevin Allan * D and Adam R. Phillips D

Department of Civil and Environmental Engineering, Washington State University, Pullman, WA 99164, USA; a.phillips@wsu.edu

* Correspondence: kevin.allan@wsu.edu

Abstract: The objective of this paper was to quantify and compare the environmental impacts associated with alternative designs of typical North American low and mid-rise buildings. Two scenarios were considered: a traditional structural steel frame or an all-wood mass timber design, utilizing engineered wood products for both gravity and lateral load resistance. The boundary of the quantitative analysis was cradle-to-grave with considerations taken to discuss end-of-life and material reuse scenarios. The TRACI methodology was followed to conduct a Life Cycle Impact Assessment (LCIA) analysis that translates building quantities to environmental impact indicators using the Athena Impact Estimator for Buildings Life Cycle analysis software tool and Athena's Life Cycle Inventory database. The results of the analysis show that mass timber buildings have an advantage with respect to several environmental impact categories, including eutrophication potential, human health particulate, and global warming potential carbon sequestration benefits from the timber products. However, it was also found that the steel buildings have a lower impact with respect to the environmental impact categories of smog potential, acidification potential, and ozone depletion potential, where a 48% to 58% reduction was found from the steel to the mass timber building designs.

Keywords: cross-laminated timber; steel; sustainability; life cycle assessment; LCIA

1. Introduction

The building sector is one of the major contributors to global climate change, producing approximately 33–39% of all global greenhouse gas emissions [1,2]. Due to the high percentage of global emissions stemming from the building sector and the ever-growing demand for residential and commercial buildings, much research has been conducted to investigate the environmental impacts of different building materials. Investigating the energy consumption and emissions of buildings throughout their useful life is completed using the life-cycle assessment (LCA) method [3]. A life-cycle assessment can greatly help in increasing the sustainability of a building project by providing information on how different materials, or processes, contribute to the overall environmental impact of the building. Life-cycle energy consumption can be split broadly into two categories of embodied energy and operational energy. The embodied energy is the energy consumed during the building's production [4]. Operational energy is the energy used to fulfill the building's function.

The operational phase is often greater than the building production phase over long time periods. In a study conducted by Kahhat et al. (2009), it was found that the energy consumed during the use phase of residential buildings would frequently exceed the total energy consumed during construction after 3–4 years of operation [5]. Iyer–Raniga and Wong (2012) investigated the environmental impact of eight heritage buildings in Australia and the use phase was found to consume more than 10 times the energy consumed during



Citation: Allan, K.; Phillips, A.R. Comparative Cradle-to-Grave Life Cycle Assessment of Low and Mid-Rise Mass Timber Buildings with Equivalent Structural Steel Alternatives. *Sustainability* **2021**, *13*, 3401. https://doi.org/10.3390/ su13063401

Academic Editor: Asterios Bakolas

Received: 29 January 2021 Accepted: 15 March 2021 Published: 19 March 2021

Publisher's Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



Copyright: © 2021 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (https:// creativecommons.org/licenses/by/ 4.0/). the building production phase [6]. A study conducted by Ochoa et al. (2002) similarly concluded that the use phase was the largest contributor to life-cycle environmental impact through analysis of residential buildings in the United States [7]. Decades of research have aimed to reduce operational energy use, which has resulted in significant increases in the efficiency of building systems. As the operational energy part of building life-cycle energy becomes more efficient, the importance of the emissions associated with the embodied energy part, such as material production, transportation, construction, and end-of-life, become more important. Several studies conducted more recently, over the last decade, indicate that embodied energy can account for a large portion of total life-cycle emissions. Ramesh et al. (2010) found that 10–20% of the total energy consumed can be embodied from pre-use stages [8]. In a study completed by Hafner (2014), it was determined that 20–55% of total CO₂ emissions came from embodied carbon in the building materials [9]. These previous studies also show that the embodied emissions of buildings are highly influenced by the selection of construction materials and the design choices made.

In the United States, low-rise buildings are commonly constructed using light-gage framing, either wood or cold-formed steel, and mid-rise buildings are traditionally constructed using reinforced concrete and steel. However, the advancements in production and understanding of mass timber in North America coupled with the drive for more sustainable construction, has increased the desire to utilize engineered wood products in both low-rise and mid-rise buildings [10,11]. Numerous studies, including those conducted on timber buildings compared to reinforced concrete and steel buildings, have consistently demonstrated that timber materials have benefits in reducing global emissions. A group of studies are reviewed here that are most relevant to the study described and presented in this paper and to provide context for the results reported in Section 3. Robertson et al. (2012) found that timber structures offer a lower environmental impact in 10 out of 11 assessment categories when compared to reinforced concrete buildings in a cradle-to-gate study [12]. Pierobon et al. (2019) conducted a cradle-to-gate study of a hybrid mass timber and reinforced concrete alternative compared to a traditional all-concrete design and determined that the hybrid structure had an average of a 26.5% reduction in global warming potential [11]. Gustavsson et al. (2010) investigated two archetype buildings and found that a concrete alternative embodied 129 kg C/m^2 compared to a wood alternative, which embodied 57 kg C/m^2 when coal was considered as a fossil fuel [13]. Guggemos and Horvath (2005) found that timber framed buildings have lower CO_2 emissions when compared to steel and concrete buildings [14]. Most of the previous work focuses on comparing timber buildings to reinforced concrete structures using a cradle-to-gate analysis boundary. Few studies have compared the environmental impact of mass timber buildings to traditional steel framed buildings from cradle to grave.

Peterson and Solberg (2002) is one of the early studies that compared mass timber to steel, using a cradle-to-gate analysis on the effect of substituting glue-laminated timber in place of steel for the main roof beams of Gardermoen airport in Norway. Peterson and Solberg (2002) found that use of glulam beams would save 0.24-0.31 tons of CO₂ equivalents per m³ of sawn wood used in the glulam production over steel [15]. However, the Peterson and Solberg (2002) study may not be directly applicable to full buildings located in the United States, where steel production is considerably cleaner in than other parts of the world, as noted by Pomponi and Moncaster (2018) [16]. A detailed cradle-tograve LCA analysis of three steel buildings located in China was more recently conducted by Su and Zhang (2016). One of the findings was that there were no significant correlations between the total area of a steel building and the embodied energy of the building (Su and Zhang, 2016). However, as the building height increased so did the embodied energy emissions per unit area, suggesting that as height increased, so too did the relative environmental burden [4]. The Su and Zhang (2016) study may also not be directly applicable to steel buildings in the United States, where again steel production relies more heavily on recycled scrap steel and lower-emission electric arc furnaces.

There is a lack of research on the environmental impact of steel buildings built in the United States, using North American steel production quantities and average rates of recycling. Further, with the drive towards lower-carbon building construction and the increasing use of mass timber as a building material, there is a lack of understanding in how North American steel buildings would compare to all-wood mass timber alternatives at different building heights. To rectify these gaps in knowledge, this paper aims to increase the understanding of the environmental impacts of all-wood, mass timber buildings compared to a conventionally framed structural steel alternatives from cradle to grave. The LCA method was applied to two archetype buildings, both located in Seattle, Washington, with heights of 5-stories and 12-stories using the Athena Impact Estimator for Buildings (IE4B).

2. Materials and Methods

The two 5-story buildings were designed to represent a typical low-rise office building, while the two 12-story buildings were designed as a typical mid-rise residential building. Each pair of buildings were identical in footprint, floor-to-floor heights, total height, and general floor plan layout but were designed following the practical conventions for each structural material. The study results compare the environmental emission impacts of each building using six impact categories of the TRACI protocol. Analysis is conducted with respect to the overall emissions of each building for each environmental category, as well as with respect to the building components and life-cycle stage.

2.1. Low-Rise and Mid-Rise Archetype Buildings

The 5-story and 12-story mass timber buildings were adopted from Wilson et al. (2020a), which investigated the seismic performance the all-wood mass timber buildings using self-centering, cross laminated timber (CLT) shear walls [17]. While several structural systems have been proposed at a conceptual level for mass timber buildings (i.e., Green and Karsh, 2012, [18]; SOM, 2017, [19]) only a few have been tested experimentally to determine their suitability for seismic applications that are prevalent in the west coast of the United States. Self-centering mass timber walls are one of the promising systems that have been experimentally and computationally investigated [20,21] and are especially desirable due to their resiliency, or ability to return to service after an earthquake with low damage [22]. Further, self-centering mass timber walls are an all-wood system that does not rely on usage of reinforced concrete for lateral stability, therefore reducing the total volume of concrete and reinforcing steel needed for the building.

The original mass timber buildings were designed for the seismic and wind loads of an arbitrary site in Seattle, Washington. The floor plans of the 5-story and 12-story buildings are shown in Figures 1 and 2, respectively. The gravity load system of both mass timber buildings is glue-laminated timber beams and columns with 5-ply (175 mm) CLT floors. Both mass timber buildings used an additional 51 mm of light-weight concrete topping slab on the CLT floors to satisfy fire, diaphragm, and serviceability vibration requirements. It should be noted that some practitioners hold the perception that thinner (105 mm–140 mm) CLT floor panels with closer spaced beams are preferable over 5-ply CLT floor panels to reduce costs. For the lateral force resisting system, the mass timber buildings used 9-ply (315 mm) CLT post-tensioned rocking walls, as described by Wilson (2018).

The buildings were then redesigned in this study using steel with the intent of maintaining functionally equivalent structures but using design decisions that would be representative of conventional steel design. Following Wilson (2018), the buildings were designed using the loads shown in Table 1 [23]. As shown by Figures 1 and 2, the column spacing and location of lateral force resisting systems did change significantly between the mass timber and steel buildings. Specifically, due to the higher stiffness and strength of steel compared to timber, the column spacing was able to be increased and fewer columns were used. Additionally, fewer lateral force resisting frames were needed for the steel building compared to the mass timber buildings.



Figure 1. 5-Story building framing plans: mass timber building (Left), steel building (Right).



Figure 2. 12-Story building framing plans: mass timber building (Left), steel building (Right).

		5 Story	12 Story
Building Use		Office	Residential
Footprint ($m \times m$)		27.4 imes 51.2	26.8 imes 65.8
Total Area (m ²)		7014.4	21,161.3
Total Height (m)		19.8	45.7
Dead loads	Roof—MEP/Misc.	0.48 kPa	0.96 kPa
	Floor—MEP/Misc.	0.96 kPa	0.96 kPa
	Exterior envelope	0.72 kPa	0.72 kPa
Live loads	Roof live	0.96 kPa	0.96 kPa
	Floor—Office	2.39 kPa	n/a
	Floor—Residential	n/a	1.92 kPa
	Floor—Lobby	4.79 kPa	4.79 kPa
Snow loads	Roof—Snow	1.20 kPa	1.20 kPa

Table 1. Prototype building characteristics and design loads.

Both steel buildings were designed using rolled, wide-flange (W-shape) sections for the beams and columns. The floors were 76.4 mm steel deck with 50.8 mm of concrete cover. The beams were designed with varying amounts of partial-composite action with the floor slab for checking code deflection limits, but composite action was ignored during seismic drift calculations, as is standard in practice. The lateral system is composed of buckling restrained braced frames (BRBFs) of various sizes as denoted by the red dashed rectangles in the steel building plans.

In addition to the design components described by Wilson (2018), this study also included additional building materials that were deemed to have the potential of an effect on the LCA, such as the foundations, façade, and fire proofing materials. Building foundations were designed to resist structural loads and provide bearing pressures less than the allowable soil bearing capacity. The assumed allowable soil bearing pressure was 191.5 kPa for site class D soil conditions. It was assumed that differential settlement would not control foundation size. The foundation thickness was calculated to resist punching shear. The quantity of rebar in the foundation was estimated through discussions with practicing structural engineers to be $86-96 \text{ kg/m}^3$. The foundations of the 5-story buildings were isolated spread footings under all gravity columns and combined footings under the lateral force resisting elements, as shown in Figure 3. The difference in number of lateral force resisting elements needed between the mass timber and steel buildings is apparent in the required foundation size, with the mass timber buildings having larger foundation area. The foundation for the 12-story mass timber building was a mat foundation due to the large number of CLT rocking walls. Conversely, the foundation of the 12-story steel building was a combination of combined and isolated footings, as shown in Figure 4.



Figure 3. 5-story buildings foundation plans: mass timber building (Left), steel building (Right).



Figure 4. 12-story building foundation plans: mass timber building (Left), steel building (Right).

Fire proofing was included in the study using gypsum wall board covering the required amount of mass timber for Type IV-B construction in Seattle, Washington and intumescent paint covering the steel in the steel buildings. The steel and CLT buildings were assumed to have identical facades, elevator and stair shafts, and non-structural build out (i.e., partition walls, doors, HVAC, etc.). The building façade was assumed to be 60% glass curtain wall and 40% insulated metal panels which is a common ratio for office buildings in the Pacific Northwest, as discussed by Pierobon et al. (2019). The glass curtain wall consisted of normal strength glazing panels and aluminum extrusion, the insulated metal panels consisted of galvanized steel studs, polystyrene foam insulation, a vapor barrier, a metal cladding on the exterior, and a gypsum wall board on the interior. In between the CLT decking and the lightweight concrete topping, a foam board was used as a vapor barrier and acoustic dampener. The roofing consisted of a 48 mm PVC membrane. The interior build out was not included in the scope of this study.

A comment on study limitations is that the mass timber buildings in this study likely use more timber than what a cost-competitive building in practice would use. This may be because the study buildings use 5-ply (175 mm) floor panels and thick 9-ply (315 mm) wall panels. To place the study buildings in perspective with an industry designed building, the cancelled 12-story Framework building in Portland, OR was also an all-wood, mass timber building using self-centering CLT walls and had a timber quantity of 0.28 m³ per m² of building floor area [24]. The 5-story and 12-story mass timber buildings in this study have timber quantities of 0.47 m³ and 0.38 m³ per m² of building floor area, respectively.

2.2. Building Materials Inventory

Detailed models of the prototype buildings were created in Revit to generate accurate bill of material schedules (BOMS), presented in Table 2. When modeling the buildings in Revit, openings were created in the decks of each floor where columns/walls pass through to avoid double counting intersecting materials. For the mass timber buildings, individual columns were assumed to span between each floor level (platform construction) whereas with the steel building archetypes, columns traveled through multiple floor levels (balloon construction). For the mass timber buildings, beam lengths were determined using inside distances between girders and columns. For the steel buildings, beam lengths were determined using flange-to-flange distances on connecting columns or girders. Material quantities for all objects were calculated using cross sectional area multiplied by the aforementioned lengths. On elevated levels, edge-of-slab was assumed to extend 0.3–0.5 m beyond the centerline of the perimeter beams and columns.

Material:	Unit:	5-Story Steel Building:	5-Story MT ¹ Building	12-Story Steel Building	12-Story MT ¹ Building
Foundation Materials					
Foundation Concrete	m ³	323.9	338.3	2147.2	1933.8
Foundation Rebar	kg	28,037.5	32,320.0	185,633.6	184,830.0
Structure Materials	U				
Beams/Columns Steel	kg	263,762.9	-	1,083,052.2	-
BRBF Concrete	m ³	14.7	-	53.5	-
BRBF Steel	kg	14,376.1	-	54,727.6	-
Rocking Walls CLT	m ³	-	535.8	-	2115.4
Beams/Columns Glulam	m ³	-	1028.9	-	2463.7
Flooring Materials					
Flooring Concrete	m ³	1011.5	224.8	2378.4	-
Flooring Concrete (lightweight)	m ³	-	374.6	-	1130.3
Flooring Rebar	kg	26,201.4	26,202.4	79,055.7	79,055.7
Flooring Steel Decking	kg	82,399.0	-	240,334.2	-
Flooring CLT	m ³	-	1214.6	-	3486.7
Polysio Foam Board (25 mm)	m ²	-	5899.7	-	20,396.7
6 mil Polyethylene	m ²	-	5731.2	-	19,813.4
Envelope Materials					
3" Insulated Metal Panel	m ²	1661.9	1661.9	4519.6	4518.8
5/8" Type-X Gypsum Board	m ²	2742.1	2742.1	7457.4	35,328.5
Aluminum Extrusion	kg	9206.8	9207.2	25,034.5	25,033.9
Galvanized Metal Studs	kg	7486.1	7486.1	20,354.5	20,354.5
Glazing Panel	kg	134,907.3	134,907.3	366,832.7	366,832.7
PVC Membrane 48 mil	m ²	1404.7	1404.7	1765.9	1765.9

Table 2. Bill of materials schedule.

¹ MT = Mass Timber.

2.3. LCIA Methodology and System Boundary

As the goal of this study was to use Athena IE4B to compare the environmental impacts from the archetype buildings over the production, construction, end-of-life, and beyond life stages for a 60-year period [25], the system boundary was defined as "cradle-to-grave" with the exclusion of the "Use" phase (Phase B1-B7) [26], as shown in Figure 5. The use phase was excluded from the system boundary to compare the building materials using the embodied energy and emissions without the influence of operational energy differences that may exist and are outside the scope of this study.



– – System Boundary

Figure 5. Assessment system boundary with the Use phase excluded.

Once an accurate bill of materials for each building was generated, they were imported into the IE4B LCA tool. The Athena IE4B tool has been specifically designed to model the environmental impacts of building projects in North America. The tool allows the user to input construction products rather than individual materials, Table 2 represents the exact quantities modeled from a construction materials standpoint. Detailed schedules reporting the raw material, energy, and water inputs are able to be generated in the IE4B software if researchers would like greater control over inventory flows. The IE4B follows the EN15978 (2011) standard, which includes impacts from productions, transportation, construction, and demolition; the standard also includes impacts from energy and water use, which were excluded from this study. All default settings were using in the development of the life-cycle assessment models to allow for the results to be easily replicable and to remove potential bias of selecting environmental product declarations (EPDs) of specific materials or products. The project location was set as Seattle, Washington in IE4B for calculations involving all transportation distances and energy mixes. The 5-story buildings were designated as Office Rental Buildings and the 12-story buildings were designated as Multi-Unit Residential Rental Buildings. The IE4B tool then used the Athena LCI database, which is composed of EPDs that primarily reflect industry averages in North America, to determine the environmental impact of each structure. The environmental impact results presented across the six categories in Section 3 exclude stage D, but stage D, and its effect on the category of global warming potential, is presented and discussed in Section 4.2. Additional information about the IE4B methodology, as well as their list of North American LCI data, can be found in the Athena IE4B User Manual and Transparency Document [27].

2.4. Summary of Environmental Impact Categories

The IE4B uses the TRACI methodology [28] to aggregate and quantify environmental impacts into the following 6 categories: (1) global warming potential, (2) acidification

potential, (3) eutrophication potential, (4) HH particulate, (5) ozone depletion potential, and (6) smog potential. The categories are briefly explained here to provide context to the discussion of results. Global warming potential (GWP) is a measure of greenhouse gas emissions, which contribute to the fueling of climate change, and is measured using kilograms of carbon dioxide equivalents (kg CO₂ eq.). Acidification potential is a measure of the acids being admitted into the atmosphere, which contribute to acid rain, and is measured using kilograms of sulfur dioxide equivalents (kg SO₂ eq.). Eutrophication potential measures of the potential of pollution in water systems or aquatic ecosystems. An example is fertilizer runoff, which can cause excessive plant or algal growth. Eutrophication potential is measured using kilograms of nitrogen equivalent (kg N eq.). HH particulate is a measure of fine particulates that are emitted to the air and atmosphere that cause a danger to human health through respiratory and cardiovascular diseases and is measured in kilograms of particles under 2.5 micrometers (PM2.5) equivalent (kg PM2.5 eq). Ozone depletion potential measures the amount of hydrocarbons emitted that contribute to the depletion of Earth's ozone layer and is measured using kilograms of Chlorofluorocarbon-11 equivalents (kg CFC-11 eq). Smog Potential is a measure of ground level ozone created by volatile organic compounds and numerous nitrogen oxides (NO_x) interacting in sunlight and creating harmful air (i.e., smog). Smog potential is measured in units of kilograms of ozone (trioxygen) equivalents (kg O_3 eq.).

3. Results

3.1. Comparison of Environmental Impact Categories

The results of the LCA for the 5-story and 12-story buildings from Stage A to Stage C are presented in Figure 6 normalized to the larger environmental impact value for each category. The normalizing value is provided next to the larger environmental impact value so that actual quantities can be calculated, if desired. The GWP shown in Figure 6 does not include the biogenic carbon sequestration from Stage D "beyond life", as the considerations involved in incorporating the biogenic carbon sequestration of the timber growth is discussed further in Section 4.2. Similar to results of previous studies, the mass timber buildings had a significantly lower GWP than the steel buildings. The GWP normalized in terms of building square footage was 160.9 kg CO_2 eq./m² and 164.7 kg CO_2 eq./m² for the 5-story and 12-story mass timber buildings, respectively. The 5-story and 12-story steel buildings had normalized GWP of 210.7 kg CO_2 eq./m² and 232.6 kg CO_2 eq./m², respectively, which is approximately 31–41% larger than their mass timber counterparts. Higher GWP density (kg CO_2 eq. per m²) with increasing building height is consistent with the findings of Su and Zhang (2016). The correlation between increasing building height and increasing GWP discussed by Su and Zhang (2016), developed using LCA analysis of steel buildings, appears to extend to the mass timber buildings as well. This correlation is likely due to the fact that taller buildings have significantly larger foundations and gravity load members due to their larger loads.

The steel buildings had lower environmental impact in the categories of acidification potential, ozone depletion potential, and smog potential. The difference in ozone depletion potential is particularly large, where the steel buildings have between 45–55% the ozone depletion potential as the mass timber buildings. The mass timber buildings had lower human health (HH) particulate potential and eutrophication potential, though the buildings were within 15% of each other.



Figure 6. Normalized comparison environmental impacts of mass timber and steel buildings.

3.2. Comparison by Building Component Group

This section further analyzes the environmental emissions of the archetype buildings separated into the main building components, as shown in Figure 7. For the steel buildings, the building was separated into the foundations, which were mostly concrete by volume, the structural system, which was all steel except for the grout inside the BRBs, the floors and roof, which were again mostly concrete and the building envelope which was assumed to be 60% structural glass glazing and 40% solid surfaces. The mass timber buildings were separated along the same lines except that the structural system was further divided into the lateral force resisting system, which is 9-ply CLT, and the gravity force resisting system, which is glulam timber. This was because the EPDs for CLT and glulam are different and the effects of those differences can be seen in the Ozone Depletion Potential and HH Particulate impact categories, where the glulam frame contributes a much higher percentage of the total emissions than the CLT walls or CLT floors.

While the effect is larger for the steel buildings, the components that are mostly concrete contribute upwards of half the total GWP emissions. The total volume of concrete required for a project is heavily related to building design decisions, and regardless of the material choice for the primary structural system, designers can take steps that reduce total concrete use by aiming for efficient design of the concrete elements. Both 12-story buildings in this study have significantly larger foundations, which required approximately 5 times more concrete and reinforcing steel per m² of building footprint, than their 5-story counterparts. Figure 7 shows that the percentage of GWP impact attributed to the foundations increased approximately 10% between the 5-story and 12-story buildings. For the mass timber buildings, the foundations alone contributed 30% and 40% of the total GWP emissions for the 5-story and 12-story buildings, respectively.

Additionally, for the steel buildings, the floors contribute between one-half to twothirds of the total concrete quantity. Therefore, environmental emissions could be improved in steel buildings by advocating for a design approach that uses mass timber floor panels over the traditional cast-in-place concrete floors. An imprecise analysis of the effect of using mass timber floors for the steel buildings in this study could be estimated by replacing the emissions associated with the steel building concrete floors with the emissions associated with the mass timber buildings CLT floors. Under that scenario, the GWP of the 5-story and 12-story steel buildings would be reduced by approximately 10% to 15%. Compared to the 5-story and 12-story mass timber buildings, the theoretical wood-floored steel buildings would have GWP 15% to 20% greater than their timber counterparts.



Structural system for steel buildings & gravity frame for timber buildings

Figure 7. Percentage contribution of building components to environmental impact categories.

Lastly, the building envelope, which was structural glass glazing, light-frame steel studs, and aluminum for this study, contributed more than 20% of total emissions to all impact categories except ozone depletion potential. Therefore, if the goal of a designer is to reduce the embodied emissions of a building, the impact of the envelope cannot be ignored as a major source of emissions. Further, most building envelopes use different materials than the primary structural materials of steel, concrete, or timber and therefore are not directly tied to structural system design choices. The impact of different envelope alternatives on life-cycle emissions should be studied further. Additionally, the building envelope design is also highly tied to the energy performance of the building during the use phase. Therefore, LCA studies on the performance of envelope alternatives probably should not omit the use phase, as picking envelope materials that minimizing the embodied energy but result in much higher operational energy may not be a net positive.

4. Discussion

4.1. Comparison by Life Cycle Stage

Another way to analyze the environmental impact of the building alternatives is to divide the analysis into the life-cycle stages (A–C), neglecting the use stage (B). For the environmental impact categories of HH Particulate and Ozone Depletion Potential the A1-A3 stages (production stage) contributed more than 95% of the total emissions for all the buildings. Since the production stage constitutes most of the emissions for those two categories, they are omitted from the rest of this section's discussion about the impact of the construction stages (A4–A5) and end-of-life stages (C and D).

The emissions of each building separated by life-cycle stage for the categories of GWP, acidification potential, eutrophication potential, and smog potential are presented in Table 3 along with their relative percentage of the total emissions for that category.

For steel and mass timber buildings, the A1–A3 stages contributed 90% and 83% of the total GWP emissions, respectively. Interestingly, the construction stages (A4 and A5) and end-of-life (C) stages contributed more to the total emissions of the mass timber buildings than the steel buildings. The difference between the mass timber and steel buildings for the construction and end-of-life stages was greater for the 5-story building than the 12-story building. The eutrophication potential and acidification potential categories followed a similar trend as GWP, where the construction and end-of-life stages constitute a higher percentage of the total emissions for the mass timber buildings.

LCA Category	Building ¹	Production (A1–A3) ²	Construction (A4 & A5) ²	End-of-Life (C1–C4) ²	Total
Global Warming Potential (10 ³ kg CO ₂ eq.)	5-story steel	1213 (90%)	77 (6%)	59 (4%)	1349
	5-story MT	826 (83%)	90 (9%)	83 (8%)	999
	12-story steel	4112 (90%)	278 (6%)	198 (4%)	4588
	12-story MT	2596 (83%)	298 (9%)	252 (8%)	3146
	5-story steel	5387 (80%)	786 (11%)	616 (9%)	7689
Acidification Potential (kg SO ₂ eq.)	5-story MT	5576 (75%)	868 (12%)	1006 (13%)	7450
	12-story steel	17,614 (78%)	2949 (13%)	2112 (9%)	22,675
	12-story MT	16,844 (74%)	2907 (13%)	3052 (13%)	22,803
	5-story steel	780 (88%)	72 (8%)	36 (4%)	888
Eutrophication Potential	5-story MT	729 (85%)	69 (8%)	61 (7%)	859
(kg N eq.)	12-story steel	2403 (86%)	259 (9%)	126 (5%)	2788
	12-story MT	2062 (83%)	229 (9%)	185 (8%)	2476
Smog Potential (10 ³ kg O ₃ eq.)	5-story steel	79 (65%)	24 (20%)	19 (15%)	135
	5-story MT	96 (62%)	27 (17%)	32 (21%)	155
	12-story steel	254 (62%)	91 (22%)	66 (16%)	411
	12-story MT	285 (61%)	88 (18%)	97 (21%)	470

Table 3. Life-cycle assessment (LCA) environmental impact data summarized by life-cycle stage.

¹ MT = Mass timber. ² Number in parenthesis is the life-cycle stage emissions as a percentage of that building's total emissions for the category.

The only category where the production stages did not account for more than 65% of total emissions was Smog Potential. For all the buildings in this study, the production stage contributed approximately 62% of the total smog potential emissions, with construction constituting approximately 17–22% and end-of-life constituting 15–21%. The beyond life stage (D) is discussed next, as it heavily relates to how carbon sequestration is accounted for in the LCA analysis.

4.2. Carbon Accounting

A point of ongoing debate when completing a cradle-to-grave life cycle analysis is the end-of-life and beyond life scenarios. End-of-life and beyond life considerations are difficult to predict because they must be forecasted decades into the future. For mass timber buildings, the GWP impact category can be highly influenced by the beyond building life (D) stage and how carbon emissions are accounted. For any wood product, there are several ways in which the wood contained can contribute to reduction in greenhouse gas emissions, as outlined by Werner et al. (2006) [29]. Timber is often referred to as being carbon neutral, or even a source of carbon sequestration, due to the biological process of the biomass removing CO₂ from the atmosphere through photosynthesis. However, this feature of timber serving as a temporary carbon sink, referred to as biogenic carbon emissions, has a few caveats and there is no clear consensus on how biogenic carbon should be modeled during analysis [30]. One reason is that the sequestered CO_2 stored in wood biomass will be released if that biomass decays or is incinerated. This means that if the global wood biomass stock is reduced, due to timber harvesting to make engineered wood products, the total biomass pool of stored carbon is reduced, leading to an increase in atmospheric CO_2 concentrations [31]. Therefore, a crucial co-requisite for increasing mass timber production as a method for removing carbon from the atmosphere long-term is

sustainable harvesting and restoration of forest growth after logging to ensure the global biomass stock is maintained or increased through forest growth [32,33]. Several studies have discussed the arguments for and against counting the beyond life stage in the total GWP [12,29]. In general, it is accepted that there is some permanent, or long-term carbon storage created from wood products [30,34].

The Athena IE4B tool calculates end-of-life and beyond life quantities by first proportionally categorizing all materials as being recycled, reused, or landfilled. Aside for metals, materials that are recycled, reused, or incinerated for energy recovery are deemed to have left the system boundary. Metals that are recycled are evaluated using a closed loop recycling method. In general, the Athena IE4B assumes that materials that are commonly landfilled today will be landfilled in the future and materials that are commonly recycled today will be recycled in the future. Further descriptions about the calculation of stage D results from IE4B can be found in the IE4B User Manual and Transparency Document [27]. With that stated, this study follows the carbon accounting guidelines set out by the IPCC (2006) and used by the Athena IE4B [25,35]. Athena IE4B only calculates the biogenic carbon permanently sequestered and reports this negative GWP value in the beyond building life stage (stage D). The Athena IE4B calculates the permanently sequestered carbon by assuming a certain percentage of the wood biomass of the mass timber products never burn or decay, it is the portion of timber that ends up in landfill and remains in stasis for perpetuity as outlined by Athena [27]. There is still debate about the ratio of biomass that will decay, and therefore release its temporarily stored carbon, versus the amount that will retain its sequestered carbon. Further, there are also questions about the validity of the assumption that increasing harvesting of lumber to meet increasing mass timber demand will not negatively affect global biomass levels. Due to these two unanswered questions, the analysis results presented in Section 3 did not account for the biogenic CO₂ emissions reported in Stage D, which is in line with the guidelines set out by Athena IE4B and the product category rules (PCR) for architectural wood products [36].

Instead, the beyond building life emissions (stage D) are reported in this section, which includes the biogenic carbon of the mass timber buildings. As shown in Table 4, the amount of sequestered carbon for the mass timber buildings is slightly larger than that of the total amount of embodied carbon for stages A-C. In actuality, the total GWP emissions for the mass timber buildings would not be negative, as this study did not include the contributions of non-structural interior building components, such a partition walls, carpeting, etc. However, Table 4 clearly shows that if Stage D is accounted for in the GWP LCIA, then the mass timber buildings have a significantly lower environmental impact than the steel alternatives. This is predominately because there is a much smaller amount of sequestered carbon in the steel buildings relative to the mass timber buildings. This sequestered carbon in the steel buildings is attributed to components that can be directly reused, refurbished, or recycled with minimal added effort.

Building	Stage D GWP (10 ³ kg CO ₂ eq.)	GWP for Stages A–C (10 ³ kg CO ₂ eq.)	GWP for Stages A-D (10 ³ kg CO ₂ eq.)
5-story steel	-71.2	1350	1280
5-story mass timber	-1140	1000	-141
12-story steel	-132	4590	4460
12-story mass timber	-3230	3150	-84.0

Table 4. LCA global warming potential data for life-cycle stage D.

4.3. GWP Analysis and Literature Comparison

Several past studies have compared the life-cycle embodied emissions of timber buildings to steel and concrete buildings. Figure 8 illustrates the GWP results for the four buildings analyzed in this study compared to several other North American LCA studies on whole buildings. While these results are difficult to compare due to analysis system boundary, software, process, and building inventory differences, it does place the embodied emissions of the buildings in this study in a broad context with the existing literature. From Figure 8, it is demonstrated that the results from the presented LCA analysis are within similar range of magnitude as prior mass timber studies. Since no studies exist on steel buildings for North America, studies on reinforced concrete buildings were used to provide additional context. Throughout all the studies there is a clear trend that reinforced concrete buildings have considerably higher GWP than either mass timber or steel. Additionally, even a hybrid reinforced concrete and mass timber buildings in this study. However, the hybrid reinforced concrete and mass timber building is significantly lower GWP than full concrete buildings. With this in mind, future research should explore the environmental impact of steel and mass timber hybrid buildings.



Figure 8. Comparison of normalized GWP values from previous studies in the literature.

5. Conclusions

The results of this study show that mass timber buildings have advantages over conventionally framed steel buildings with respect to several environmental impact categories, especially global warming potential. For a system boundary of cradle-to-grave, excluding the operation phase, the mass timber archetype buildings had GWP that were 31% to 41% lower than that of the steel building alternatives. Further, if the carbon sequestration effects of the buildings (Stage D) were included in the analysis, the mass timber buildings became close to carbon neutral (excluding operational energy) while the steel buildings remained relatively unchanged.

However, the steel buildings had lower environmental impact in the categories of acidification potential, ozone depletion potential, and smog potential compared to the mass timber buildings. The steel buildings had ozone depletion potential emissions that were 45% to 55% lower than that of the mass timber building alternatives. For broader context with respect to other structural system, mainly reinforced concrete, the GWP calculated in this study was compared to previous studies on North American buildings. The steel buildings had GWP emissions in between that of mass timber buildings and the reinforced concrete buildings. Further, the GWP of the steel buildings located in the United States, as calculated in this study, was significantly lower than the GWP of steel buildings located in China, calculated by Su and Zhang (2016). This is likely due to the North American steel, which is produced using cleaner processes that mostly utilize recycled scrap steel.

Further, a large portion of the emissions across all six impact categories for both buildings were from the concrete components and the building envelope components. For the steel buildings, this was especially pronounced because the foundations and floors were concrete, resulting in more than 50% of the total GWP being attributed to the concrete components. This finding suggests that there is likely a significant environmental benefit to using mass timber floors in steel buildings to reduce their environmental impact. The building envelope components contributed more than 20% of the total emissions in the impact categories of GWP and smog potential. The envelope contributed more than 40% of the total emissions for the categories of HH particulate, eutrophication potential, and acidification potential. This demonstrates that holistic design is best suited for reducing environmental impact of buildings, as all four archetypes buildings would have benefited from a lower emission building envelope.

Lastly, future research may focus on the exploration of how different design decisions, including variation in column spacing, beam spacing, and building height may affect material quantity and therefore life-cycle environmental impact. Variations in design configuration that can make use of thinner mass timber panels, smaller foundations, and less concrete for flooring should further reduce the total environmental impact. Lastly, future work should focus on incorporating the use phase scenarios to further study the effect of the building envelope design on both embodied and operational energy and the interaction between the two.

Author Contributions: K.A.: Built Revit models to calculate material quantities presented in the BOMS (Table 2), conducted LCA analysis using IE4B, analyzed data from IE4B, and contributed to the writing and revision of the manuscript. A.R.P.: Contributed to analysis of the data from IE4B. He also contributed to writing, editing, and revising the research manuscript. All authors have read and agreed to the published version of the manuscript.

Funding: The APC was funded by Washington State University.

Data Availability Statement: Data presented in this study is available on request from the authors.

Acknowledgments: Any opinions, findings, and conclusions expressed in this material are those of the authors and do not necessarily reflect the views of the sponsor.

Conflicts of Interest: The authors declare no conflict of interest.

References

- 1. Abergel, T.; Dean, B.; Dulac, J. Towards a Zero-Emission, Efficient, and Resilient Buildings and Construction Sector: Global Status Report 2017; UN Environment and International Energy Agency: Paris, France, 2017.
- Levermore, G.J. A review of the IPCC Assessment Report Four, Part 1: The IPCC process and greenhouse gas emission trends from buildings worldwide. *Build. Serv. Eng. Res. Technol.* 2008, 29, 349–361. [CrossRef]
- United States Green Building Council. Building Life-Cycle Impact Reduction; White Paper; United States Green Building Council: Washington, DC, USA, 2019.
- 4. Su, X.; Zhang, X. A detailed analysis of the embodied energy and carbon emissions of steel-construction residential buildings in China. *Energy Build.* **2016**, *119*, 323–330. [CrossRef]
- 5. Kahhat, R.; Crittenden, J.; Sharif, F.; Fonseca, E.; Li, K.; Sawhney, A.; Zhang, P. Environmental impacts over the life cycle of residential buildings using different exterior wall systems. *J. Infrastruct. Syst.* **2009**, *15*, 211–221. [CrossRef]
- Iyer-Raniga, U.; Wong, J.P.C. Evaluation of whole life cycle assessment for heritage buildings in Australia. *Build. Environ.* 2012, 47, 138–149. [CrossRef]
- Ochoa, L.; Hendrickson, H.; Matthews, H. Economic input-output life-cycle assessment of U.S. residential buildings. *J. Infrastruct.* Syst. 2002, 8, 132–138. [CrossRef]
- Ramesh, T.; Prakash, R.; Shukla, K.K. Life cycle energy analysis of buildings: An overview. *Energy Build*. 2010, 42, 1592–1600. [CrossRef]
- 9. Hafner, A. Contribution of timber buildings on sustainability issues. In Proceedings of the World Sustainable Building 2014, Barcelona, Spain, 28–30 October 2014.
- 10. Connolly, T.; Loss, C.; Iqbal, A.; Tannert, T. Feasibility Study of Mass-Timber Cores for the UBC Tall Wood Building. *J. Build.* 2018, *8*, 98. [CrossRef]
- 11. Pierobon, F.; Huang, M.; Simonen, K.; Ganguly, I. Environmental benefits of using hybrid CLT structure in midrise non-residential construction: An LCA based comparative case study in the US Pacific Northwest. J. Build. Eng. 2019, 26, 100862. [CrossRef]

- 12. Robertson, A.B.; Lam, F.C.F.; Cole, R.J. A Comparative Cradle-to-Gate Life Cycle Assessment of Mid-Rise Office Building Construction Alternatives: Laminated Timber or Reinforced Concrete. *Buildings* **2012**, *2*, 245–270. [CrossRef]
- 13. Gustavsson, L.; Joelsson, A.; Sathre, R. Life cycle primary energy use and carbon emissions of an eight-storey wood-framed apartment building. *Energy Build*. **2010**, *42*, 230–242. [CrossRef]
- 14. Guggemos, A.A.; Horvath, A. Comparison of environmental effects of steel- and concrete-framed buildings. *J. Infrastruct. Syst.* **2005**, *11*, 93–101. [CrossRef]
- 15. Petersen, A.K.; Solberg, B. Greenhouse gas emissions, life-cycle inventory and cost-efficiency of using laminated wood instead of steel construction: Case: Beams at Gardermoen airport. *Environ. Sci. Policy* **2002**, *5*, 169–182. [CrossRef]
- 16. Pomponi, F.; Moncaster, A. Scrutinizing embodied carbon in buildings: The next performance gap made manifest. *Renew. Sustain. Energy Rev.* **2018**, *81*, 2431–2442. [CrossRef]
- 17. Wilson, A.; Motter, C.; Phillips, A.R.; Dolan, J.D. Seismic response of post-tensioned cross-laminated timber rocking wall buildings. *J. Struct. Eng.* **2020**, 146. [CrossRef]
- 18. Green, M.C.; Karsh, E.J. *The Case for Tall Wood Buildings, in Mgb Architecture + Design;* Equilibrium Consulting: Vancouver, BC, Canada, 2012.
- 19. SOM. AISC Steel & Timber Research for High-Rise Residential Buildings; Skidmore, Owings, and Merrill: Chicago, IL, USA, 2017.
- Pei, S.; Van de Lidt, J.; Barbosa, A.; Berman, J.; McDonnell, E.; Dolan, J.; Blomgren, H.E.; Zimmerman, R.B.; Huang, D.; Wichman, S. Experimental seismic response of a resilient 2-story mass timber building with post-tensioned rocking walls. *J. Struct. Eng.* 2019, 145, 04019120. [CrossRef]
- Sarti, F.; Palermo, A.; Pampanin, S. Quasi-static cyclic testing of two-thirds scale unbonded posttensioned rocking dissipative timber walls. J. Struct. Eng. 2016, 142. [CrossRef]
- 22. Wilson, A.; Phillips, A.R.; Motter, C.; Lee, J.Y.; Dolan, J.D. Seismic loss analysis of buildings with post-tensioned cross-laminated timber walls. *Earthq. Spectra* 2020. [CrossRef]
- Wilson, A. Numerical Modeling and Seismic Performance of Post-Tensioned Cross-Laminated Timber Rocking Wall Systems. Master's Thesis, Washington State University, Pullman, WA, USA, 2018.
- 24. Chen, Z.; Hongmei, G.; Bergman, R.D.; Liang, S. Comparative life-cycle assessment of a high-rise mass timber building with an equivalent reinforced concrete alternative using the Athena Impact Estimator for buildings. *Sustainability* **2020**, *12*, 4708. [CrossRef]
- ASMI. Impact Estimator for Buildings Version 5.4.01; Athena Sustainable Materials Institute: Ottawa, ON, Canada, 2019. Available online: http://www.athenasmi.org/resources/about-lca/technical-details/ (accessed on 2 December 2020).
- 26. EN. 15978 Sustainability of Construction Works—Assessment of Environmental Performance of Buildings—Calculation Method; European Committee for Standardization: Brussels, Belgium, 2011.
- 27. ASMI. User Manual and Transparency Document: Impact Estimator for Buildings v.5; Athena Sustainable Materials Institute: Ottawa, ON, Canada, 2019. Available online: https://calculatelca.com/wp-content/uploads/2019/05/IE4B_v5.4_User_Guide_May_2019.pdf (accessed on 17 January 2021).
- Bare, J.C.; Norris, G.A.; Pennington, D.W.; McKone, T. TRACI: The tool for the reduction and assessment of chemical and other environmental impacts. J. Ind. Ecol. 2003, 6, 49–78. [CrossRef]
- 29. Werner, F.; Taverna, R.; Hofer, P.; Richter, K. Greenhouse gas dynamics of an increased use of wood in buildings in Switzerland. *Clim. Chang.* **2006**, *75*, 319–347. [CrossRef]
- 30. Hoxha, E.; Passer, A.; Saade, M.R.M.; Trigaux, D.; Shuttleworth, A.; Pittau, F.; Habert, G. Biogenic carbon in buildings: A critical overview of LCA methods. *Build. Cities* **2020**, *1*, 504–524. [CrossRef]
- Skullestad, J.L.; Bohne, R.A.; Lohne, J. High-rise timber buildings as a climate change mitigation measure—A comparative LCA of structural system alternatives. *Energy Procedia* 2016, 96, 112–123. [CrossRef]
- 32. BSI. Specification for the Assessment of the Life Cycle Greenhouse Gas Emissions of Goods and Services PAS 2050:2011; British Standards Institute (BSI): London, UK, 2011.
- ISO. Greenhouse Gases: Carbon Footprint of Products: Requirements and Guidelines for Quantification and Communication ISO 14067:2018; ISO: Geneva, Switzerland, 2018.
- Breton, C.; Blanchet, P.; Amor, B.; Beauregard, R.; Chang, W.-S. Assessing the Climate Change Impacts of Biogenic Carbon in Buildings: A Critical Review of Two Main Dynamic Approaches. *Sustainability* 2018, 10, 2020. [CrossRef]
- 35. International Panel on Climate Change (IPCC). 2006 IPCC Guidelines for National Greenhouse Gas Inventories; IPCC: Geneva, Switzerland, 2006.
- FPInnovations. Product Category Rules (PCR) North American Structural and Architectural Wood Products. 2015. Available online: https://fpinnovations.ca/ResearchProgram/environment-sustainability/epd-program/Documents/pcr-v2.pdf (accessed on 6 January 2021).